

IMPERIAL INSTITUTE

MONOGRAPHS ON MINERAL RESOURCES
WITH SPECIAL REFERENCE TO THE
BRITISH EMPIRE

IMPERIAL INSTITUTE

MONOGRAPHS ON MINERAL RESOURCES
WITH SPECIAL REFERENCE TO THE
BRITISH EMPIRE

PREPARED UNDER THE DIRECTION OF THE
MINERAL RESOURCES COMMITTEE OF THE
IMPERIAL INSTITUTE, WITH THE ASSISTANCE
OF THE SCIENTIFIC AND TECHNICAL STAFF

TIN ORES

BY G. M. DAVIES, M.Sc. (LOND.), F.G.S.

Scientific and Technical Department, Imperial Institute



LONDON

JOHN MURRAY, ALBEMARLE STREET, W

1919

ALL RIGHTS RESERVED

IMPERIAL INSTITUTE

Director : Professor WYNDHAM DUNSTAN, C.M.G., LL.D., F.R.S.

Scientific and Technical Research Department and Technical Information Bureau

Superintendents : T. A. HENRY, D.Sc. (Lond.), F.C.S. ; H. BROWN ; E. GOULDING, D.Sc. (Lond.), F.I.C.

Assistant Superintendents : T. CROOK, A.R.C.Sc., F.G.S. ; R. G. PELLY, F.I.C.

Principal Assistant : S. J. JOHNSTONE, B.Sc. (Lond.), A.I.C.

Public Exhibition Galleries.—Colonial and Indian Collections

Senior Technical Superintendent : S. E. CHANDLER, D.Sc. (Lond.), A.R.C.Sc., F.I.S.

Other Members of the Scientific and Technical Staff of the Institute

A. E. ANDREWS, F.C.S.

Miss H. BENNETT, B.Sc.
(Lond.).

L. L. BLACKNELL.

G. S. BOULGER, F.I.S. F.G.S.

F. BOULTON.

G. T. BRAY, A.I.C.

W. S. DAVEY.

G. M. DAVIES, M.Sc. (Lond.),
F.G.S.

F. L. ELLIOTT.

A. T. FAIRCLOTH.

F. FERRABOSCHI, M.A. (Cantab.),

A.I.C., F.C.S.

J. R. FURLONG, Ph.D. (Würz-
burg), A.I.C.

Miss R. C. GROVES, M.Sc.
A.I.C.

A. B. JACKSON, A.L.S.

H. J. JEFFERY, A.R.C.Sc., F.I.S.

A. S. JUDGE, late I.C.S.

B. E. LONG, B.A. (Cantab.).

A. D. LUMB, A.R.S.M., F.G.S.

T. McLACHLAN, A.I.C.

F. MAJOR, B.Sc. (Lond.).

G. L. MATTHEWS, B.Sc. (Lond.),
A.I.C.

E. C. MOORE.

Miss A. C. S. PALMER.

O. D. ROBERTS, F.I.C.

S. J. ROGERS, B.Sc. (Lond.),
A.I.C.

F. W. ROLFE.

W. G. RUMBOLD.

H. SPOONER.

J. D. F. WEST, A.I.C.

B. W. WHITEFIELD.

W. O. R. WYNN, A.I.C.

IMPERIAL INSTITUTE

Advisory Committee on Mineral Resources, 1919

The Right Hon. the VISCOUNT HARCOURT, D.C.L. (*Chairman*).

*Admiral Sir EDMOND SLADE, K.C.V.O., K.C.I.E. (nominated by the Admiralty), *Vice-Chairman*.

EDMUND DAVIS, Esq.

*Professor WYNDHAM DUNSTAN, C.M.G., LL.D., F.R.S., Director of the Imperial Institute.

W. J. GLENNY, Esq., Department of Overseas Trade (nominated by the Board of Trade).

*Professor J. W. GREGORY, F.R.S., Professor of Geology in the University of Glasgow, formerly Director of the Geological Survey of Victoria, Australia.

Sir ROBERT HADFIELD, Bart., lately President of the Iron and Steel Institute.

*Dr. F. H. HATCH, Consulting Mining Engineer, formerly President of the Institution of Mining and Metallurgy.

Major VAUGHAN MORGAN, Intelligence Department, War Office (nominated by the War Office).

W. W. MOYERS, Esq., Messrs. H. A. Watson & Co.

Dr. T. A. HENRY, *Secretary*.

Major A. D. LUMB, M.C. (*Acting Secretary*).

* *Members of the Editorial Sub-Committee.*

PREFACE

THE Mineral Resources Committee of the Imperial Institute has arranged to issue this series of monographs on Mineral Resources in amplification and extension of those which have appeared in the *Bulletin of the Imperial Institute* during the past fifteen years.

The monographs are prepared either by members of the Scientific and Technical Staff of the Imperial Institute, or by external contributors, to whom have been available the statistics and other special information relating to mineral resources collected and arranged at the Imperial Institute.

The object of these monographs is to give a general account of the occurrences and commercial utilisation of the more important minerals, particularly in the British Empire. No attempt has been made to give details of mining or metallurgical processes.

HARCOURT,
*Chairman Mineral
Resources Committee.*

July 1919.

CONTENTS

CHAPTER I

TIN ORES: THEIR OCCURRENCE, CHARACTERS AND USES

PAGE

THE ORES OF TIN—WORLD'S PRODUCTION OF TIN ORE—VALUATION OF TIN ORE—THE PRICE OF TIN —THE PROPERTIES OF TIN—THE USES OF TIN— SECONDARY TIN	I
--	---

CHAPTER II

SOURCES OF SUPPLY OF TIN ORES

(a) BRITISH EMPIRE :

<i>Europe</i> : United Kingdom	17
<i>Asia</i> : Ceylon, Hong Kong, India, Federated Malay States, Unfederated Malay States, Straits Settlements	29
<i>Africa</i> : Gold Coast, Nigeria, Nyasaland, Rho- desia, Union of South Africa, Swaziland	47
<i>America</i> : Canada	56
<i>Australasia</i> : Commonwealth of Australia, New Zealand	57

CONTENTS

CHAPTER II

SOURCES OF SUPPLY OF TIN ORES

(continued)

PAGE

(b) FOREIGN COUNTRIES

Europe : Austria-Hungary, France, Germany,
Holland, Italy, Portugal, Russia, Spain . . . 75

Asia : China, Dutch East Indies, Indo-China,
Japan, Siam 84

Africa : Belgian Congo, Portuguese East Africa,
South-west Africa 91

America : Bolivia, Other South American States,
Mexico, United States 93

REFERENCES TO LITERATURE ON TIN 100

TIN ORES

CHAPTER I

TIN ORES: THEIR OCCURRENCE, CHARACTERS, AND USES

THE British Empire is well supplied with workable deposits of tin ore, the total British output being between 50 and 60 per cent. of the world's supply. In early times and up to the eighteenth century Cornwall furnished the greater part of the world's output. About 1870 the rich alluvial deposits of the Malay Peninsula began to be worked on a large scale, followed in 1872 by the Australian deposits. The tin-mining areas of South Africa and Nigeria are of more recent development. India, too, produces a small amount. The chief foreign sources are Bolivia, the Dutch East Indies, Siam and China.

The chief centres of the smelting and refining of tin are in the Straits Settlements and the United Kingdom. Other important centres are those of the Dutch Indies, Germany, China and Australia. Before the war, smelting was carried on in Germany, but the industry has practically ceased there, and another result of the war is the establishment of a tin-smelting industry in the United States.

The greatest consumer of tin is the United States, which buys 40 per cent. or more of the world's output. This large consumption is to be attributed partly to the use of tin-plate cans in the preserved food, oil, and other industries, but still more to the employment of various tin-bearing alloys. Other consumers, taken in the order of their importance in pre-war days, are the United Kingdom, Germany, France, Australia, Austria-Hungary, Russia, Italy and Belgium.

The war had at first less effect on the supply of tin than on that of many other metals. The world's output had risen from about 95,000 tons in 1901 to a maximum of 134,000

tons in 1913. The loss of the German, Austrian and Belgian markets in 1914, together with diminished industrial requirements in other countries, led to a general reduction in output, whilst the increasing cost of production and difficulties of transport increased this downward tendency. The production in 1916 was about 122,000 tons, which is still greater than in any year prior to 1912. The large demands in America for tin in 1916 and the following years could with difficulty be met, and consequently the price rose to an unprecedented figure. In July 1914 the average price of tin in London was £142 10s. 4d. per ton; in the same month of each of the four following years it was £167 5s. 10d., £168 9s. 6d., £242 6s. 6d., and £359 17s. 9d. respectively.

THE ORES OF TIN

Cassiterite or *tinstone* is practically the only important ore of tin. It consists of tin oxide (SnO_2), with a theoretical metallic content of 78.6 per cent. Oxides of iron and tantalum are sometimes present in small amounts. The mineral has usually a deep brown to black colour, but it is sometimes red (*ruby tin*), yellow (*rosin tin*), and may even be colourless. It has an adamantine lustre, due to its very high refractive index (the mean value being 2.045). Its hardness is 6 or 7, and its specific gravity usually between 6.8 and 7.1. It crystallises in the tetragonal system, with prismatic habit and pyramidal terminations, and is often twinned. The varieties known as *sparable tin* and *needle tin* are characterised by an acute ditetragonal pyramid. A compact variety composed of radiating fibres, with concentric structure, is known as *wood tin*, and *toad's-eye tin* shows a similar structure on a smaller scale. *Stream tin* is water-worn cassiterite. It is found in alluvial deposits, while *float tin* occurs in the soil formed by the disintegration of stanniferous rocks. "Black tin" is a term frequently applied to concentrated tin ore.

Cassiterite occurs in lodes that are connected with granite intrusions, or more rarely the volcanic equivalents of granite. The lodes traverse both the granite and the surrounding rocks, and mark a late phase in the consolidation of the intrusion, when emanations of fluorine and boron altered the granite into greisen and formed minerals such as tourmaline, fluorite, topaz, lithia-mica, axinite and apatite, as well as quartz. A common associate of cassiterite is wolframite, together with the secondary minerals scheelite and stolzite.

Copper sulphides, arsenopyrite, pyrite, and ores of bismuth, uranium and iron, are also found in cassiterite lodes. The variety wood-tin, which only occurs in the upper part of tin lodes and in gravel deposits, is probably an alteration product of stannite. Cassiterite itself is a very stable mineral and survives indefinitely in detrital deposits.

Stannite is a sulphide of tin, copper and iron, containing 22 to 27 per cent. of tin, and frequently contains zinc. It is tetragonal but usually occurs massive, and is opaque, with a metallic lustre, and grey, black or bronze colour. It has a hardness of 4 and a specific gravity of 4.3 to 4.5. It occurs in veins associated with cassiterite, as in Cornwall, New South Wales and Tasmania, and is sometimes worked for both tin and copper.

Native tin is reported to occur as irregular rounded grains in some of the river gravels of New South Wales and elsewhere, but it is of no commercial importance.

The remaining stanniferous minerals are of scientific interest only. They include the sulphides canfieldite, cylindrite, franckeite, teallite and plumbostannite, the borates norden-skiöldite, hulsite and pageteite, and the silicate stokesite.

STATISTICS OF PRODUCTION OF TIN ORE

Reliable figures for the production of tin ore in the countries of the world are not easily obtainable. In some cases there are no official returns, in other cases these are several years in arrear. Again, some of the returns are in terms of tin ore, without the percentage of tin being stated, and in others only exports are given. Table 1 gives the most trustworthy figures indicating the amount of tin in the ores raised, these figures have been obtained or calculated from official or other returns available. (See also Diagram 1, p. 5.) The same applies to other similar tables throughout the Monograph.

VALUATION OF TIN ORE

Most of the Cornish ore is sold at the ticketings held fortnightly at Redruth. The smelters bid for the parcels of ore offered by the mines, having previously sampled and assayed the ore. The samples are taken from the wet ore, containing from 6 to 12 per cent. of moisture, and no allowance is made for variation in water content between sampling and delivery. In addition to an arbitrary deduction to cover the weight of the sacks in which the ore is delivered, the smelters are allowed

Table I
World's Output of Tin Ore (Tin Content)

In tons (c. 2,240 lb.)

	1913	1914	1915	1916	1917
<i>British Empire</i>					
United Kingdom	5,271	5,283	5,056	4,968	4,607
Australia	1,191	807	3,400	5,179	5,450
India	324	322	272	139	139
Federated Malay States	18,121	59,126	19,013	19,569	11,870
Unfederated Malay States	1,227	1,740	1,505	3,041	3,340
Nigeria	5,020	3,743	4,800	1,733	5,755
Union of South Africa	1,715	2,254	2,024	2,057	1,928
Swaziland	2,008	341	347	400	321
Straits Settlements	8	16	6	40	1
<i>Foreign Countries</i>					
Austria-Hungary	21	—	—	—	—
Bolivia	22,032	26,106	21,000	21,441	20,720
China	8,044	8,283	7,007	7,800	7,593
Dutch East Indies	10,012	20,500	17,003	19,323	19,518
Indo-China	68	159	61	—	—
Italy	52	—	—	—	—
Japan	195	—	—	—	—
Portugal	100	—	—	—	—
Siam	6,527	6,748	6,501	8,000	8,705
Spain	130	—	—	—	—
United States	70	61	93	91	125

to deduct 3 lb. for every hundredweight, so that 2,300 lb. must be delivered for every ton. The amount of tin contained in the ore is calculated from the dry assay of the sample, a returning charge of 1½ per cent (6½ per cent) is deducted, and the amount (in hundredweights) is multiplied by the tin standard, the product, or price payable by the smelter, being reckoned to the nearest half-crown. The unnecessary complications of this antiquated system of trading are obvious.

One of the Australian smelters before the war made a smelting charge of £3 per ton, with a deduction of 2 per cent. from the assay to cover loss in smelting. A larger deduction was made if the concentrate contained less than 70 per cent. tin. The smelting charges in the Straits Settlements were also about £2 10s. to £3 per ton of ore, the assay values being reduced by varying amounts according to the grade of the ore.

In the case of Nigerian concentrates the returning charge varies with the price of tin, and usually increases by 5s. per




DIAGRAM 1.— OUTPUT OF TIN ONE BY COUNTRIES, 1901-1916, EXPRESSED IN TERMS OF METALLIC TIN

ton for each unit below 70 per cent. down to 65 per cent., and decreases by 2s. 6d. per ton for each unit above 70 per cent.

A specimen contract for the delivery of Bolivian tin concentrates in Liverpool contains the following details as to payment. The price of tin on which the payment is based is the mean of the cash and three months' price of standard tin as quoted on the London Metal Exchange on the fourteen days following the steamer's reported arrival at Liverpool, averaged to the nearest five shillings. From the percentage of tin content as shown by assay the following deductions are made:

Table 2

Percentage of tin or over	Units deducted	Percentage of tin or over	Units deducted	Percentage of tin or over	Units deducted
74	2.00	67	2.95	60	4.00
73	2.125	66	3.10	59	4.15
72	2.25	65	3.25	58	4.30
71	2.375	64	3.40	57	4.45
70	2.50	63	3.55	56	4.60
69	2.625	62	3.70	55	4.75
68	2.750	61	3.85		

The percentage so obtained is multiplied by the agreed average price of tin and divided by 100. A returning charge of £6 is deducted for concentrates assaying 60 per cent. or over, and a further deduction of 2s. 6d. is made for each unit below 60, down to a minimum of 55 per cent. The total antimony, copper and bismuth content must not exceed 0.75 per cent., and 2s. 6d. is deducted for each 0.1 above 0.25 per cent.

THE PRICE OF TIN

Table 3 and Diagram 2 show the fluctuations in the price of tin in the years 1901 to 1918, while Table 4 and Diagram 3 show the average monthly price from January 1912 to December 1918.

Table 3

Average Price of Tin in London per ton (2,240 lb.)

	£	s	d		£	s	d		£	s	d
1901	118	12	8	1907	172	12	9	1913	201	14	0
1902	120	14	5	1908	132	2	6	1914	151	2	9
1903	127	6	5	1909	134	15	6	1915	164	4	0
1904	126	14	8	1910	155	0	2	1916	182	3	5
1905	143	1	8	1911	192	6	2	1917	237	13	3
1906	186	12	11	1912	209	8	5	1918	329	11	2





DIAGRAM 2.—BRITISH AND FOREIGN OUTPUT OF TIN ORE, 1901-1916, EXPRESSED AS TIN,
AND AVERAGE PRICE OF THE METAL IN LONDON, 1901-1918.



DIA RAM 3.—AVERAGE PRICE OF TIN IN LONDON, JANUARY TO DECEMBER
1912, 1913, 1914, 1915.

PRICE OF TIN

9

Table 4

Average Price of Tin in London per ton (2,240 lb.)

	1912.			1913.			1914			1915			1916.			1917.			1918.		
	£	s.	d.	£	s.	d.	£	s.	d.	£	s.	d.	£	s.	d.	£	s.	d.	£	s.	d.
Jan..	191	14	0	228	5	0	172	0	11	156	14	6	175	10	4	186	6	4	203	6	2
Feb..	195	4	10	220	6	3	181	12	0	156	14	6	181	3	4	168	10	3	311	12	3
Mar.	192	15	0	213	11	10	174	0	1	180	10	10	193	13	11	207	10	8	318	15	0
April	200	8	3	224	14	2	164	3	7	166	10	0	190	10	0	220	3	10	329	18	1
May.	209	6	1	224	14	3	150	19	3	162	18	6	190	11	9	245	2	10	364	7	8
June	205	18	9	204	9	1	148	16	2	167	17	3	179	11	3	242	7	7	334	10	0
July.	202	8	3	183	16	11	142	10	4	167	5	10	168	9	0	242	6	6	359	17	9
Aug.	208	3	0	188	19	0	*			151	12	10	160	10	0	243	18	8	380	16	8
Sept.	223	19	6	193	7	7	*			152	18	4	171	8	4	243	19	5	343	19	0
Oct.	228	9	1	185	0	3	*			151	16	2	179	8	2	247	9	4	335	10	0
Nov.	227	16	10	181	0	0	*			167	18	5	186	19	8	275	2	10	347	7	7
Dec..	226	17	8	171	18	11	147	4	4	167	3	10	183	9	1	298	10	3	267	14	3

* No quotation

Diagram 2, in which the price of tin has been plotted on the same diagram as the output of dressed tin ore in British and foreign countries, shows the close interdependence which exists between supply and price, and which cannot be disguised by the speculative character of the market. The output is given in greater detail in Diagram 1. In 1905-6 an increasing demand for tin, together with a diminished output in the Malay States and Banka, caused the price to rise; this stimulated the development of low-grade deposits in Australia and elsewhere, and caused an increased production, which by 1908 had overtaken the demand and brought down the price. Consumption continued to increase, however, and from 1908 to 1912 the price rose in spite of the increasing supplies from Bolivia, Banka and China. In 1913 and 1914 this increased production caused the price to fall, and the first fifteen months of the war saw a small demand, low price, and diminishing output. In 1916 and the following years, however, the American consumption grew to unprecedented proportions; the expense and difficulty of mining and shipping the ore under war conditions caused a further decline in production; and consequently prices rose to hitherto unknown figures.

High prices, as compared with those of 1914, are likely to rule for some time. To the large demands caused by industrial expansion in Allied countries after the war will be added those of Germany and Austria; and only gradually will it be possible to obtain the capital and machinery necessary for a large

increase in production. Until the supply more nearly equals the demand, high prices must prevail, and this will stimulate the exploitation of low-grade deposits which in 1914 would have been unremunerative.

THE PROPERTIES OF TIN

Tin has a silvery-white colour and a brilliant lustre. It has a crystalline structure, as may be seen when the surface has been slightly attacked by an acid (*moiré métallique*). To this crystalline structure may be attributed the low tensile strength of the metal, as well as the characteristic "cry" and the elevation of temperature produced by bending a bar of tin.

The atomic weight of tin is 118.7 and its specific gravity is 7.29 when cast. In commercial tin the latter often rises to 7.5, since the impurities commonly present have a higher specific gravity than tin. Tin melts at 232°C ., and boils at about $2,100^{\circ}\text{C}$., but is volatile at lower temperatures. Its specific heat is 0.056. It has a conductivity of 14.5 for heat and of 11.3 for electricity, that of silver being taken as 100 in each case. It is very malleable and ductile, especially at 100°C ., and can easily be rolled or beaten into foil. At a temperature of about 200°C ., however, pure tin is so brittle that it is readily shattered by a blow from a hammer. At low temperatures, and especially about -40°C ., tin tends to pass into an allotropic modification known as grey tin. This change is sometimes referred to as "tin pest," the tin being covered with small pustules of grey tin, which is an incoherent powder and has a lower density than the common white tin.

The best brands of commercial tin are remarkably pure, often containing less than 0.1 per cent. of other metals. Class A tin, which contains not less than 99.75 per cent. of tin, is taken as the standard with regard to price; Class B metal, with from 99.0 to 99.75 per cent. tin, is priced at £7 per ton lower. The former is used in tin-plate manufacture, where impurities give a duller and poorer coating, but Class B tin serves for the making of alloys.

The impurities usually present are copper, iron, lead, antimony, bismuth, tungsten, sulphur, arsenic and stannic oxide. These impurities tend to make the tin harder and less malleable, and also impair the brilliancy of its lustre. Table 5 gives the analyses of several commercial brands of tin, according to the London Metal Exchange.

Table 5
Analyses of Commercial Brands of Tin

	Tin	Anti- mony	Arsenic	Lead.	Bis- muth	Copper	Iron	Silver.	Sulphur.
Banka . . .	99.950	0.007	nil	trace	nil	0.018	0.015	nil	trace
Billiton . .	99.960	0.006	nil	nil	nil	0.023	nil	nil	nil
Penang . . .	99.939	trace	0.003	trace	nil	0.016	0.028	nil	0.004
Singapore. .	99.870	0.008	0.015	0.011	0.004	0.052	0.003	0.006	0.005
Mt. Bischoff .	99.795	0.015	0.003	0.037	0.005	0.035	0.012	trace	0.008
Pyrmont . .	99.938	0.017	0.019	trace	nil	0.022	trace	nil	0.004
Irvine Bank .	99.580	0.062	0.031	0.221	0.025	0.126	0.002	0.018	0.004
Williams, Harvey & Co., No. 1	99.860	0.015	0.010	0.004	0.005	0.017	0.003	nil	0.006
Do., No. 2 .	99.560	0.160	0.047	0.162	0.007	0.050	0.005	trace	0.013
Do., No. 2a .	99.350	0.245	0.065	0.223	0.015	0.042	0.016	trace	0.013
Do., No. 3 .	99.200	0.300	0.037	0.396	0.007	0.100	0.013	0.014	0.006
Do., No. 4 .	99.941	0.011	0.022	trace	0.001	0.020	trace	trace	0.005
Penpoll, No. 1	99.720	0.118	0.054	0.041	0.007	0.052	0.004	0.009	0.007
Do., No. 2 .	98.710	0.569	0.042	0.546	0.055	0.193	0.007	0.015	0.004
Do., No. 3 .	99.360	0.325	0.056	0.212	0.050	0.088	0.002	0.021	0.009
Redruth* . .	99.160	0.170	0.053	0.177	0.017	0.145	0.014	0.006	0.008
Th. Goldschmidt, No. 1 . . .	99.860	0.004	nil	0.102	nil	0.043	trace	nil	trace
Do., No. 2 .	99.460	0.015	nil	0.125	nil	0.069	trace	nil	trace
Do., No. 3 .	99.150	0.122	0.046	0.143	0.112	0.352	0.007	0.006	trace
Chinese, No. 1	99.343	0.031	0.040	0.434	0.007	0.052	0.010	trace	0.011
Wing Hong & Co., No. 2 . . .	98.662	0.039	0.035	1.035	0.012	0.144	0.014	trace	0.011
Do., No. 3 .	95.280	0.381	0.050	1.995	0.020	0.106	0.026	0.018	0.008

* Cobalt, 0.012 per cent.

USES OF TIN

Tin is rarely used alone, except in pipes for distilleries and in the form of tin-foil for wrapping purposes.

The most important use to which it is put is in the manufacture of tin-plate. The industry is centred chiefly in South Wales and the United States, and consists in applying a film of tin to the surface of thin sheets of mild steel. The sheets thus protected are made into "tins" or cans for the transport of preserved food, oil, and other commodities, or into cooking utensils, etc. The metal used for rolling into sheets was formerly charcoal iron, but very mild steel is now employed. The bars of steel are heated to redness, rolled, and folded in two. The rolling and doubling over are repeated until sheets of the required thickness are obtained, which are then cut to size and separated. The rough "black plates" thus produced are covered with a black scale of oxide, which is

removed by pickling them in warm dilute sulphuric or hydrochloric acid and then rubbing them with sand and water. They are then annealed, cold rolled, re-annealed, and again pickled, rubbed with sand, and swilled with water. While still wet they are passed through the tinning machine. This usually has two compartments, but the division does not reach to the bottom. The molten tin in the lower part is covered by a flux of zinc chloride in the first compartment and by melted grease in the second. The plates pass through the flux and down through the tin, emerging through the grease. They then pass through rolls which remove superfluous tin and give a smooth and bright surface.

Table 6
Pewter, Soft Solders, and Fusible Metals

	Tin	Lead	Bismuth	Cadmium	Melting Point.
Pewter, English	80	20			
" French	82	18			
Solder, for electric fittings	94	5			
" tin-smith's	66 2/3	33 1/3			171° C.
" plumber's	60	40			168°
"	50	50			188°
"	33 1/3	66 2/3			227°
" bismuth	10	40	20		143.5°
"	10	20	40		113.3°
" Bureau of Standard	10	80		10	183°
Fusible metal, Rose's	25	25	50		93°
" " Wood's	13	27	50	10	65° to 71°

Tin alloys readily with most metals. The alloys serve a variety of purposes, and account for the greater part of the world's tin consumption. In tin-plate a true alloy is formed at the junction of the tin and iron, and the same may be said in the case of copper vessels coated with tin. An alloy of lead and tin, containing 15 to 25 per cent. of tin, is used for coating iron sheets, which are then known as *terne plates* and used as a substitute for galvanised iron for roofing, oil-tanks, etc. Small amounts of tin are often added to the *spelter* used in galvanising iron, to improve the appearance. Pewter and solder are other familiar examples of tin-lead alloys. The lead in pewter used for drinking vessels, dishes, etc., must not exceed 20 per cent., or there will be a risk of lead poisoning. A little copper is sometimes added to increase the hardness

of pewter, but the colour is adversely affected by it. Tin-lead alloys are also used for organ-pipes. Solders vary widely in composition, according to the use for which they are intended. The melting point falls with increase of tin until the eutectic proportion is reached with 63 per cent. of tin. By the addition of bismuth still lower melting points are obtained, and the alloy passes into the so-called fusible metals.

The use of tin for hardening copper has been known from ancient times. About 5 per cent. tin is added to copper for coinage purposes, while ancient bronzes contain from 8 to 15 per cent. Gun metal contains 8 to 10 per cent. of tin, and has great strength and toughness. In bell metal the percentage varies from 16 to 25. Speculum metal for reflectors contains about 33 per cent. of tin and 67 per cent. of copper, though other alloys are now frequently used for the purpose. Gun metal, formerly used for casting cannon, is now employed in various parts of machines, such as gearings, slide-valves, bearings, etc. For these purposes phosphorus is advantageously added to act as a deoxidiser, and in excess to increase the hardness and resistance to wear. Such alloys are known as phosphor-bronze.

Table 7

Bronze, Gun Metal, etc.

	Tin	Copper	Zinc	Lead	Phosphorus
British bronze coinage	4	95	1	—	—
Gun metal	9	91	—	—	—
Bell metal	25	75	—	—	—
Speculum metal	33	67	—	—	—
Phosphor-bronze	10	89	—	—	1
Bronze bearing metal	8	77	—	15	—

Alloys of tin with antimony and one or more other metals are of great industrial importance. The white antifriction metals vary in composition according to the weight and speed of the load they are intended to bear. Britannia and similar silvery-white metals consist mainly of tin, while in type metal lead preponderates and tin is often omitted in the softer and cheaper qualities. Tin amalgam was formerly much used for making mirrors.

Table 8
Bearing Metal, Britannia Metal, and Type Metal

	Tin.	Antimony.	Copper.	Lead.	Bismuth.
Bearing metal, Babbitt's	90	7	3	—	—
" " for locomotives	82	14	4	—	—
" " soft	11.5	13.5	3	72	—
Britannia metal for spinning	94	5	1	—	—
" " " rolling	90	7	3	—	—
" " " casting	84	10	4	—	2
Queen's metal	75	8.5	—	8.5	8
Type metal	10	18	2	70	—
" " " "	7.5	14.5	—	78	—

Tin compounds are extensively used in the dyeing, calico-printing, and silk industries. The stannous salts have great reducing properties and are used as resists and discharges in printing. Stannic chloride, cotton spirits, or tin spirits (names given to a variety of solutions of tin) is largely used as a mordant for cotton and linen, as is also sodium stannate (preparing salts). For wool, stannous chloride (tin crystals) is usually employed. The weighting of silk also consumes large quantities of stannic chloride. Many other compounds, such as stannous nitrate, sulphocyanide, acetate, oxalate, citrate and tartrate, are also used as mordants in dyeing. The "pink salt" formerly employed by dyers consists of stannic chloride and ammonium chloride.

In ceramic industries stannic oxide is extensively used to form an opaque white in enamels, glazes and glassware. A blood-red glaze is produced by compounds of tin and chromium, while purple of Cassius is a compound of tin and gold.

Stannic sulphide is employed as a gilding material under the name of mosaic gold. Various pink, lilac, blue and green pigments contain tin, but they are of comparatively little importance.

A mixture of tin and lead oxides forms the putty powder used in polishing glass, stone and metal. Under the name of tin ash it is used also in the pottery industry.

The relative quantities of tin used in the United States for the different purposes enumerated above is shown in Table 9. The figures relate to a war year, 1917, and in other countries different proportions are probably allocated to the various industries. Chemicals (oxide, chloride, etc.) only account for 1,718 tons.

Table 9

Consumption of Tin in the United States in 1917 (tons)

Tin andterne plate	27,600	Collapsible tubes	2,100
Solder	17,000	White metal	1,704
Babbitt and other bearing metals	10,800	Miscellaneous	8,193
Brass and bronze	4,800		
Foil	1,000		
		TOTAL	70,257 tons

The recent scarcity of tin has led to investigations being made, especially in America, into the possibility of reducing the tin contents of various alloys in order to make the limited supply of the metal go farther. In the case of tin-plate, it was shown some years ago that while the lustre and resistance to rusting increase somewhat with increasing weights of coating, the utility of the tin-plate for packing most classes of food is practically the same for plate carrying from 1 to 3 lb. of tin per base box (112 sheets, 14 by 20 in.). Bronze bearing metal containing 65 per cent. copper, 30 lead, and 5 tin has been used with success, and in this alloy 2 or even 3 per cent. antimony may for some purposes be substituted for tin. Babbitt metals with only 5 per cent. tin, or even no tin at all, have been tested by the Bureau of Standards as well as aluminium and other bronzes. The Bureau recommends a solder containing 80 per cent. lead, 10 tin, and 10 cadmium.

SECONDARY TIN

The recovery of tin from clean scraps of tin-plate and from alloys and compounds containing tin yields considerable amounts of tin and tin compounds in this country and the United States. Only in Germany, however, has extensive use been made of old tin cans and other such refuse, but an attempt is now being made to utilise in this country the old tins that were formerly either wasted or sent to Germany as ships' ballast. In some cases the scrap is merely placed on grids and heated, when the molten tin falls to the bottom. The Bergse process employs stannic chloride as a solvent, which dissolves the tin and forms stannous chloride. This solution is electrolysed in a separate vat, when metallic tin is deposited and stannic chloride regenerated. In an electro-chemical process the tin-plate cuttings form the anode and a 10 per cent. solution of caustic soda is used as the electrolyte. Sodium

The tin ore imported is chiefly of Bolivian origin, and is shipped to this country from ports in Chile and Peru. The total imports from South American States rose from 22,542 tons in 1914 to 35,767 tons in 1915, when the Bolivian ore which formerly went to Germany was diverted to this country. In 1916 the amount had fallen approximately to normal at 24,587 tons, the excess ore being taken up by smelters in the United States and South America. Nigeria sends the whole of its output of tin ore to be smelted in this country, but the South African ore which formerly came here now goes almost entirely to the Straits Settlements. This change, though obviously accelerated by war conditions, had begun before the war, and its effects will doubtless continue in time of peace.

The greater part of the tin imported into the United Kingdom is smelted in the Straits Settlements. Australia, Hong Kong and the Dutch East Indies are the next largest contributors. The imports from the last-named country show an increase in 1915 and 1916, due to much of the tin that was formerly sent to Holland and Germany coming to this country.

Tables 12 and 13 give details of the imports of tin ore and tin in recent years.

The exports of tin ore and tin from the United Kingdom are shown in Tables 14 to 16. Small amounts of ore were re-exported, principally to Germany. In the five years preceding the war the United States took between 28,000 and 33,000 tons of tin annually, or about 70 per cent. of our exports. In 1915 the exports to the States fell to 17,610 tons, in 1916 they were 21,072 tons, and in 1917, 18,702 tons. This fall is largely due to high freights, much foreign and colonial tin that was formerly brought to this country for trans-shipment being now sent direct to its final destination.

The tin-plate exports also show a great decrease in quantity, though not in value, during the war years, having fallen from 494,497 tons in 1913 to 177,383 tons in 1917. The United States was formerly a large customer, but now that her own tin-plate output has increased to over a million tons a year she has begun to send it to this country, besides supplying much of the needs of Canada, South America, Japan, India, and other countries.

Cornwall, with the western part of Devon, was for centuries the most important tin-mining region in the world. The industry dates back to pre-historic times. In the sixteenth century the output of tin was about 700 tons a year, which

UNITED KINGDOM

19

Table 12
Imports of Tin Ore into the United Kingdom

In tons (2,240 lb)

Countries whence Imported	1910.	1911.	1912.	1913.	1914.	1915.	1916.	1917.
Australia	16	14	79	607	219	244	112	34
Nigeria	688	1,372	2,378	3,380	6,433	5,849	7,430	8,756
South Africa	3,339	5,157	5,211	889	574	1,456	54	54
Strait Settlements and Dependencies	10	6	4	91	28	23	16	25
Other British Possessions	13	7	80	278	148	166	388	21
Total from British Possessions	4,063	4,512	5,470	5,736	7,247	7,768	8,000	8,899
Germany	325	279	1,583	1,84	54	—	—	—
Netherlands	136	135	309	95	30	—	—	9
Belgium	45	54	76	115	70	—	—	—
France	82	882	839	1,183	618	183	221	78
Portugal	15	31	66	194	81	459	496	554
Spain	123	154	277	697	379	348	252	49
United States	72	222	243	105	67	15	75	2
Bolivia and other South American States	19,682	21,439	21,885	24,202	22,512	45,767	24,887	31,319
Total from Foreign Countries	497	388	180	491	243	241	281	307
Total from Foreign Countries	22,009	21,825	25,210	25,556	24,65	36,980	25,912	32,318
Total	26,072	28,237	28,682	31,592	32,308	44,748	33,912	41,208
Value	£ 1,820,782	£ 2,306,334	£ 2,100,880	£ 3,328,953	£ 2,921,413	£ 3,777,711	£ 3,159,022	£ 4,710,934

SOURCES OF SUPPLY OF TIN ORES

Table 13
Imports of Tin into the United Kingdom

In tons (2,240 lb.)

Countries whence imported.	1919	1921	1922	1923	1924	1925	1926	1927.
Australia	3,872	3,571	3,241	2,251	1,403	2,372	2,657	323
India	51	—	—	137	—	5	6	1
Hong Kong	—	—	—	—	—	—	—	—
Straits Settlements and Depen- dencies	45	1,117	1,532	92	1,009	1,294	1,176	853
Other British Possessions	4,064	86,094	30,759	4,333	3,333	3,233	25,612	25,571
	59	—	—	5	—	5	—	—
Total from British Possessions	44,000	14,770	4,844	33,773	10,736	33,376	29,311	26,748
Germany	42	141	22	—	31	—	—	—
Netherlands	13	181	50	—	21	—	—	—
France	20	64	30	—	5	—	—	—
Dutch East Indies	4	138	1,241	1,011	324	3,781	4,206	277
China	5	180	28	37	4	194	—	—
United States	202	440	—	200	—	10	8	—
Bolivia	943	369	511	87	354	47	—	116
Other Foreign Countries	6	12	45	19	78	65	31	2
Total from Foreign Countries	1,294	1,517	2,313	2,299	775	4,520	4,375	395
Total	46,285	45,966	43,157	45,982	40,961	38,896	33,616	27,143
Value	£ 7,159,782	£ 8,739,469	£ 8,975,144	£ 9,552,004	£ 6,339,145	£ 6,304,546	£ 6,149,490	£ 6,198,243

UNITED KINGDOM

Table 14
Exports of Tin Ore (Foreign and Colonial) from the United Kingdom
In tons (2,240 lb.)

Countries to which Exported	1910.	1911.	1912.	1913.	1914.	1915.	1916.	1917.
Straits Settlements								
Other British Possessions	69	—	—	—	—	214	813	—
Total to British Possessions	69	—	—	—	—	214	813	—
Germany							224	—
Belgium	2,499	3,916	2,272	2,198	2,423	—	—	—
France	141	98	579	431	343	—	—	—
Austria-Hungary	—	65	421	253	19	—	—	—
Other Foreign Countries	—	230	316	329	3	—	—	—
Total to Foreign Countries	2,640	4,211	3,598	3,508	2,445	—	—	—
Total	2,709	4,281	3,598	3,508	2,463	216	—	—
Value	182,122	314,137	3,297,774	314,479	219,742	15,669	74,276	23

Table 15
Exports of British Tin from the United Kingdom
In tons (2,240 lb.)

Countries to which Exported	1910.	1911.	1912.	1913.	1914.	1915.	1916.	1917.
Canada	—	—	—	—	—	—	—	—
Egypt ¹	887	1,02	952	847	712	927	959	1,136
India	—	—	—	—	—	21	214	283
South Africa	158	157	230	327	112	214	69	29
Other British Possessions	111	117	211	173	12	228	337	187
Total to British Possessions	142	129	116	169	166	74	84	77
Total to Foreign Countries	1,298	1,405	1,592	1,459	1,292	1,664	1,654	1,712

¹ Under this heading is included tin which had been imported from abroad, but which was refined at the smelting works in England and was accordingly declared by the exporters as British tin. ² Included in Foreign Countries prior to 1915.

SOURCES OF SUPPLY OF TIN ORES

Table 15 (continued).
Exports of British Tin from the United Kingdom

In tons of 2,240 lb.

Countries to which Exported	1910	1911	1912	1913	1914	1915	1916	1917.
Russia	11.5	1.26	1.17	1.15	2.24	1.65	1.67	47.13
Sweden	5.68	9.14	9.5	6.92	2.27	1.80	8.10	133
Norway	1.4	1.3	1.1	1	1.5	1.6	1.67	34
Denmark	2.3	2.9	2.8	2.7	2.1	2.2	2.55	175
Germany	2.22	2.19	1.59	1.7	2.1	1.7	1	1
Netherlands	2.9	1	1.2	1.2	1.72	1.7	1	1
Belgium	5.7	4.1	2.2	2.5	1.37	2.8	3.70	2,585
France	1.9	1.39	1.19	2.1	1.15	2.58	1.53	400
Portugal	1.91	4.12	4.1	4.2	2.6	2.8	6.28	538
Spain	4.2	1.1	4.2	4.1	1.7	5.95	3.24	287
Italy	1.79	1.9	3.3	3	2.7	5.11	—	—
Bulgaria	0.3	0.3	0.3	0.4	0.4	0.4	3 ¹	25 ¹
Turkey	2.88	2.5	2.5	2.1	2.6	2.1	—	—
Egypt ²	1.76	1.2	1.2	1.5	1.6	2.13	6.03	6,903
United States	4.12	3.97	1.55	4	1.6	1.5	3.1	25
Chile	5.7	5.1	5.8	8.2	7.4	1.7	2.5	146
Brazil	2.55	1.7	2.2	2.2	2.1	1.2	0.55	1,305
Argentine Republic	5.21	4.9	3.52	3.1	2.4	1.2	—	—
Other Foreign Countries	9.3	1.3	3.3	1	1.5	1.8	5.97	213
Total to Foreign Countries	117.70	1.90	1.17	1.57	12.97	12.53	16.368	17,553
Total	12.377	41.594	11.928	11.513	15.393	14.167	18.024	419,205
Value	1,809,075	2,171,783	2,533,353	2,433,705	2,690,211	2,338,757	3,254,124	4,224,594

¹ Exported to ports or places in territory formerly Turkish but now occupied by other Powers, e.g. Crete, Dedegatch, Salonika, etc.; ² Including Anglo-Egyptian Sudan prior to 1914.

UNITED KINGDOM

23

Table 16
Exports of Tin (Foreign and Colonial) from the United Kingdom
In tons (2,240 lb.)

Countries to which Exported	1910	1911	1912	1913	1914	1915	1916	1917.
Canada	12	3	5	1	5	155	523	469
Other British Possessions	3	—	2	122	33	27	—	6
Total to British Possessions	15	3	7	132	38	182	530	475
Russia	441	35	561	338	631	2,698	20	178
Sweden	—	3	5	—	59	1,571	126	10
Norway	—	—	2	—	—	422	—	11
Germany	287	950	1,262	1,351	1,975	—	—	—
Netherlands	1,679	3,189	3,022	3,139	2,075	1,628	—	—
France	4	132	244	62	215	271	598	2,377
Spain	105	127	94	8	18	397	297	445
Italy	326	3	49	—	73	1,777	213	1,307
United States	28,115	29,092	27,224	25,665	24,167	13,093	16,939	11,889
Other Foreign Countries	211	212	270	23	233	512	750	1,432
Total to Foreign Countries	31,524	33,995	35,760	30,114	30,75	23,182	16,994	17,649
Total	31,539	34,25	35,728	30,136	30,713	23,364	17,494	18,124
Value	4,877,271	6,429,545	6,753,517	6,147,101	4,750,912	3,932,385	3,236,798	4,005,874

increased to 2,000 or 3,000 tons in the eighteenth century. Between 1860 and 1890 it reached nearly 10,000 tons a year, but receded to about 4,000 tons in 1899. As recently as 1870 Cornwall produced 50 per cent. or more of the world's output, whereas it now produces only about 4 per cent. The total amount of tin which has been produced from Cornish ore is estimated at about 1,500,000 to 2,000,000 tons, a figure only exceeded by one other region. The Malay Peninsula, including Banka and Billiton, produced about 2,300,000 tons of tin down to 1916, Australia and Bolivia each about 300,000 tons, whilst the lodes of Saxony and Bohemia, which are now practically exhausted, have yielded little more than 100,000 tons.

The tin and copper deposits of Cornwall and Devon are connected with five large masses of granite, and some smaller ones, which are intrusive in sedimentary rocks and associated igneous rocks known as "greenstones." The sediments are for the most part slaty in character and are called "killas." In age they are partly Ordovician (or older), partly Devonian and Carboniferous, while the granite intrusions are either late Carboniferous or Permian.

Closely connected with the granite intrusions are numerous "elvans," or dykes of quartz-porphry, while the last phase of igneous activity was marked by the emanation of metalliferous vapours and solutions through fissures which traversed the granite and overlying killas. This gave rise to the tin-copper lodes, with their dominant east-north-east strike. The lead-silver lodes which traverse the killas in a north and south direction appear to be of later date.

The lodes and elvans are for the most part crowded together at one side of the granite intrusion, near its margin or in the surrounding metamorphic aureole. This appears to be due to excessive disturbance of the sedimentary rocks on one side of the intrusive mass. To the same cause may be attributed differences in the structure of the lodes. In the principal centres they consist of wide zones of fissured rocks, with frequent breccias and crushed material; while the outlying lodes consist of clean cracks or joints of remarkable straightness.

The chief ores found in the lodes are cassiterite, with some stannite; chalcopyrite, bornite and chalcocite; wolframite and scheelite. Less important are galena, tetrahedrite, silver ores, zinc-blende, bismuthinite, molybdenite, cobalt and nickel ores, pitchblende (uraninite), manganese and iron ores.

Professor Cronshaw, who has made a detailed examination of a number of lodes at various depths, contributes the following

note, embodying his conclusions on the time-order of deposition of the lode contents :—

“ The mineral contents show a definite arrangement within the lode fissures, and, moreover, display well-defined mutual relationships. This definite arrangement is the outcome of a definite order of intrusion, which, for the Camborne district—and it very probably admits of wider application—has been found to be as follows :—

- I. Large grained and considerably brecciated quartz
- II. Small grained quartz, cassiterite, tourmaline, and chlorite.
- III. (a) Brown, finely crystallised tourmaline and chlorite, or ‘ brown peach,’ with minute grains of cassiterite and a certain amount of arsenopyrite.
(b) ‘ Blue peach,’ with cassiterite, and some arsenopyrite
- IV. (a) Fluorspar, and to a less extent, secondary quartz veins containing a little copper pyrites and occasional re-crystallised cassiterite.
(b) Calcite veins
(c) Veins of hematite, iron pyrites, quartz, etc.
(d) Veins of galena, zinc-blende, quartz and copper pyrites.

The bulk of the cassiterite made its appearance at stage III (a).

“ The several stages were separated by intervals, towards the end of which movements re-opened the lodes, preparatory to an infiltration and deposition of additional material. The amounts of the various mineral associations deposited in the lodes at each stage differ in every case, as also the extent to which fissuring took place during each interval. Thus some lodes are characterised by the predominance of certain minerals, or associations of minerals, and likewise a certain amount of variation in character of mineral constituents takes place from point to point within one and the same lode. The commonly observed preference of copper ores for the upper parts of the lodes is probably due to the fact that the latest movements which were connected with the mineralising operations would be more likely to affect those portions of the lodes which lay within the killas than the portions situated

in the more resistant masses of granite, and the ores of copper, which were amongst the latest to arrive, would find in this zone the open spaces required for their deposition.

"The later cross-courses intersect and fault the tin-copper lodes so that their directions of strike are roughly at right-angles to one another. The cross-courses do not contain tin, but in some cases they have yielded ores of lead, zinc and silver.

"*Camborne and Land's End Areas* - Geographically considered the lodes of south-west Cornwall show certain peculiarities in their distribution. In the Land's End area they are gathered into isolated groups, either within the granite or immediately outside its margin; in the Camborne and Redruth districts they are packed into the narrow belt of metamorphosed shales lying along the flanks of the Carn Breca and Carn Marth granite intrusions, whilst the intervening country occupied by a broad tract of killas, is characterised by a more general distribution. These features, when considered in conjunction with the geological structure of the region, lead to the important observation that the more important ore-bodies are generally situated at or near the junctions between granite and killas. The apparently anomalous cases of lodes occurring within tracts of killas and granite still conform to the general rule, for, in the former case, the killas is underlain at no great depth by granite, and, in the latter case, lodes situated within the outcrop of granite no doubt represent the roots of eroded, and formerly more extensive, bodies. That the fissuring was far from being general is shown by the absence of valuable ore-deposits from the lower half of the Land's End mass, as also from the metamorphosed margin above Penzance, and the zone of alteration surrounding the large granite boss of Carnmenellis.

"Another factor which seems to have an important influence upon the distribution of the ores is the angle at which the surface of the granite slopes beneath the killas. Where this is high the zone of metamorphism is narrow, and the mineral deposits are sparingly developed; on the other hand, the richest and largest deposits have generally been found where the slope is gentle.

"In many cases the passing of a lode from killas into granite has effected an important change in the value and

nature of its contents. It has long been observed that, generally speaking, the lodes in the granite are richest in tin, those in killas most productive of copper, whilst in those at or near the junction of the two rocks, both tin and copper are found. Many lodes of the latter type furnish good instances of the variation in the proportions of tin to copper with change of depth, and as a general rule it is found that in the upper parts of such lodes copper ores are dominant, whilst in depth and within the granite they give place to rich deposits of tin.

"The general distribution of the individual lodes is more conveniently considered when they are grouped into zones. This is rendered possible by the fact that, as a rule, they occur in groups of more or less closely packed and parallel individuals, which branch, intersect, and display a generally complicated structure and arrangement. It is along these lode-zones that the principal mines are arranged. The country rock between these zones has suffered only a relatively small amount of mineralisation. The individual members display many irregularities. In strike they are roughly parallel to one another, averaging about E. 30° N., and their general dip is high and towards the north. They intersect one another, branch and unite, die out or 'make' in the directions of dip and strike, and send out subsidiary offshoots. They vary in width from point to point, and in the amount and direction of their inclination. Again they 'mineralise' portions of the surrounding country rock by sending out fine offshoots."

In the west of Cornwall are the two mining centres of St. Just and St. Ives, both at the northern margin of the Land's End granite mass. In the St. Just district many of the mines are situated on the cliffs, and follow the ore for long distances beneath the sea. Much of the ore is confined to narrow fissures and, at the junction of these, nearly horizontal sheets or "floors" of tin ore often occur. The principal mines of this district are the Levant and Botallack mines. Of the St. Ives mines, St. Ives Consols is the most interesting, by reason of its irregular pipe-like deposits of tin ore known as "carbonas." The great carbona appears to have been formed at the junction of veins with a cross-course; it had an average height of 24 feet and width of 12 feet, though in places its dimensions were much greater, and it consisted of tourmaline, cassiterite, chlorite, fluorite, chalcopyrite and pyrite.

In the Camborne and Redruth district the primary zoning of the ores is well shown, many of the lodes being rich in copper ore while in the killas, on entering the granite the copper gives place to tin. Thus at Dolcoath, the richest as well as the deepest mine in Cornwall, copper ore prevailed to a depth of about 1,000 feet, below which tin ore was found.

Most of the lodes connected with the St. Austell granite are in the metamorphic aureole on the south side of the intrusion. In the granite they are clean cracks or joints, filled with quartz, cassiterite and wolframite, while in the killas they often contain much brecciated country rock, or consist of numerous small parallel cracks, sometimes with intersecting cracks constituting stockworks. At Park of Mines a peculiar structure occurs, most of the tin ore being in opened planes of parting in the killas through which the veins cut.

The Bodmin Moor granite intrusion has metalliferous lodes near its south-eastern margin, but they have yielded more copper than tin.

The lodes of Devonshire are chiefly in the neighbourhood of Tavistock, on the west side of the Dartmoor granite, and Ashburton on the east side of that intrusion. Most of them are in the killas, and copper ores are more abundant than tin ores.

The relative importance as sources of tin of these five great granite intrusions is shown by the following table, giving the approximate percentage of the total annual output produced by each intrusion and its surrounding rocks in recent years:—

	Per cent of total output.
Land's End granite	12
Camborne granite	85
St. Austell granite	1
Bodmin Moor granite	1
Dartmoor granite	1

The working of alluvial deposits, or "tin streaming," is an older industry than lode mining, and most of the deposits have been worked over and over again till practically exhausted. The St. Austell district is particularly famous for its tin-bearing alluvial deposits. At the old Happy Union Streamwork a Pentewan the tin ore was confined to 3 to 10 feet of gravel resting on bedrock beneath some 50 feet of barren sand and silt, and about 50 feet below sea-level. In the high-level

alluvial flats or "moors," such as Goss Moor and Red Moor, which have been worked successfully in the last few years, the tin-gravel rests on solid rock and varies from a few inches up to 30 feet. It is covered by layers of peat, gravel, sand and clay to a thickness of 20 feet. The richest ground occurs in erosion channels and hollows in the solid rock, and has sometimes yielded several per cent. of black tin. All the tin-gravels appear to be the results of the natural concentration of the heavier material brought down during a period of exceptional erosion when the land stood at a higher level than now. The output of black tin from these alluvial deposits in 1914 was 91 tons, chiefly from the "moors" in the St. Austell district.

There are also similar works which treat the refuse sand and mud discharged from tin-dressing floors into streams and rivers. Several such works are situated on the Red River, which runs from the Camborne mines into St. Ives Bay. In spite of their activity much tin ore has reached the sea, where it has been concentrated by wave action on the foreshore of the bay. The output of black tin from these sources in 1917 was 954 tons, but its average tin content was only 32.7 per cent. against 65.6 per cent. in the case of ordinary ores.

Old mine dumps contain material that was formerly thrown aside, but which may become worth treating through an increase in the price of tin or improved methods of treatment. This source yielded 350 tons of black tin in 1917.

Outside Cornwall and Devonshire there are no tin deposits of economic importance in the British Isles. Stream tin occurs, however, together with magnetite, wolframite and gold, in some of the valley gravels of County Wicklow. There is also a peculiar occurrence at Carn Chuinneag, Ross-shire, of cassiterite associated with streaks of magnetite in foliated granite-gneiss.

ASIA

CEYLON.—Cassiterite has been found in gem gravels from the Balangoda area examined at the Imperial Institute, and some of the concentrates from river sands also contain small amounts of the mineral. No deposits of economic importance have yet been discovered.

HONG KONG.—In the Kowloon territory there are tin-bearing alluvial deposits, and steps were being taken before the war to

work them. The source of the tin is probably connected with the granite, which has hitherto provided almost the sole mining industry of the Colony.

Hong Kong has a considerable industry in refining the crude tin produced in Yunnan and other parts of China. There are five refineries, and the imports of unrefined tin from Yunnan amounted to 6,153 tons in 1913 and 6,741 tons in 1914.

INDIA.—The tin ore production of India is still small, though its value has increased from £9,645 in 1909 to £94,495 in 1917. South Burma was till recently the chief source, but the Southern Shan States have produced increasing amounts of ore since 1912. The output in recent years is as follows:—

Table 17
Output of Tin and Ore in India

In tons (2,240 lb)

	1912	1913	1914.	1915	1916	1917.
<i>Burma :</i>						
Mergui, metal .	137.8	110.8	98.15	127.675	112.86	140.895
.. ore .	113.05	85.85	93.05	88.113	91.85	88.05
Tavoy, metal .	62.0	65.7	—	0.013	—	—
.. ore .	1.5	1.05	38.35	12.05	82.2	88.1
Southern Shan States, ore .	60.1*	83.75*	138.35*	330.605*	243.1	404.4
Thaton ore .	—	—	—	—	45	83.85
Amherst, ore .	—	—	—	—	0.5	1.65
<i>Bihar and Orissa :</i>						
Hazaribagh, metal .	—	—	0.05	0.035	—	—
Total, metal .	200.7	182.5	98.2	127.74	112.86	140.895
.. ore .	174.05	120.95	260.75	431.158	105.65	666.05
Total value £	50,914	40,384	38,203	51,980	59,104	94,495

* Mixed cassiterite-wolframite concentrates.

The ore is obtained chiefly from stream deposits. Some of it is smelted locally in small native furnaces, and the rest is exported in the form of 70 per cent. concentrates, mainly to the Straits Settlements. Table 18 shows the destination of the tin ore exported, and Table 19 the source of the imported tin. The consumption of foreign tin in India amounts to about 1,700 tons in normal years, and tin-plate is imported to the extent of 40,000 to 50,000 tons a year.

Table 18

Exports of Tin Ore from British India in the years ending 31st March, 1911-1917

In tons (2,240 lb.)

Countries to which consigned.	1910-11	1911-12	1912-13	1913-14	1914-15	1915-16	1916-17.
United Kingdom.	19	9	35	38	28	9	12
Straits Settlements	101	100	178	197	86	78	202
Other countries	-	16	1	5	1	-	-
Total . Tons	120	134	214	240	115	87	214
Value . £	10,260	13,198	20,927	24,373	12,034	8,815	23,448

Table 19

Imports of Uncrushed Tin into British India in the years ending 31st March, 1911-1917

In cwt. (112 lb.)

Countries from which consigned	1910-11	1911-12	1912-13	1913-14	1914-15	1915-16	1916-17.
United Kingdom.	2,868	3,526	4,800	4,155	4,426	2,522	1,422
Straits Settlements	33,212	39,363	29,615	32,104	33,082	25,158	25,501
Other British Possessions	95	103	48	52	107*	376*	733*
Foreign countries	180	2,329	43	92	202	305	309
Total . cwt.	36,355	39,321	34,536	36,403	37,817	28,361	27,965
Value . £	295,455	349,291	335,733	323,282	311,607	213,521	259,003

* Chiefly Federated Malay States

The tin deposits of Burma form a link between the great tin fields of the Malay Peninsula to the south and those of Yunnan in China to the north. As in Malaya, the greater part of the ore is won from alluvial deposits, though the working of lodes has also begun. In most cases work is carried on only on a small scale and by native methods; and the output might be greatly increased by the extended use of modern machinery.

In the extreme south of Burma, the tin-mining areas of the Mergui district have been examined by Mr. J. J. A. Page, of the Geological Survey of India. Granite ranges, trending north and south, are flanked by hills formed of unfossiliferous

schists, slates, sandstones and quartzites. These sedimentary rocks constitute the Mergui series, but their age is unknown. The granite is in part gneissoid, and there is also a younger granite which is intrusive in the gneissic granite and the sedimentary rocks. Dykes of quartz-porphyry also penetrate the granites and sedimentaries. Decomposition products and recent alluvial deposits, together with a thick growth of jungle, conceal the rocks over large areas and add to the difficulties of exploratory work.

Cassiterite is widely distributed throughout the district, and is invariably found near the granite hills. It occurs in pegmatites, rich in tourmaline and muscovite, locally known as *kra*, and in veins and massive segregations of quartz. The disintegration of these rocks produces the hill-side talus accumulations and stream deposits which are usually worked by the Chinese and Siamese tin-miners. Among the tin-mining areas on the mainland may be mentioned Maliwun, Karanthuri, Yaungwa, Bökpyin, Yengan, Manoron, Mergui, Thabalik and the Great Tenasserim valley. In the Mergui Archipelago cassiterite has been worked in the gravels of King's Island, and also occurs in Kissering and Davies Islands.

Farther north, tin ore is obtained in small amounts in the Tavoy district, but it is overshadowed by the important wolfram mining industry of that district, which in 1917 yielded 3,697 tons of ore. The granite and sedimentary rocks of the Mergui series are here traversed by pegmatite and quartz veins, which contain cassiterite and wolframite in varying proportions. Cassiterite is relatively more abundant in the lodes which traverse the granite, and these are frequently bordered by tin- and tungsten-bearing greisens. The granite itself is stanniferous in places. From these sources are derived the float and alluvial deposits which yield the bulk of the ore won. The Amherst district, north of Tavoy, produced a small amount of tin ore in 1916.

The Thaton district of Lower Burma also began producing in 1916. The tin-bearing alluvium is said to be rich and extensive, and a considerable output is anticipated.

The Bawlake State, Karenni, Southern Shan States, began with an output of 60 tons of ore in 1912. In 1917 it had increased to 404 tons, and the district is now the chief producer of tin ore in India.

In the Hazaribagh district of Chota Nagpur, Bengal, tin has been found from time to time in river sands by the native iron-smelters. There are two known occurrences of the ore

in situ, at Nurunga and Chappatand, and the ore occurs in a cassiterite-granulite which sometimes contains as much as 30 to 50 per cent. of tinstone. This rock has been opened up to a small extent at Nurunga, where it forms a thin band in a mass of microcline-granulite.

Isolated crystals of cassiterite have been found associated with gadolinite in pegmatite in the Palanpur State, and the mineral is known to occur in several other localities.

FEDERATED MALAY STATES.—The Federated Malay States are the largest producers of tin ore in the world. Moreover, owing to the great preponderance of alluvial over lode ore, the resulting metal is of exceptionally good quality, and consequently "Straits tin" commands high prices. Most of the ore is exported to the Straits Settlements for smelting, though some is smelted locally, principally in Perak and Selangor. The amount smelted before export is shown in the following table, which gives the exports from the four Federated States expressed as metallic tin:—

Table 20

Tin in Ore and Metal Exported from the Federated Malay States

In tons (2,240 lb)

	1912	1913	1914	1915	1916	1917
Negri Sembilan.	1,731	1,884	1,697	1,244	907	734
Pabang . . .	3,082	3,133	3,085	3,808	3,480	3,496
Perak . . .	28,407	29,493	28,557	27,776	27,242	24,643
Selangor . . .	15,201	15,406	15,103	13,038	12,241	10,660
Total . . .	48,421	50,126	49,042	46,766	43,870	39,833
Exported—						
as block tin .	10,404	5,080	3,612	4,369	4,777	5,415
as tin in ore .	38,017	45,037	45,430	42,397	39,093	34,418
Total value £	9,803,694	9,782,598	7,087,418	7,176,054	7,526,566	8,480,610

These export figures do not give a true idea of the relative production of tin in the four States, owing to a certain amount of inter-State trade in the ore. Thus a considerable proportion of the ore raised in Negri Sembilan is included in the exports from Selangor. Allowing for such inter-State trade, the estimated production of tin for each State in 1917 is as follows:—

Table 21

	Tons (2,240 lb.)
Negri Sembilan	1,038
Pahang	3,691
Perak	24,678
Selangor	10,426
Total	<u>39,833</u>

The decrease in the exports, which has become more pronounced in each year since 1913, may be in part accounted for by the war. Another and more permanent reason is that a large number of Chinese coolies have left the tin mines to take up work on the rubber estates, whilst others have migrated to Kedah and Siam. It is probable too that the area of rich tin-bearing ground suitable for Chinese methods of working is becoming reduced; and the capital necessary for modern hydraulic operations has, like the labour, been diverted to rubber plantations.

A brief account of the geology and general mining conditions of the Malay Peninsula will be given, before dealing with the four States separately. The Main Range, which forms the principal watershed of the Peninsula, consists of granite apparently of Mesozoic age. On the west side of the Main Range offshoots of the granite form hills in Province Wellesley and Penang, in the Bidadaris, to the east of the Larut district, and in the Kledang Range in Perak. The oldest sedimentary rock above the granite is a crystalline limestone; then follow in upward succession clays, shales, quartzites and conglomerates of Gondwana (Permo-Carboniferous) age, and finally recent alluvium. All these rocks contain tinstone, either detrital or deposited in them by pneumatolytic action at the time of the granite intrusion. An interesting series of stanniferous clays and boulder clays is believed by Mr. J. B. Scrivenor, the Government Geologist, to be a glacial deposit of Gondwana age, and to contain detrital tinstone. This theory requires an earlier pneumatolytic phase than that connected with the Mesozoic granite. Many miners and others prefer the old view that the clays and boulder clays (the Gopeng Beds of Scrivenor) are really recent alluvial deposits or alteration products.

In Pahang, the eastern foothills of the Main Range are formed of quartzites, conglomerates and shales. Further to the east lies the Benom Range, which is composed of horn-

blende granite, and still further east is a broad belt of the Gondwana rocks, together with rocks of volcanic origin.

The powerful action of the ground-water, under tropical conditions, reduces hard rocks to a soft condition for a considerable depth below the surface. In this way what were once quartzites, phyllites or granites may now be easily cut by hand, or washed away by a monitor, and their ore content, which might otherwise have been unobtainable except at prohibitive cost, can be won at comparatively little expense. Consequently alluvial methods of working are widely employed on deposits other than alluvium. Lode mining in hard rocks furnishes only a small, though increasing, proportion of the ore won.

Associated with detrital tin ore in the crude concentrates there are other heavy minerals, including ilmenite, magnetite, wolframite, zircon, rutile, garnet, tourmaline, topaz, corundum, monazite, xenotime, andalusite, tremolite, hematite, limonite, pyrite, arsenopyrite, chalybite, anatase, brookite, scheelite, galena, native copper, columbite, and struverite. The heavy minerals left after the removal of the cassiterite constitute what is known as *amang*. Several samples of amangs, and of minerals isolated from them, have been examined at the Imperial Institute (see *Bull. Imp. Inst.*, 1906, 4, 301; 1908, 6, 155; 1911, 9, 354; and 1913, 11, 243).

Chinese miners were the pioneers of the Malay tin industry, and about 75 per cent. of the ore still comes from mines owned and managed by Chinese. Their methods vary according to circumstances. In the granite they burrow beneath the masses of residual boulders in the valleys for the pay-dirt (*karang*) which lies below. Patches of hill-side drift are hoed into a ground-sluice or *lampan*. On larger properties the deposit is worked opencast (*lumbong*), and the *karang* is carried in baskets to the sluice boxes. Mining by shaft and galleries is sometimes adopted. In many cases, after the Chinese have thus picked out the eyes, the deposit may still be profitably worked by hydraulic means. Gravel-pump dredges have proved as successful here as in Australia, particularly in the western States, which are more developed and better provided with roads than is Pahang.

The ore smelted locally is treated in small Chinese furnaces, about 4 feet high and 2 feet in diameter. They are built of clay and held together by iron bands, while a piston worked by hand in a hollow tree-trunk supplies the blast. Wood and charcoal are used, but no flux.

Tin mining is somewhat heavily taxed by means of an export duty on tin and tin ore. The duty is on a sliding scale, and varies with the price of tin. With tin at £150 a ton it works out at about 13 per cent. of the value of the tin content, which was taken to be 70 per cent. of the weight of the ore until 1917, when the percentage was raised to 72 for purposes of assessment. A rebate is allowed in the case of ore from lodes which require blasting or crushing. An additional and prohibitive duty of \$30 per pikul (£58 16s. per ton) is charged on any ore exported without a guarantee that it will be smelted in the Straits Settlements, the United Kingdom, or Australia. The tin duty is an important source of revenue to the Government, and amounted to £1,265,847 in the record year 1912.

Negri Sembilan.—In Jelebu three lodes are worked at Titi. Hydraulic methods were employed till recently, when difficulties in regard to the disposal of tailings led to their temporary abandonment. In this mine, as in many others in Negri Sembilan, a mixed cassiterite and wolframite concentrate is obtained, and the minerals are separated electro-magnetically. In 1914 the mine yielded 494 tons of tin ore and 95 tons of wolfram ore. The Triang and the Kenaboi rivers also yield tin ore.

In the neighbourhood of Seremban decomposed pegmatites with stanniferous quartz veins are worked by hydraulic methods. Kuala Pilah, Pantat, Rasa, Chukong, Gebok and Lukut may also be mentioned.

Pahang.—The country to the east of the Main Range is not so rich in tin ore as that to the west. There are, however, alluvial workings near the western boundary of Pahang (Bentong, Tras, Machi), and also in the east, in the Blat (Belat) valley in the Kuantan district. Lode mining is carried on near the headwaters of the Kuantan river.

The Machi tin field lies to the south of Bentong. The deposit is alluvial, and generally not more than 12 feet thick. The cassiterite is angular and varies so much in grain that a large proportion is lost by the crude Chinese method of dressing it. Small lodes exist in the locality. One of these was found to contain quartz, yellow garnet, cassiterite, zinc-blende, arsenopyrite, and pyroxene.

The alluvial flats at Bentong have been worked for tin, but at present the work is confined to the higher valleys of the Main Range, on the boundary of Pahang and Selangor. In these localities the cost of transport is a very serious matter, all supplies and ore having to be carried by coolies for long

distances over rough jungle paths. The workings are in shallow alluvium and decomposed granite. In the Chinchong valley boulders of a rock composed of quartz, topaz and cassiterite have been found and traced to the parent rock. In the Ulu of the Kenong angular cassiterite of varying grain-size is won, and near Bukit Fraser stanniferous granite and pegmatite occur. On Gunong Gapis, above Tras, a soft granitic rock is sluiced for cassiterite. A small lode on the Gau stream, traversing Gondwana beds, contains cassiterite associated with pyrite, chalcopyrite, bornite, arsenopyrite, zinc-blende, chalybite, calcite, quartz and garnet. The Lang and Triang valleys also contain stanniferous alluvium.

There are also alluvial workings on the Blat river, a tributary of the Kuantan.

The lodes on the Sungei Lembing, another tributary of the Kuantan, run east and west, and are from 2 to 10 feet wide. The country rock is an altered sediment overlying granite, and the geological conditions resemble those of Cornwall. The lodes carry workable amounts of copper as well as tin, especially in their upper portions.

Perak.—The Kinta district is the most important tin-mining region in the Malay Peninsula. Crystalline limestone underlies the wide valley through which the Kinta river flows. It is covered in part by clays and boulder-clays (Gopeng Beds) of supposed Gondwana age. The other Gondwana rocks are mostly shales and quartzites. Fault-blocks of the limestone form precipitous hills rising above these younger beds. The valley is flanked by the granite of the Main Range on the east, and by that of the Kledang Range on the west. The intrusion of this granite, which is evidently younger than the Gondwana rocks, was accompanied by pneumatolitic action and the formation of tin-bearing veins. But the boulder-clays contain detrital cassiterite which cannot, if they are Gondwana beds, be derived from the Mesozoic granites of the Main and Kledang ranges, but must be attributed to some earlier stanniferous intrusion. Boulders of tourmaline-corundum rock occur in these beds. The recent deposits include sand with seams of lignite, and stanniferous alluvium and cave deposits. Even the soil is stanniferous.

The principal mining areas in the Kinta District are as follows, beginning in the south-east, proceeding northward along the east side of the valley, and returning southward along the west side:—

Kampar.—In this district clays overlying limestone are

worked in the low-lying country, while shallow alluvial deposits on the granite slopes of Bujang Malaka have also yielded ore. In the Ulu of the Petai a pipe containing felspar, tourmaline, cassiterite and metallic sulphides was found in a tourmaline-felspar country rock. The pipe was at first only slightly inclined to the horizontal, and measured about 8 feet by 13 feet. The ore is said to have yielded 5 per cent. black tin, and about 1,000 pikuls (60 tons) were won from it. The apparent absence of quartz and the freshness of the felspar are peculiar features of this occurrence.

Malim Nawar.—Here sandy soil resting on limestone is washed for cassiterite. It appears to be the coarser residue of Gondwana clays.

Sungei Siput.—This village is situated on the Depang river south of the limestone mass of Gunung Tempurong. In Jehosaphat's (Jesophat's) Valley an old fault-fissure has been filled with detrital quartz, tourmaline, iron ores, topaz and cassiterite, and subsequently cemented with iron-stained calcite to form a rich "vein" about 4 feet wide. A large cave in the neighbourhood is also known to contain detrital tin ore.

Gopeng.—This area includes the Gopeng, New Gopeng, Ulu Gopeng, Kinta Tin, Tekka, and Sungai Raia mines. On many of these properties hydraulic operations are conducted on a large scale, the monitors removing clays and boulder-clays, phyllites, quartzites and granite.

Pulai.—Most of the tin ore of this field has been obtained from clays and boulder-clays, though it also occurs in the granite and in caves in the limestone.

Ulu Piah.—This mine is situated near Ampang on a patch of the clay beds faulted down between the granite and the limestone.

Tambun.—In both the Tambun and New Tambun mines the clays, which are practically free from boulders, are dug by hand and puddled to separate the tin ore.

Tanjong Rambutan.—Here, not far from the northern boundary of the Kinta district, there are two mines—the Rambutan and the Kinta Association. In the latter the clays are remarkable for the number of large quartz boulders they contain.

Menglembu.—On the west side of the Kinta valley, near Menglembu village, a number of ore-bodies have been found in the granite of the Kledang Range. Some of these are ordinary veins, while others may be described as pipes. To the former class belongs the lode on Bukit Kambing, which trends N.E. and S.W., and has a hade of 32°. The width of

the portion worked was 4 feet, and the average yield of ore 6 per cent. Work was abandoned when the yield fell to about 2 per cent. black tin. Several other lodes are known; they have a similar strike to the Bukit Kambing lode, and like it are associated with fairly fresh feldspar and much tourmaline. Fluorspar is sometimes present.

The pipe-like occurrence is seen in the workings of the Menglembu Lode Syndicate. Here the granite is strongly jointed and contains in places numerous minute veins of cassiterite set close together. Their general direction is 20° E. of N., cutting the joints at an angle of about 45° . The veinlets together compose ore-bodies which, though very irregular, average about 60 feet by 20 feet in horizontal dimensions, while one of them has been followed down for 500 feet.

Penkalan.—Three large excavations are worked to the north of Lahat. They are all in the Gondwana clays. In No. 2 a fault with a throw of about 20 feet has been exposed in the limestone floor, while in No. 3 small bodies of ore occur in the limestone itself, and the remains of others on its irregular surface.

Lahat.—In this great open-cast mine, stiff blue clays of Gondwana age overlie stanniferous granite which rises to the west, and are themselves covered by beds of sand and clay with seams of lignite. These recent deposits are a more important source of tin ore than the Gondwana clays themselves.

Rotan Dahan.—Here angular tin ore is distributed throughout a series of clays, 140 feet thick in places.

Redhills and Pusing Lama.—Both these mines are in red clays and boulder-clays with abundant boulders of tourmaline-corundum rock, and in both tin-bearing veins have been found in addition to detrital tin ore.

Pusing Bharu.—Here also the tourmaline-corundum rock is abundant in the boulder-clays. These are covered by stanniferous sandy beds and lignite. The limestone floor, by solution, gives rise to well-marked "cups," which are lined with Gondwana boulder-clays and filled with sand and lignite.

Siputeh.—Here the "cups" are even better developed, and caused great trouble when the mine was first opened. The rare occurrence of a tourmaline vein in limestone has been noticed here.

Tronoh.—A large open-cast mine was formerly worked by a system of shafts and galleries in the so-called "Tronoh deep-lead." This is really a huge trough or elongated cup in the limestone, filled with Gondwana clays below and sands and

lignite above. The western boundary is a reversed fault which brings down Gondwana quartzites and shales.

Tanjong Toh Allang.—The country here consists of quartzites, shales and tourmaline schists. The most prosperous mines are in the vicinity of kaolinitised granite intrusions.

Tin Ore in Limestone —The deposit, of non-detrital cassiterite in limestone may conveniently be described together. They occur in the form of veins and pipes, the latter being as a rule the more valuable. Veins have been found at Siak, near Siputeh; at Ayer Dangsang, near Lahat, where a pipe opened out into a vein in depth, and at Penkalan No. 3 mine, where several small stringers have been noted. A larger ore-body at this locality contained calcite, cassiterite, chalcopryrite, bornite, pyrite, arsenopyrite, tremolite, green fluorite and a little quartz. None of these veins have proved worth following up, but in two cases they gave rise to rich patches of ore owing to the solution of the limestone.

Pipes have been found at Lahat, Ayer Dangsang, Menglembu, and Changkat Paur. They are roughly elliptical in section and, in the last three localities, are composed of numerous small veins. The gangue is mainly calcite, though quartz occurs also, and the cassiterite is associated with pyrite, arsenopyrite, chalcopryrite, bornite and antimonite. Fluorite and tremolite are common, but tourmaline is rare. The Lahat pipe had a similar origin, but the calcite had been dissolved and the sulphides oxidised by descending waters.

The Larut district, to the north-west of the Kinta district, is another important tin area. The country round Taiping is an alluvial flat, rich in cassiterite, bounded on the east by the granite hills of the Taiping range, and on the west by the quartzite Semanggol Range. Lode mining has been carried on at Selama and Blanda Mabok, the lode at the latter place yielding also argentiferous galena and gold.

In the Intan field, Upper Perak, a lode on Gunong Paku is being mined.

At Bruseh, in the south of Perak, a stockwork of tin-bearing veins in schist is worked between the Pinang and Durian rivers. The veins, the average thickness of which is about 1 inch, are numerous, and generally rich in tourmaline. A little wolframite is found. The decomposed schist is worked by monitors, aided by explosives, the average yield being about $\frac{1}{2}$ kati per cubic yard (1 kati = 1.3 lb.).

Selangor.—Near Tanjong Malim, in the north of Selangor, there are numerous veins of quartz containing coarse cassiterite.

traversing soft sandstone and shale. Kalumpang and the Selangor river produce considerable amounts of ore.

Farther south, at Serendah, decomposed granite was recently worked by monitors on the site of old *lampans*, but is now worked on tribute. The granite is traversed by veins of quartz and of greisen, both carrying cassiterite.

Kuala Lumpur is the centre of the most important mining district in Selangor. At Salak South a pegmatite rich in tin is worked. The Sungai Besi occurrence, like that at Tronoh, consists of unusually rich deposits occupying a great cavity at the junction of limestone and granitic rocks. Rawang, Kepong, Setapak, Ampang and Serdang are producing localities in this district.

UNFEDERATED MALAY STATES.--The Unfederated Malay States under British protection possess tin deposits, though apparently to a less extent than the Federated States. The relative smallness of their output, however, is due in part to the primitive, small-scale operations of the Malay and Chinese miners. European methods are adopted in only a few instances, and difficulties of transport further limit the development of many of the deposits. The export of tin ore in recent years is given below :--

Table 22

Exports of Tin Ore from the Unfederated Malay States

In tons (2,240 lb)

	1912.	1913	1914	1915	1916	1917.
Johore. . .	308	461	841	2,842	3,408	3,272
Kedah. . .	835	865	860	868	679	476
Kelantan . .	19	7	9	6	--	--
Perlis . . .	188	108	187	230	209	196
Trengganu . .	403	331	379	398	475	431
Total . . .	1,753	1,772	2,279	4,344	4,771	4,375

Johore.—Up to 1914 Kota Tinggi produced most of the ore in this State, smaller amounts coming from Muar and Batu Pahat. In 1915, however, a new tin field on the east coast was opened, and produced 2,015 tons of ore, against 827 tons from Kota Tinggi. The new field appears to extend from the

Jemaluang, near Mersing, to the Sedili, and the quality of the ore is equal to that from the Kota Tinggi field.

Kedah.—There are four mining districts in Kedah, viz. Kuala Muda, Kulim, Krian and Kubang Pasu. The greater part of the tin exported from Kuala Muda district is won in alluvial workings near the town of Semiling, on the Merbok river, at the foot of the southern slope of Kedah Peak. A rich deposit of mixed tin and tungsten ore has been discovered recently near the village of Changloon in Sungai Sintok.

Kelantan.—Tin ore has been worked on a small scale at Bukit Yong, Pulau Chondong and on the Nenggiri, but, as the British Adviser says in his Administration Report for 1914, "serious mining has at present no existence in Kelantan." Good tin deposits have been reported from time to time in Ulu Kelantan and elsewhere, and transport difficulties are partly responsible for the lack of development.

Perlis.—In the State of Perlis, which lies to the north of Kedah, cassiterite is won from caves and underground streams in the limestone hills on the Setul border. Some of these underground workings extend for a distance of four or five miles.

In many cases work can only be carried on during dry seasons, or after pumping. The tin-bearing deposits in the caverns are not extensive, prospecting is difficult, cost of transport is very high, and large-scale operations are extremely risky, though the Chinese meet with a small capital will often do well. In one instance a gravel pump and steam plant were installed to work an underground stream, with quite inadequate results. The cassiterite is usually very fine-grained, and the cave deposits are in some cases cemented by oxide of iron, necessitating crushing. Some danger to the paddy fields in time of flood has been anticipated from the tailings, where these accumulate in large quantities.

Trengganu.—In Kemaman, in the south of Trengganu, lode mining is carried on at Bundi and Sungai Ayam. The bulk of the ore produced comes from these mines, both of which are under European management.

The Bundi deposit consists of soft clayey and sandy material, with masses of quartz, sulphides and iron oxides, between walls of hard granite. The length is 1,575 feet and the greatest breadth 120 feet, and the bottom has been reached only at Glen Reef, the most northerly working. The cassiterite occurs in the soft clay and in the ironstone, in the form of slender, pale yellow needles, sometimes forming spongy masses.

The Sungei Ayam lode is from 2 to 3 feet wide. It is very flat, and is mined by a succession of shallow stope-drives.

Sungei Sendok, Sungei Paka, and Sungei Kajang also produce some tin. On the Dungan river wolframite and a little cassiterite are won. At Bukit Tawang, at the head of the Trengganu river, an attempt at hydraulic mining proved unsuccessful.

STRAITS SETTLEMENTS.—The Straits Settlements are small in area and only Malacca produces any tin ore. But they possess the largest tin-smelting and refining industry in the world, which is divided between Singapore and Penang. The states of the Malay Peninsula are naturally the source of the greater part of the ore smelted, but Siam, the Dutch Indies, Australia, South Africa, Burma, and even Alaska send tin ore to the Straits for smelting. A certain amount of crude tin is also received and refined.

The magnitude of the industry is indicated in the following tables. Table 23 shows the source of the tin ore and metallic

Table 23

Imports of Tin Ore and Tin to the Straits Settlements in 1914

In tons (2,240 lbs.)

Countries from which Imported	Quantity		Value.
	To Singapore	To Penang	
<i>Malay Peninsula</i>			£
Johore ore	720	—	72,760
Kedah "	—	819	76,161
Kelantan "	21	—	2,029
Trengganu "	379	—	39,867
Negri Sembilan "	1,182	1,049	262,818
Pahang tin	1	—	192
" ore	2,926	—	349,925
Perak tin	294	—	43,798
" ore	14,716	21,687	3,859,836
Selangor tin	72	1,790	277,695
" ore	12,223	8,152	2,122,722
" tin	1,510	1,159	493,137
India (Burma) ore	—	113	11,470
Hong Kong "	2	—	168
" tin	2	—	252
Australia ore	2,574	197	302,225
South Africa "	2,700	—	296,742
Dutch East Indies "	1,214	—	465,763
Siam "	518	7,324	801,009
" tin	262	356	75,993
United States ore	26	—	3,150
Total ore	42,495	38,951	8,086,645
" tin	2,081	3,302	801,067

Table 24
Imports of Tin Ore into the Straits Settlements
(Pikuls of 133½ lb.)

Countries from which Imported	1910	1911	1912	1913	1914	1915	1916	1917
Federated Malay States	778,366	767,969	860,155	1,033,360	1,035,369	987,433	882,036	756,601
Unfederated Malay States	28,107	26,052	35,049	27,215	32,610	82,641	95,528	78,574
Australia	42,001	48,039	51,810	61,813	45,032	35,311	34,867	20,393
India	—	1,685	2,659	2,453	1,892	1,393	2,307	5,951
South Africa	—	3,777	29,210	44,048	45,357	36,206	44,338	53,805
Other British Possessions	—	170	200	206	29	3,650	16,650	1,337
Total from British Possessions	849,577	847,692	979,123	1,169,128	1,160,289	1,146,634	1,075,726	916,061
Dutch East Indies	73,904	51,650	65,325	54,982	70,789	108,806	113,918	132,725
Siam	62,372	75,826	114,105	135,390	131,744	174,486	194,960	190,666
United States	—	—	—	1,110	430	5,305	1,106	825
Other Foreign Countries	1,380	197	—	—	—	—	—	2
Total from Foreign Countries	137,656	130,673	179,490	191,482	202,969	286,597	309,933	324,518
Total	987,233	978,365	1,158,613	1,360,610	1,363,258	1,433,231	1,385,659	1,240,579
Value	58,704	58,230	68,965	80,989	61,146	85,311	82,480	73,444
	6,023,977	7,522,054	9,836,326	11,330,506	8,666,645	9,169,349	9,522,339	10,483,574

STRAITS SETTLEMENTS

45

Table 25
Imports of Tin into the Straits Settlements
(Pikuls of 133 lb)

Countries from which Imported	1910	1911	1912	1913	1914	1915	1916	1917.
Federated Malay States	165,233	168,091	180,312	100,437	81,035	82,999	91,563	99,102
Unfederated Malay States	—	28	102	—	—	—	103	—
Hong Kong	70	4,682	—	—	27	170	24	406
Other British Possessions	46	24	—	1	—	—	9	—
Total from British Possessions.	165,349	172,825	180,414	100,438	81,065	83,169	91,750	99,508
Dutch East Indies	1,075	—	25	45	—	29,534	37	—
Siam	12,200	33,207	20,086	15,013	9,374	11,051	8,060	7,087
Other Foreign Countries	—	26	9	10	—	—	—	—
Total from Foreign Countries	33,205	33,227	20,720	15,118	9,374	35,185	775	7,087
Total	198,554	206,052	201,134	115,556	90,439	121,354	100,464	107,195
Value	11,819	12,265	11,972	6,878	5,373	7,223	5,970	6,380
	1,750,766	2,258,854	2,392,950	1,335,283	861,667	1,063,453	992,875	1,330,943

SOURCES OF SUPPLY OF TIN ORES

Table 26
Exports of Tin from the Straits Settlements
(Pikuls of 133½ lb.)

Countries to which Exported	1911	1912	1913	1914	1915	1916	1917
United Kingdom	550,627	563,280	591,025	596,476	351,760	421,232	449,481
India	24,824	23,313	30,494	27,583	22,793	23,257	22,967
Ceylon	643	1,192	491	815	964	513	1,195
Hong Kong	2,733	1,883	5,653	2,759	1,205	9,090	4,208
Canada	1,396	4,749	4,292	1,202	2,185	673	1,515
Australia	—	—	—	429	—	—	67
Other British Possessions	175	139	335	114	306	361	1,978
Total to British Possessions	559,375	565,856	632,887	629,426	479,013	455,432	481,411
Austria-Hungary	17,666	—	—	—	—	—	—
Belgium	—	25,897	25,817	15,725	—	—	—
France	—	—	168	6,306	—	—	—
Germany	53,853	60,911	81,326	66,840	78,911	71,361	100,470
Italy	2,559	6,894	10,762	21,398	—	—	—
Netherlands	23,211	17,746	22,241	25,016	32,561	34,667	38,094
Russia	12,529	15,723	—	421	—	—	—
Spain	4,356	4,549	8,390	3,005	69,678	28,774	18,188
China	253	—	—	76	3,026	5,769	5,969
Japan	2,982	1,517	2,901	1,565	2,170	268	875
Dutch East Indies	11,155	10,746	13,227	13,495	15,914	20,577	28,216
Siam	2,197	1,466	990	252	621	90	—
United States	98	227	724	1,890	1,974	1,610	1,112
Other Foreign Countries	214,426	256,517	297,955	325,079	542,494	472,070	392,327
Total to Foreign Countries	550	605	4,308*	605	239	5,257	9,052
Total	311,087	410,967	471,720	483,288	746,628	640,449	594,303
Total	964,402	1,034,833	1,101,607	1,112,714	1,155,641	1,095,881	1,075,714
Value	57,405	61,597	63,750	66,231	68,788	65,231	64,031
Value	8,797,247	10,737,717	13,171,563	9,983,606	10,686,813	11,392,201	13,745,750

* Including 3,614 pikuls to Denmark.

tin received at Singapore and Penang in a typical year, 1914, while Tables 24 and 25 show the imports from 1910 to 1917 in a more generalised form. The increase in the imports from the Dutch East Indies in 1915 was due to the war and the Allied blockade of Germany. Table 26 gives the distribution of Straits tin in the same years, and shows one effect of war conditions in the increase in shipments direct to the United States, Russia, and other countries, instead of via England. The increased export to Germany in the early part of 1914 is noteworthy.

MALACCA—The tin ore exported from Malacca in the years 1912-1917 amounted to 11, 15, 0, 57, 30 and 10 long tons respectively.

On the coast of Malacca, for some distance south of Kuala Linggi, the sand and mud below high-tide mark have been washed for tin. The source of the mineral is a schist with numerous quartz veinlets carrying cassiterite. The schist overlies granite, and forms the shore for some distance. This schist has been mined, but most of the tin produced in Malacca has come from the beach deposits, where the material has been disintegrated and concentrated by the waves.

At Chin-Chin some tinstone has been obtained from the soil, but ferruginous cement interferes with hydraulic operations.

AFRICA

GOLD COAST.—Stream tin has been found in small patches of gravel in the Winnebuh district. Tinstone also occurs on the surface and in pegmatite-grisen dykes in the Mankofa depression and on Mount Mankwadi, in the same district.

NIGERIA.—Before the coming of Europeans, tin was produced in Bauchi by the natives, who washed the river gravels in calabashes and obtained coarse black tin with 60 to 65 per cent. of the metal. The smelting was a family secret. Small blast furnaces, 3 feet 6 inches in diameter, were used, with charcoal fuel and a blast supplied by primitive bellows of sheepskin. The metal was cast in the form of thin rods about $\frac{1}{2}$ inch in diameter and 12 inches long; it contained about 99.4 per cent. tin. There is little doubt that the metallic tin found in the gravels was smelted by the natives.

On the subjugation of the hostile Emir of Bauchi in 1902, the alluvial deposits of the Delimi river at Naraguta became known, and were worked first by the Niger Company. Between 1904 and 1909 the work of the Mineral Survey of Northern Nigeria, in conjunction with the Imperial Institute,

48 SOURCES OF SUPPLY OF TIN ORES

showed the presence of cassiterite in the stream gravels of many localities, but it was not till 1909 and 1910 that a number of companies were formed for the purpose of winning tin in Nigeria. The former inaccessibility of the field has been removed by the construction of a railway between Naraguta and Zaria, where it connects with the Baro-Kano line. An extension to Jos and Bukuru was opened in 1914.

Table 27 shows the output and exports of ore and tin from Nigeria. Practically the whole amount was sent to the United Kingdom, as is shown in Table 28.

Table 27
Output and Exports from Nigeria
In tons (2,240 lb.)

Year.	Output	Exports.		
	Ore	Ore	Metal.	Value (£).
1904	1½	—	—	—
1905	½	—	—	—
1906	11	—	—	—
1907	175	21	133	25,265
1908	514	519	17	80,799
1909	453	269	39	42,141
1910	774	692	31	77,310
1911	1,470	1,530	—	181,759
1912	2,886	2,803	—	336,330
1913	5,331	4,194	2	568,428
1914	6,143	6,175	—	706,988
1915	6,910	6,535	—	723,480
1916	8,222	7,054	—	859,603
1917	8,314	9,966	—	1,485,887
Total . . .	41,005	39,758	222	5,087,990

Table 28
Exports of Tin Ore and Tin from Nigeria, 1910-1917
In tons (2,240 lb.)

Countries to which Exported	1910	1911.	1912.	1913.	1914.	1915.	1916.	1917.
United Kingdom, ore	689'11	1,529'35	2,802'64	4,193'72	6,175	6,535	7,054	9,966
" " tin	30'72	—	—	2'17	—	—	—	—
Germany " ore	2'80	0'25	0'36	0'04	—	—	—	—
" " tin	0'05	—	—	—	—	—	—	—
Total . . ore	692	1,529'60	2,803'00	4,193'76	6,175	6,535	7,054	9,966
" " tin	30'77	—	—	2'17	—	—	—	—
Value . . £	77,310	181,759	336,330	568,428	706,988	723,480	859,603	1,485,887

The chief source of the tin is the river gravels and alluvial flats in the neighbourhood of Naraguta, Ngell, Bukuru, Forum, Ropp, etc., on the Bauchi plateau. The plateau has an elevation of three or four thousand feet, and the climate is consequently much healthier than in most parts of West Africa. Here in the ancient crystalline rocks is an extensive intrusion of soda granite, with pegmatite dykes and veins of quartz and tourmaline, and from these sources the stream tin was derived. Near Ngell the granite contains cassiterite associated with pyrite, chalcopyrite, tetrahedrite, zinc-blende, galena and sometimes wolframite. The concentrates from the alluvial deposits often contain much ilmenite, as well as zircon, garnet and monazite. Rolled fragments of topaz are also common.

In the upper portions of the streams the patches of tin-bearing gravel held up by bars of hard rock are usually so small that they are left to native tributers to work. The middle courses have more extensive areas yielding tinstone beneath 10 to 30 feet or more of barren overburden, and here hydraulic methods are profitably employed. The tin usually occurs close to the bedrock, but there are sometimes two or more tin-bearing layers. The overburden is often baked hard in the dry season, and black powder has been used in places to break it up. In the lower sections of the valleys the deposits near the present streams frequently yield little or no tin, and systematic prospecting by bore-holes is required to determine the position of the old stream channel with its tin-bearing gravel, which may lie beneath a cover 100 feet deep or more. The work of lifting the overburden and tin-gravel in these thick deposits will prove very costly if coal or crude oil is used to operate the gravel pumps, and it has recently been proposed to utilise the water-power of the Kwall Falls, where the Ngell River drops 800 feet over the edge of the plateau.

In addition to this central and highly important field of the Bauchi plateau, tinstone occurs in many other parts of the Northern Provinces, as in the Ningi and Burra hills in Bauchi, in the neighbourhood of Gadama and Fagam on the borders of Bauchi and Kano, around Jemaa, Amari, Gantam and Aribi in the north of Nassarawa, on the Vere hills in Yola and the Shebshi hills in southern Muri, and near Eri in eastern Ilorin, where it occurs in pegmatites carrying quartz and muscovite but no tourmaline.

In the Southern Provinces, the work of the Mineral Survey of Southern Nigeria showed the presence of cassiterite in the sands of many streams. The most notable occurrences observed

are those near Akwa-Ibami, in the Uwet district, where the proportion of cassiterite in the stream beds was found to be from 2 to 5.2 lb. per ton, with an average of 3 lb. per ton. There was a small output of 35 tons of tin ore in the Calabar Province in 1916.

NYASALAND.—A few of the concentrates from river sands examined at the Imperial Institute in connection with the Mineral Survey of Nyasaland were found to contain small amounts of cassiterite, but no deposits of economic importance are known in the Protectorate.

RHODESIA.—Promising deposits of tinstone occur in the Enterprise district, east of Salisbury, and farther south in the Ndanga district, 30 or 40 miles east of Victoria. In both localities the ore occurs in pegmatite dykes, which are more or less greisenised and traverse ancient schistose rocks in the neighbourhood of granite. Lithia-mica, lepidolite, is abundant in the tin-bearing dykes, and, with its striking purple colour, forms a useful indicator. The cassiterite is patchy in its distribution; it is dull black in colour and, in the Victoria field, shows unusual crystalline forms. West of Untali, alluvial tin is reported in the Odzi Reserve and along the Tsungwesi River, and the lithia greisens of the former locality yield tin, tungsten and tantalum minerals. In the Hartley district near the Umniati River, cassiterite occurs with copper ore in chlorite schist, and tin-bearing pegmatite dykes are known in the Mazoe and Shamva districts. No tin-bearing alluvial deposits have been discovered, though there are considerable amounts of shed tin in the vicinity of the dykes. Some development work has been done on the more promising lodes in these districts since the first discovery of tinstone in 1908, and 9 short tons of ore was exported in 1915, while the Secretary for Mines reports an output of 3.63 short tons of tin from the Victoria district in 1916. The high working costs are a serious obstacle to the successful extraction of tin ore in Rhodesia.

UNION OF SOUTH AFRICA (for South-West Africa see p. 92). —The chief tin-mining districts in South Africa are the Waterberg area, in the western Transvaal, and Swaziland (p. 55). The Cape Province also produces a little tin, the total output from 1906 to the end of 1917 being valued at £49,817, against a value of £3,229, 753 for the Transvaal.

There was until recently no tin-smelting industry in South Africa, and the ore, which was formerly exported to England, was later sent almost entirely to the Straits Settlements. In 1917, however, smelting began at Zaaiplaats, and these works

Table 29

Output of Tin Ore in the Union of South Africa

In short tons (2,000 lb)

	1912.	1913.	1914.	1915.	1916.	1917.
Cape Province	---	71½	43	30½	20	38
Transvaal	2,032	3,906½	3,376	3,194½	3,235	2,640
Total . tons	2,032	3,977½	3,419	3,225½	3,255	2,678
Value . £	307,099	439,557	311,391	331,420	330,571	319,016

are expected to supply the whole of the South African demand for tin. The output in 1917 was at the rate of about 250 tons per annum, most of which was used in the manufacture of white bearing metal for the railways. Delagoa Bay and Durban are the chief shipping ports for the ore, and Table 30 shows its destination.

Table 30

Exports of Tin Ore from the Union of South Africa

In short tons (2,000 lb)

Countries to which Exported.	1910.	1911.	1912.	1913.	1914.	1915.	1916.	1917.
United Kingdom	2,408	1,709	811	1,219	1,335	1,265	56	30
Straits Settlements	—	12	1,104	1,760	2,021	2,529	2,591	2,660
Other countries	—	8	3	23	23	59	—	—
Total . tons	2,408	1,719	1,918	2,779	3,381	3,853	2,557	2,690
Value . £	175,994	241,601	210,329	381,942	457,925	385,901	235,890	282,743

Table 31

Imports of Tin into the Union of South Africa

In short cwt (100 lb)

Countries whence Imported.	1910.	1911.	1912.	1913.	1914.	1915.	1916.	1917.
United Kingdom	1,314	1,232	1,331	1,262	1,301	1,377	1,869	2,795
Other countries	1	2	14	9	—	29	—	312
Total . cwt.	1,315	1,234	1,345	1,271	1,301	1,397	1,889	3,017
Value . £	8,344	9,224	12,988	12,797	10,294	11,170	16,771	35,074

South African imports of tin are given in Table 31. The country's requirements are small, and have hitherto been supplied almost entirely by the United Kingdom. Imports of tin plate fell from 4,458 tons in 1915 to 2½ tons in 1917, and the imports of tin manufactures vary in value between £30,000 and £50,000 a year.

CAPE PROVINCE.—Cassiterite occurs in several localities in the neighbourhood of Cape Town. The most important appears to be at Annex Langverwacht, near Kuils River. Here it occurs disseminated through a granite, and also in veins of quartz and greisen near the junction of the granite with the Malmesbury slates. Wolframite and tourmaline are associated with the cassiterite, and considerable deposits of tin-bearing gravel have been formed by the disintegration of the rocks. The tin ore produced in 1916 was all obtained from these gravels, while a certain amount of development work has been done on the tin-bearing lodes in the neighbourhood. Stanniferous quartz veins also occur at Vredchoek, at the north-west end of the Tygersberg, and in other places.

NATAL.—In the Umfuli tin field, situated about eight miles east of Melmoth in the Entenjani district of Zululand, a plateau of Waterberg sandstone has been cut through by the Umfuli river and its tributary, the Ntunja. A small area of hornblende-schists of the Swaziland System has thus been exposed. The schists are permeated by numerous veins of pegmatite and aplite, and cassiterite occurs in the pegmatites in association with mica, garnet, tourmaline, quartz and feldspar. The cassiterite is sporadic in its distribution, and samples of the pegmatite assayed from a trace to 0.316 per cent. of metallic tin. Prospecting in this district has so far met with disappointing results.

TRANSVAAL.—The Waterberg tin fields in north-western Transvaal include the Potgietersrust tin field (Zaaiplaats, Rooipoort, Groenfontein, Solomon's Temple, etc.), the Nylstroom tin field (Doornhoek, Kronikloof, Welgevonden), the Warmbaths tin field (Zwartkloof, Elandsfontein, Witfontein, etc.), and the Rooiberg tin field. All these localities lie on the eastern and southern margins of a geological basin, the central portion of which is composed of sandstones and conglomerates of Upper Waterberg age, constituting the Waterberg plateau. Below the escarpment of these beds is a belt of Lower Waterberg felsites with interbedded shales (and quartzites in the Rooiberg), overlying the Red Granite and the Norite of the Bushveld Plutonic Complex. Beyond the out-

crop of these lie the Older Granite and the quartzites and dolomites of the Transvaal System. These older rocks, however, are unconnected with the source of the tinstone, and the same may be said of the Karroo beds which overstep all these formations in the south-eastern part of the district. The Red Granite and the Lower Waterberg rocks are the important tin-bearing formations. In the Red Granite the cassiterite deposits occur (a) in the form of roughly cylindrical pipes; (b) associated with irregular bodies of altered granite; (c) as irregular disseminations in slightly altered granite; (d) as impregnations along well defined lines of fissure; (e) associated with pegmatite and quartz veins. In the felsites, shales and quartzites of the Lower Waterberg the deposits are found (a) in lodes and more or less definite lines of fissure, small veins, and leaders, and (b) as irregular patches and pockets, often connected with fissures or determined by planes of stratification. Ancient workings, smelting places and ingots show that tin was extracted in this district at some unknown period in the past.

The most important deposits in the Potgietersrust tin field are situated on the farms Zaaplaats, Roo-depoort, Groenfontein and Solomon's Temple. They are distributed along a well-defined zone in the Red Granite, which strikes in a north-west and south-east direction and continues into Groenylei and Appingadam in one direction and Welgevonden, Welgelegen, and Grootrivier in the other. This zone comes immediately below a coarse pegmatite. The usual type of deposit in this field is that of cassiterite-bearing pipes, roughly circular in section, descending at varying angles into the granite in a general north-westerly direction. They vary from a few inches to 20 feet in diameter. They are very erratic in direction and variable in composition, and in some cases have been followed through 3,000 feet of ramifications. They usually occur in groups, and neighbouring pipes may unite either at depth or near the surface. The pipes sometimes show an outer zone of tourmaline-quartz rock, which is usually not more than a few inches thick. The main mass of the pipe varies from slightly altered granite to an apparently homogeneous greenish material, which sometimes becomes extremely hard through secondary silicification. In the smaller pipes the cassiterite is fairly uniformly distributed, but in the larger ones it is generally more concentrated towards the periphery, and especially the lower portion, while in the central part it is less abundant or even absent. Cavities or vughs occur in

some of the pipes; they are lined with quartz crystals and contain also fluorite, galena, zinc-blende, arsenopyrite and chalcopyrite. In addition to the pipes, several other types of ore body are found, some of which show a flat and more or less lenticular form. In one case there are several sheets of tin-bearing granite separated by barren rock. Fissure veins and irregular masses of altered tin-bearing granite also occur.

The Nylstroom tin field is situated on the farms Doornhoek, Kromkloof, and Welgevonden, some sixteen miles north-east of Nylstroom. The principal deposits are associated with the felsites and shales of the Lower Waterberg. The main lode at Doornhoek cuts the bedding-planes of the shales obliquely; it averages 18 inches in width, and is largely made up of brecciated and highly altered fragments of the country rock, with quartz, tourmaline, cassiterite and fluorite. A second lode follows one of the coarser beds in the shales, which also is much altered and brecciated. In the immediate neighbourhood of these lodes the shales sometimes show minute veins of cassiterite. A short distance below the base of the shales the underlying felsites carry cassiterite, associated with quartz and hematite, in small pockets from $\frac{1}{2}$ inch to $1\frac{1}{2}$ inches in diameter, while other pockets contain tourmaline with quartz and sericite matter.

The Warmbaths tin field extends from Zwartkloof through Droogekloof, Flandsfontein and Newbury to Witfontein and thence northward to Rhenosterpoort, forming a narrow belt which follows the junction of the felsites and the Red Granite. Cassiterite occurs in both types of rock, and also in detrital deposits. At Zwartkloof the ore bodies are somewhat irregular and ill-defined; they occur in the granite and are frequently associated with masses and veins of very coarse pegmatite and quartz. Alluvial and eluvial deposits occur on this farm. On Flandsfontein No. 1,782, there are two main sets of fissures in the granite, and the ore bodies associated with them vary in width from a few inches to 2 or 3 feet. Fissure lodes also occur in the lower part of the felsites. On Witfontein No. 371 the alluvial deposits have proved more important than the occurrences in the granite and felsite. All three types of deposit occur also on Flandsfontein No. 2,149, and small quantities of tin have been won from the granite on Rhenosterpoort.

The Rooiberg tin field lies about 40 miles west of Warmbaths. The cassiterite deposits, with the exception of one occurrence in the Red Granite, are all found in the Rooiberg

quartzites, which, with the associated shales, are overlain with apparent conformity by the Lower Waterberg felsites, while both types of rock are intruded by the Red Granite. The workings are principally on the farms Olievenbosch, Hartebestfontein, Weynek, Quaggadontein and Leeuwpoort, and many of them are on the site of ancient workings. The lodes in the quartzites coincide with two main sets of fissures, and there are also irregular pockets in the country rock rich in tourmaline and cassiterite. Other minerals frequently present are quartz, carbonates of iron and lime, felspar, fluorite, hæmatite, pyrite, chalcopyrite and bornite. Superficial deposits of limonitic breccia, known as "ou-klip," are occasionally rich in tin. On Quaggadontein, cassiterite occurs in the upper portion of the Red Granite.

Forty miles north-east of Pretoria, cassiterite occurs in the Red Granite on the farms of Enkeldorn, Vlaklaagte and Roo-depoortje.

On the Olifants River, tin ore is won at Mutne Fides and Stavoren. A considerable amount of scheelite is present in the Stavoren ore, and difficulty has been experienced in disposing of the tin-tungsten concentrate, since scheelite cannot be separated magnetically, as can wolframite. The Swaziland tin deposits cross the border into the Eastern Transvaal, but are not at present worked there.

SWAZILAND

Table 32

*Output of Tin Ore in Swaziland in the Years ending March 31,
1911-17*

	1910-11	1911-12	1912-13	1913-14	1914-15	1915-16	1916-17
Quantity, tons *	476	311	35	192	195	524	459
Value, £	42,250	42,896	37,049	51,000	43,500	50,000	46,732

* Kind not stated.

There are two tin-bearing districts in North-Western Swaziland, viz. the alluvial deposits of Mbabane (Embabanan) and the surrounding country, and the lodes round Forbes Reef.

The detrital deposits occur as "flats" along the course of the Mbabane and other rivers, and to a less extent on the hill slopes. At King's Flat, to take a typical example, there is a soft overburden of about 12 feet of dark soil, which carries

little tin. Below this lies $2\frac{1}{2}$ feet of coarse tin-bearing gravel, composed largely of fragments of quartz up to 3 inches across, which rests on the granite floor of the valley. The cassiterite occurs in the gravel as loose crystals, but occasionally in boulders of pegmatitic rock; it is associated with other accessory minerals of the granite, including ilmenite, monazite, euxenite, aschynite, corundum and tourmaline. The cassiterite is evidently derived from the pegmatite dykes and quartz veinlets in the granite, which belongs to the Older Granite and not the Red Granite of the Waterberg tin fields. The mineral has been seen in many of these pegmatites, and at Sanders Creek a dyke of decomposed pegmatite yielded considerable amounts when worked by hydraulic methods. Since 1912, hydraulic operations have proved most successful. A race 14 miles long brings water from the Umbelusi River, which, together with local supplies, is used three times over in monitors to break ground at different levels, and also generates power for elevating the material it has already broken.

Forbes Reef is situated some 14 miles north of Mbabane on the east side of the Ingwenya Range. This range is formed of quartzites and schists of the Swaziland System, in which are intrusions of the same granite as at Mbabane. In one case the tin occurs in a dyke in the schist, 2 to 3 feet wide, composed almost entirely of white feldspar with patches of chlorite and cassiterite. More usually the veins follow fissures parallel to the strike of the schists. Along these fissures the schist is tin-bearing over a width of about 3 inches.

AMERICA

CANADA-- At New Ross, Lunenburg County, Nova Scotia, a quartz vein in granite carries a streak of rich ore from 3 to 5 inches wide. This contains cassiterite and chalcopyrite, with tungsten and zinc minerals, and assays from 10 to 30 per cent. tin and 8 per cent. copper. Pegmatitic zones in the granite also contain cassiterite.

Tin and tungsten ores occur on the south-west branch of the Miramichi River, New Brunswick, and cassiterite has also been recorded from several localities in British Columbia and from the Yukon district. A sample of black sand from sluice boxes in the Atlin district of British Columbia is said to have assayed 6.71 per cent. of tin.

There is, however, no production of tin ore in Canada.

The imports of the metal are shown in Table 33. Some 50,000 tons of tinned plate are imported annually, mostly from the United States.

Table 33
Imports of Tin into Canada in the Years ending
March 31, 1912-17

(Short cwt. of 100 lb.)

Countries whence Imported	1911-12	1912-13	1913-14	1914-15	1915-16	1916-17
United Kingdom	22,855	21,135	17,574	12,173	21,953	30,759
Straits Settlements	5,939	7,973	7,919	18,26	121	112
Hong Kong			195	891	116	
Total from British Possessions	28,794	29,108	25,548	14,943	22,190	30,871
United States	11,710	22,778	20,737	11,719	7,936	1,855
Other foreign countries	286	333	91	112		
Total from Foreign Countries	12,046	23,111	20,828	11,841	7,936	4,855
Total short cwt.	40,840	52,219	46,376	26,762	30,126	35,726
Value	£ 355,553	1,76,280	1,08,320	50,145	213,250	303,079

AUSTRALASIA

Table 34
Output of Tin Ore and Tin in the Commonwealth of Australia

In tons (2,240 lb.)

	1912	1913	1914	1915	1916	1917
New South Wales (metal ore)	900	903	650	857	909	1,109
Northern Territory	1,175	2,118	1,667	1,331	1,220	963
Queensland	271	258	166	140	—	—
Tasmania	3,249	3,197	2,985	2,125	1,707	1,177
Victoria	3,714	4,040	2,573	2,599	2,855	2,637
Western Australia	48	57	53	96	122	139
	551	661	332	326	435	—
Total, ore and metal	6,892	11,114	7,529	7,171	—	—
Value	£ 1,313,573	1,397,197	752,095	798,911	—	—

AUSTRALIA.—Since 1872, when tin mining began in New South Wales, Queensland and Tasmania, Australia has pro-

SOURCES OF SUPPLY OF TIN ORES

Table 35

IN CASE OF

[†] Years ending June 30th, 1915-17.

Table 36
Exports of Tin from the Commonwealth of Australia

In cwt (112 lb)

Countries to which Exported	AUSTRALIA						
	1900*	1911*	1912*	1913*	1914-15†	1915-16†	1916-17†
United Kingdom	67,433	66,951	61,48	45,128	23,653	58,966	24,922
New Zealand	2,713	3,671	3,284	3,355	3,225	3,234	2,639
Other British Possessions	17	672	27	11	205	12	8
Total to British Possessions	70,163	71,694	64,795	48,494	27,083	62,212	27,569
Belgium	6,368	2,686	3,142	5,879	—	—	—
Germany	1,757	3,258	5,16	11,178	1,071	—	—
Italy	—	1,270	1,270	1,100	—	—	320
United States	92	479	37	—	1,029	1,224	31,278
Other Foreign Countries	11	3	45	14	21	2,278	2,038*
Total to Foreign Countries	17,369	11,696	11,253	17,120	3,11	6,475	33,516
Total	87,532	83,390	76,048	65,614	30,194	68,687	61,085
Value	675,830	725,177	777,588	651,211	226,187	576,983	571,353

* Years ending December 31st, 1911-13

† Years ending June 30th, 1915-17.

‡ Including 1,900 cwt to France.

duced considerable quantities of tin ore. In 1907 the output was about 14,000 tons of ore, and the Commonwealth ranked fourth among the world's producers, but since that date the output has diminished. All the States contribute, with the exception of South Australia, and Table 34 shows their shares in the annual output.

The total value of the Commonwealth output up to 1916 amounted to about £35,000,000, of which Tasmania contributed £13,000,000, New South Wales £10,500,000, Queensland £9,000,000, Western Australia £1,200,000, Victoria £800,000, and the Northern Territory £400,000.

There are tin-smelting works at Launceston in Tasmania; Woolwich, near Sydney, New South Wales; and Irvinebank, near Herberton, Queensland. The metallic tin is exported to the United Kingdom, New Zealand and other countries. An increasing proportion of the ore produced is, however, sent to the Straits Settlements for smelting. Tables 35 and 36 give details of the ore and tin exported. The reduction of the exports by over 50 per cent. in the year 1914-15, as compared with 1913, was due partly to the war, partly to the effect of the dry season which interfered with dredging operations; and a considerable recovery is shown in the figures for 1915-16.

The imports of tin into Australia, as shown in Table 37, are very small, but there is a large amount of tinned plate imported, chiefly from the United Kingdom. The total imports of tinned plates and sheets into the Commonwealth in the year ending June 30, 1917, amounted to 823,349 cwt., valued at £1,330,636.

Table 37
Imports of Tin into the Commonwealth of Australia

In cwt (112 lb)

Countries of Origin	1910 *	1911 *	1912 *	1913 *	1914-15 †	1915-16 †	1916-17 †
United Kingdom	230	100	125	2	294	10	62
Other Countries	1	2	—	—	—	—	—
Total	231	102	125	2	294	10	62
Value	£ 1,858	972	1,491	20	2,238	101	594

* Years ending December 31st.

† Years ending June 30th.

NEW SOUTH WALES.—The total production of New South Wales, from the beginning of the industry in 1872 up to and including 1917, is 82,904 tons of tin and 33,967 tons of tin ore, of a total value of £10,963,004. The output of ore in recent years from the principal fields is given below.

Table 38

Output of Tin and Tin Ore in New South Wales

	1914	1915	1916	1917	1918	1919
Ardlethan Div., ore and concentrates valued at £	7,714	12,536	25,332	54,414	29,593	61,669
Bendemeer Div. ore, tons	21	52	27	•	•	•
Deepwater Div. " "	19	46	3	•	39	22
Emmaville Div. " "	1,118	1,088	961	1,115	1,088	936
Glen Innes Div. " "	6	128	191	103	120	138
Inverell Div. " "	14	40	•	•	31	200
Tingha Div. " "	1,066	1,109	93	66	70	600
Torrington Div. " "	76	110	•	59	615	103
Wilson's Downfall Div. " "	167	158	175	139	137	128
Total output, metallic tin, tons	9,8	9,33	6,50	85	999	1,109
" output, tin ore, "	1,135	118	1,160	1,331	1,220	963
" value of tin and ore	1,382,71	121,292	297,130	66,780	96,497	373,696

• Not stated

The metallic tin produced in New South Wales is smelted at Woolwich, near Sydney, and the ore exported goes mainly to the Straits Settlements.

Tin deposits are widely distributed over the State, but the most important are situated in the north-eastern part, with Emmaville and Tingha as the chief centres. All the localities mentioned in the above table are in this quarter, with the exception of Ardlethan.

Tin-mining began at Elsmore, near Inverell, in 1872. Here the cassiterite occurs as crystals disseminated through granite and greisen, and, on the decomposition of the rock, has become concentrated in surface deposits. It is associated in these deposits with some wolframite, and also with carbonate of bismuth. The wolframite is derived from lodes which cut the granite, but do not appear to be stanniferous.

In the surrounding district shallow alluvial deposits were soon discovered, and for the most part worked out, as at Newstead, Stannifer, Tingha and Stanborough.

Cassiterite was found abundantly in the bed of Cope's Creek, and also in the alluvial flats bordering it. At Tingha, on this stream, dredging for tin was commenced in 1900 for the first time in New South Wales. In 1912 two-thirds of the total output of the State was furnished by dredging plants, of which there were thirty-five of the suction-pump type, and only four bucket-dredges. To the end of 1917 the dredges produced 18,854 tons of concentrates, valued at £2,078,778.

In addition to recent and Pleistocene superficial deposits, there are in the Tingha-Inverell district Eocene alluvial deposits of similar origin and containing cassiterite derived from the same granitic rocks. These old valley deposits, known as "deep leads," were buried beneath sheets of basaltic lava, the outpouring of which was accompanied by eruptions of volcanic ash now altered to bauxite. The Elsmore Valley Lead is an example; there are three beds of wash-dirt, 70½ feet, 1½ feet and 1 foot thick, worked by a mine 225 feet deep. The Newstead Lead was worked from its outcrop, and found to deepen gradually northward to a depth of 130 feet or more.

Near the junction of Cope's Creek with the Gwydir River there are several hills of basalt overlying a Tertiary stream-deposit. This is worked for diamonds, which are small but numerous, and are accompanied by topaz, sapphire, zircon, tourmaline, ilmenite, magnetite, spinel, cassiterite, etc. Although not in sufficient quantity to pay the whole cost of extraction, the flintstone forms a valuable by-product of the diamond-washing.

The Emmaville or Vegetable Creek district is some 40 miles to the north east of Inverell and Tingha, with similar geological conditions. The oldest sedimentary rocks at Emmaville are bluish-grey claystones of Carboniferous age, which have been intruded by tin-bearing granite and by quartz-felsites and diorites. There are Tertiary alluvial deposits covered by sheets of lava and volcanic ash, and also post-Tertiary stream-deposits.

Of the last type, the most productive was that of Vegetable Creek. The upper 5 miles of this stream are stated to have yielded 15,000 tons of cassiterite between 1872 and 1884, the area worked being about 150 acres, and the average depth of gravel washed about 2 feet 6 inches. Catarrh Creek also contained important shallow alluvial deposits, and there are numerous smaller occurrences in the district.

Of the Tertiary alluvial deposits some are still capped by lava, and in others the lava has been removed by denudation.

The most important deposit of the latter class is at the Y Water-holes. It has an area of 1,100 acres, and its average depth is about 20 feet. The deposit consists of current-bedded clay and sand, the richest ore occurring in the lower part and the next richest at the top, where the tin from denuded material has been concentrated. Scrubby Gully, Surface Hill and Ruby Hill are other examples of bare Tertiary deposits.

Of the basalt-covered Tertiary leads in the Emmaville district, by far the most important is the Vegetable Creek Lead. In portions of its course there are two distinct flows of lava, each overlying a bed of stanniferous wash dirt. The old stream had two main tributaries giving rise to the Rose Valley Lead and Fox's Deep Lead. The latter, at its junction with the Vegetable Creek Lead, was struck at 247½ feet from the surface, and is the deepest lead worked in the Emmaville district. At Bailey's Mine, Rose Valley, a stanniferous alluvial deposit is overlain by a felspar-porphyrity, the only known instance in Australia of a deep lead beneath an acid lava.

To the south of Vegetable Creek Lead is the Graveyard Lead, and the two leads probably unite about 6 miles west of Emmaville. From this point a strip of basalt-covered country runs northward to Kangaroo Flat and Avoca, where stanniferous drift has been worked, and it is probable that the lead will be found rich enough to be worked in intermediate localities.

Farther west are the Spring Lead, Rocky Creek Lead and Ruby Hill Lead, and to the east is the Wellington Vale Lead, near Deepwater.

Lode-mining for tin has been carried on in the Tingha and Emmaville districts. The lodes include fissure-veins, joint-veins, pipe-veins and stockworks, and occur chiefly in granite. The associated minerals are quartz, felspar, chlorite, mica, arsenopyrite, pyrite, fluorite, tourmaline, wolframite, galena, chalcopyrite, bismuth, molybdenite, vesuvianite, stilbite, hematite, pyrrhotite, manganese, scheelite and beryl. In most of the veins the ore shows a tendency to run in shoots inclined to the plane of the lode. The largest veins are the Ottery, Dutchman, Butler's and Curnow's veins, all of which are from 3 to 4 feet wide. Pipe veins are a peculiar feature of both the Tingha and Emmaville districts. They usually occur at the intersection of joints in granite, and are circular or oval in section, and up to 4 or 5 feet in diameter. They consist of quartz, felspar and chlorite, with disseminated

cassiterite, molybdenite, wolframite, etc., and pass gradually into unaltered country-rock.

Still farther to the north-east is the Wilson's Downfall district, which may be regarded as an eastward extension of the Stanthorpe tin field of Queensland. Shallow alluvial deposits have been worked in the Ruby, Maryland, Herding Yard, Cemetery, Wilson's Downfall, Wylie, Two-Mile and Bookookoorara Creeks.

In the Lachlan mining district, in the southern part of the State, is the important tin field of Ardlethan, about 40 miles west of Temora. It was discovered in 1912. Here the lodes traverse granite and schist, and usually consist of greisen or quartz-tourmaline rock. Topaz is sometimes abundant, and the cassiterite is associated with bismuthinite, molybdenite, wolframite, chalcopyrite, arsenopyrite, cerussite, pyromorphite, and zinc-blende. A hydrous arsenate of copper and iron is often present.

Among other localities in the central and southern parts of New South Wales may be mentioned Mount Tallabong, the Lachlan Valley, Burra Burra, Mandurah, Albury, Jingellic, Germanton, Tumbarumba, Wagga Wagga, Bungonia and Jindabyne.

In the Barrier district, in the extreme west of New South Wales, tin ore occurs at Euriowie and Poolamacca. At Euriowie cassiterite is found in coarsely crystalline dykes of granite and greisen traversing gneiss and mica-schist. The dykes are usually from 1 to 20 feet thick and terminate abruptly with rounded ends. Work in this field has been greatly hampered by scarcity of water and distance from any railway.

Small quantities of finely divided cassiterite, associated with zircon, garnet, ilmenite, monazite, gold and platinum, occur in some of the shore sands, notably between Byron Bay and Clarence Head, and in lesser quantities between Port Macquarie and Cape Hawke near Seal Rocks, and at Shell-harbour, Fernell etc.

Native tin has been recorded in washings from the Aberfoil and Sam rivers, near Oban, in grains from 0.1 to 1 mm. in diameter. More interesting economically are the considerable quantities of stannite at Howell (Bora Creek), near Inverell. This mineral also occurs at Folwong, near Bungonia. At Howell it is associated with galena, zinc-blende and arsenopyrite, and at Folwong chiefly with arsenopyrite and some chalcopyrite, galena and zinc-blende. Ore from the Conrad Mines at Howell was found to contain about 9 per cent. of

tin, 3 per cent. of which was present as a residue unattacked by all reagents and fluxes with the exception of potassium cyanide. To this residue, which is said to have the appearance of fine garnets and a composition expressed by the formula $7\text{SnO}_2 \cdot \text{Fe}_2\text{O}_3$, the name *conradite* has been given.

NORTHERN TERRITORY. The production of tin ore in the Northern Territory is small in comparison with other Australian States, averaging about 200 tons a year, but this is partly due to the undeveloped state of the country. The concentrates are sent to Singapore for smelting. The output in recent years has been as follows

Table 39

Value of Tin Ore produced in the Northern Territory

In £.

1910.	1911.	1912	1913	1914	1915 (1st half year).
34,113	24,900	27,001	25,520	15,400	5,545

Table 40

Output of Tin Ore in the Northern Territory

In ton (2,240 lb.)

	1911	1912		1911	1912
Horseshoe Creek and			Daly River	1	3
Mount Todd	40	40	The Noddy		3½
Emerald Hill	4	9	Hidden Valley	3½	1
Wolfram Camp	20	14	Umbrayarra	45	30
Fergusson	2	3	Maty River	7½	12
Burrundie	79½	10½	Stray Creek		5
Snadden's Creek	13	5½	Pine Creek	½	—
Mount Shooobridge	3	8½	Miscellaneous	1	—
The Finnis and Mt Tolmer	½	2½			
The Cullen		9			
West Arm and Bynoe Harbour	18	21	Total tons	239	270½
			Value, £	22,900	27,001

At Mount Wells, Burrundie, lode-mining is carried on, and fifty Chinese miners were employed in the early part of 1914. The mine has been producing since 1886. The lodes consist of quartz or pegmatite dykes intrusive in a shear-zone in chlorite schist, and may expand when followed into the granite.

Systematic development has, however, been neglected, and the mine is worked by Chinese tributers.

At Horseshoe Creek the lodes also cut chlorite schists. Here, as in other parts of the Territory, the Chinese miners have followed lodes down to the water level and then abandoned them, or picked out rich pockets without attempting to trace them to further deposits.

What appears to be an important tin field has recently been developed at Maranboy, at the heads of Beswick and Providence Creeks, in latitude $14^{\circ} 28'$ South, longitude $132^{\circ} 49'$ East. It is about 33 miles east of Katherine, a station on the Overland Telegraph Line. The lodes occur in pre-Cambrian tufts overlying granite, and consist of replacements of the tufts, in which cassiterite is associated with tourmaline or with quartz and chlorite. On the neighbouring King River cassiterite occurs in a quartz-tourmaline vein in tuff.

Hayes Creek and Rum Jungle are other localities in which tin ore has recently been found.

QUEENSLAND. Tin mining in Queensland began in 1872 with an output of 1,107 long tons of ore, followed by 8,938 long tons in 1873. The latter figure has never been exceeded, and the total output to the end of 1917 is 141,725 long tons of ore valued at £9,156,043. The following table shows the output of the different fields.

Table 41
Output of Tin Ore in Queensland

(In tons, 2,240 lb.)

	1912	1913	1914	1915	1916	1917.
Batavia River			0.5	0.008	0.15	—
Charters Towers	33.25	33.75	58.75	—	1	15.5
Chillagoe	5.1	197	228	320	186	104
Coen and Rocky					2	2.75
Cooktown	2.2	293	223	296.75	234.5	218
Croydon	15	6.5	32	—	—	—
Ethelridge	5	9.75	7	—	1	0.75
Herberton	191	1,861	1,011	1,164	821	541
Kangaroo Hills	193	206.5	103	120	130.5	70.5
Nanango	0.15	2.1	—	—	—	—
Palmer	37.5	31.75	18	29.25	17	10
Port Douglas		5.5	0.4	—	—	—
Ravenswood	33.25	37.5	27.5	175	4.5	—
Stanthorpe	106.75	240.75	211	181	309	214.5
Total . tons	3,230.15	3,197.35	2,085.40	2,124.83	1,706.65	1,177.06
Value	£ 894,593	343,069	176,107	183,472	181,401	160,600

All the tin fields are in the northern part of Queensland with the exception of Stanthorpe and Nanango, which are near the southern border.

The Herberton and Chillagoe tin fields are situated to the south-west of the port of Cairns, with which they are connected by railway. The Herberton field is traversed by the main dividing range of Queensland, while the Herberton Range on the eastern border prevents easy access to the coast. The rocks are slates, schists and quartzites with intrusions of biotite or hornblende granite, granite-porphxy and quartz felsite. Elvan dykes penetrate both the plutonic rocks and the altered sediments. The tin lodes occur in an irregular manner. The lode material as a rule merges gradually into barren country rock, and varies from unaltered granite or quartzite to greisen and chloritic or kaoline material. The cassiterite is often accompanied by topaz, fluorite, tourmaline, wolframite, bi-muthamite, antimonite, galena, chalcocite and magnetite. Alluvial tin was first worked in this district in 1880, and the discovery of lodes near Herberton and Watsonville soon followed. Irvinebank, Koorboora, Stannary Hills, Sunnymount, and Newellton are other important lode mining centres in these fields.

Farther north, in the Annan River tin field, south of Cooktown, the output is almost entirely stream tin, although lodes have been worked to some extent in a greisenised granite near its contact with slate. The district is one of rugged mountains, but the streams draining westward into the Annan River are held up by bars of harder rock, giving rise to an alternation of cascades and quiet reaches in which extensive alluvial deposits occur. Cassiterite is also found in alluvial terraces above the present stream levels, and in superficial deposits on the hillsides below the granite-slate contact. Some of the deposits have been worked continuously for tin since the opening of the field in 1885. To bring water to the higher terraces, races had to be constructed, often several miles in length; water supply is a most important factor in many of the Queensland fields, and a dry season leads to a diminished output of tin.

At Lode Hill, on the Bloomfield River, Cooktown district, the greisenised granite has been decomposed to a considerable depth. It is removed by hydraulic means, and is stated to yield on an average $1\frac{1}{4}$ lb. of tinstone per cubic yard.

In the Stannhills tin field, near Croydon, cassiterite occurs in veins in granitic rocks, and is associated with chlorite,

quartz, pyrite, galena, zinc-blende and chalcopyrite. The Desert Sandstone, which overlies the granite and forms isolated flat-topped hills, is stanniferous in places. Alluvial deposits have been worked, but these are not extensive and are of less importance than the lodes.

The Kangaroo Hills tin field, about 100 miles south of Herberton, produces lode and alluvial tin. Lodes have recently been discovered at Watercress.

Still farther south, in the Charters Towers district, a certain amount of lode-mining for tin is carried on, but the industry is quite overshadowed by the gold production of the district.

In the Stanthorpe district, near the New South Wales border, the first discovery of tin ore in Queensland was made in 1872. The alluvial deposits are still yielding good returns to hydraulic methods of extraction, and there is a little lode-mining, especially in the Ballandean portion of the district.

Cassiterite occurs, associated with gold, platinum and monazite, in the shore sands near Currumbin Creek, in the south-east of Queensland. Similar deposits are found on the coast of New South Wales.

SOUTH AUSTRALIA.—Cassiterite has been found in the bed of a lake near Eata Dam, about 30 miles south-east of Tarcoola. It occurs in decomposed granite dykes and quartz veins, and in the superficial deposits. There has been no production of tin ore.

TASMANIA.—The ore is smelted in reverberatory furnaces at Launceston. These furnaces yield metal assaying 90 to 95 per cent. tin, which is subsequently refined to an average purity of 99.80 per cent.

The principal mine in the Northern and Southern Division is the Shepherd and Murphy, near Middlesex, otherwise known as the Bismuth Mine. The lodes appear to be connected with a Devonian granite intrusion, and traverse (1) sandstone or quartzite, (2) lime-silicate rock resembling the Swedish "skarn" (see also p. 84), which consists of garnet, pyroxene and magnetite. These rocks are covered by Tertiary basalts. The lodes contain quartz, fluorite, topaz, beryl, a greenish hydrated mica and monazite, together with cassiterite, wolframite, bismuthinite, native bismuth, molybdenite, chalcopyrite, pyrite, arsenopyrite, and rarely galena. Scheelite, bismutite, calcite and stibite also occur. The tin, tungsten and bismuth minerals are of economic importance, and occur in the mill concentrates in approximately the following percentages: cassiterite, 53; wolframite, 30; bismuthinite, 7.

Table 42
Output of Tin Ore in Tasmania

In tons 20.4 lb.

	1922	1923	1924	1925	1926*	1927
TASMANIA						
Northern and Southern Division						72.43
North Eastern Division						631.22
Pioneer and Gladstone Districts						575.61
Ringboma District	9.735	75.96	62.18	72.75		42.4
Derby District	32.60	24.35	15	22.51		6.2
Bransholme District	52.38	54.25	25.1	34.89		86.975
Moona District	151.2	122.8	17.99	144.92		9.33
Streats Islands	64.7	6.9	4.16	32.5		201.55
Eastern Division	2.18	5.75	1.24	4.934		601.282
Weldborough, Lattah and Blue Eye Mines	45.1	24.4	15.4	12.84		25.34
St Helens Mines	42.5	23.88	12.5	12.84		
Avoca Mines	47.8	12.7	1.2	12.7		
Schantons	1.25					
North Western Division	1,387.29	1,761.74	827.5	673.9		
Western Division	228.335	355.11	294.8	292.18		
Total	3,713.26	4,174.1	2,822.713	4,594.84	2,510.96	2,632.337
Value	543,105	831,973	251,3	222,72	337,852	427,917

* Details not available copies of the Report intended for England having been lost at sea

the remainder being pyrite, magnetite, quartz and fluorite. The concentrates are treated at Launceston by Wetherill magnetic separators. These give a wolfram concentrate containing 70 per cent tungstic acid and 0.7 per cent. tin, and a non-magnetic product containing 56.3 per cent. tin, 8 per cent. bismuth, and 0.7 per cent. tungstic acid. This product is shipped to England, where the bismuth is extracted and the residue smelted as a tin ore. The Wetherill separations of mill concentrates from the deeper, unoxidised ores are carefully roasted and again passed through the separator to eliminate the pyrite and other minerals which are sometimes intimately mixed with the valuable ores.

The chief output of tin ore comes from the North-Eastern and North-Western Divisions. In the former are the Pioneer Mine, which produced 368 tons of ore in 1912, and the Briseis (Derby District) with 538 tons in the same year. Both these mines are on the Ringarooma River and work deep leads. At the Pioneer the overburden is 40 feet thick in places, and consists of cemented material which has to be blasted. The Briseis was discovered in 1872. Here the cassiterite occurs in a coarse quartz sand overlain by a sheet of olivine-basalt which is generally so decomposed as to be removable by hydraulic methods. Water has been brought from a distance of over 30 miles, and recently the river and main road have been diverted in order to follow the lead across the old river channel.

At Gladstone, lower down the Ringarooma River, alluvial and lode workings yield tinstone, often associated with gold and wolfram. The lodes occur near the junction of the Mount Cameron granite with Palaeozoic slates; and the alluvial deposits have been in part re-distributed by marine action during a comparatively recent depression of the country beneath the sea.

In the Eastern Division the Anchor is the chief mine in the Blue Tier district. The rock worked is a tin-bearing granite averaging $\frac{1}{2}$ per cent. cassiterite. The biotite of the ordinary Blue Tier granite is altered to muscovite and talc, much of the feldspar is kaolinised, and cassiterite, wolframite, scheelite, fluorite, pyrite, molybdenite, galena and chalcopyrite occur. Farther south, in the Ben Lomond and Avoca districts, tin lodes occur in granite. The overlying grits and conglomerates of Permian-Carboniferous age contain water-worn fragments of the granite and of quartz and cassiterite, and form one of the most ancient deposits of detrital tin hitherto

recorded. In the Scamander district cassiterite and wolframite occur in lodes.

The North-Western Division contains the most important tin mine in Tasmania, the Mount Bischoff, which produced 1,110 tons of ore in 1912. The mine was discovered in 1871 and the output to the end of 1914 was 72,500 tons of ore. It is situated 45 miles from the north coast at Emu Bay. Mount Bischoff consists of contorted slaty rocks traversed by dykes of quartz-porphry, while the surrounding plains are largely formed of sheets of basalt. The porphyry dykes carry topaz and cassiterite, and there are fissure veins containing cassiterite, pyrite, arsenopyrite, fluorite, wolframite, tourmaline and siderite. Disintegration of the slaty rocks has given rise to extensive residual deposits in which the cassiterite is concentrated, known as the Brown Face, White Face, etc., and small alluvial deposits also occur.

In the Western Division is the North Dundas tin field, including the Rem-on-Bell, Dreadnought-Boulder and Montana mines. Here the Dundas Slates were cut, probably in Devonian times, by dykes of quartz porphyry and basic igneous rocks, and by various types of veins. In some of the veins cassiterite is associated with quartz and tourmaline, or with quartz alone, in others with sulphides. Of these pyrrhotite is the most abundant, though pyrite is often present in large amount, and arsenopyrite, chalcopyrite, galena and zinc-blende are usually seen. Quartz and dolomite are the chief gangue minerals, with smaller amounts of tourmaline, chlorite, epidote and fluorite. The alluvial deposits contain cassiterite and chromite, with traces of gold and o-murchum.

Immediately to the east of the North Dundas field, in the X River district, the same types of lodes occur.

In the Zeehan field, nearer the west coast, a variety of veins are found, some of which carry tin. Both cassiterite and stannite are often present, associated with pyrite, chalcopyrite, bismuthinite, tetrahedrite, wolframite, galena, quartz, tourmaline, siderite and fluorite.

In the Heemskirk district the primary tin deposits are veins in granite and the overlying slates and sandstones. Quartz and tourmaline are the usual vein minerals. An interesting occurrence is an irregular pipe-like body at the Federation Mine. This was followed for a distance of 115 feet, and its cross section diminished from 25 by 15 feet near the surface to 5 by 1 feet at the deepest point exposed. The pipe consisted of soft greenish-grey material resembling pinitite, with

abundant cassiterite and pyrite, and these minerals, together with quartz and tourmaline, occurred also in the surrounding zone of altered granite.

The tin lodes of the Stanley River and Mount Balfour districts are similar to those of the Heemskirk and North Dundas tin fields.

VICTORIA. Victoria has a low output of tin ore as compared with most of the other States in the Commonwealth. The localities producing ore in recent years are given below :—

Table 43
Output of Tin Ore in Victoria
(In tons (2,240 lb.)

	1914	1915	1916	1917	1918	1919
Beechworth	10	200	2	11.25	24	11
Chiltern	5.25					4.5
Diggers Creek					6.1	
Eldorado		5.5	1	7.5	8.5	105.5
Eskdale	5	0.25	0.25			
Glen Wills			6			
Koetong		1.5	1.5			3.2
Lightning Creek	0.3					
Mitta Mitta						1.5
Myrtleford	5.5	2.25	5.2			
Rutherglen	1.05					3.75
Sunnyside		1.05				
Surveyor's Creek		1.15	0.85			
Tallandoon	1	1.5	0.5			
Toora	1.35	1.5	20.25	0.75	11	9.5
Walwa	8.25	8.5				
Total . . . tons	1.9	57.15	52.6	95.5	122	138.95
Value . . .	5.35	6,080	1,985	9,147	12,955	10,769

Most of the Victorian tin ore is from alluvial deposits, many of which yield both cassiterite and gold. Stream tin occurs at Glen Wills, Beechworth, Eldorado, Chiltern, Stanley, Rutherglen, Koetong, and Cudgewa, in the North-Eastern District; at Toora, Tin Creek and Agnes River in Southern Gippsland; near Bruthen in Eastern Gippsland; at Gembrook, Neerim, Darnum, the Bunyip and Tarago Rivers in Western Gippsland; Upper Yarra, and other districts. Tin-bearing lodes, some of which have been worked, are known at Mount Cudgewa, Mount Wills, Pilot Range, Mitta Mitta, Eskdale and Tallandoon in the North-Eastern District, and Mount Singapore on Wilson's Promontory, in Southern Gippsland.

WESTERN AUSTRALIA.—The most important tin fields of Western Australia are those of Greenbushes and Pilbara, which have produced about 9,700 and 5,300 tons of ore respectively to the end of 1916. In 1913 a small production was reported at Murchison and Coolgardie, and other occurrences are known in the Kimberley district and on the Thomas River in the Gascoyne valley. The output of black tin reported to the Mines Department during the years 1912 to 1916 is given below.

Table 44
Output of Tin Ore in Western Australia

In tons (1,000 lbs.)

	1912	1913	1914	1915	1916	1917
Greenbushes Mineral Field	139.15	158.18	241.54	247.33	281.74	
Pilbara Gold Field (Marble Bar District)	124.38	139.10	87.43	28.05	154.17	
Murchison Gold Field (Cue District)						
Coolgardie Gold Field (Coolgardie District)		15				
Total Value	tons	583.83	600.93	349.94	325.88	444.91
		66,180	6,771	3,513	29,061	43,258

The Greenbushes district is in the south-west of the State. Cassiterite occurs in pegmatite and quartz tourmaline veins and impregnations in granite. This is covered by lateritic alteration products, which in places contain concentrated residual tin ore. This material usually requires crushing. More important sources of tin are the alluvial deposits in the stream valleys. The richest of these is in Spring Gully, where an upper layer of sand, known as "free dirt," rests on stiff white "clayey dirt." The former is particularly rich in tin-stone. Tantalite and stibio-tantalite occur with the cassiterite in some of these deposits.

About twelve miles south of Greenbushes, tin ore has been obtained at Nannup or Smithfield.

In the Pilbara district, in the north-west division, tin ore is produced at Moolyella, Cooglegong, Old Shaw (Eley's Well), Green's Well, Wodgina, Stannum, and Mill's Fmd. At all these localities the original source of the cassiterite is the pegmatite veins which traverse granite and metamorphic rocks. At Wodgina, where, unlike most other tin fields in the State, the output of lode tin has exceeded that of stream tin, the

lodes vary from mere threads to masses over 500 feet in width and carry tourmaline and tantalite. At Moolyella the pegmatite veins consist largely of albite. From these sources are derived the shallow alluvial and residual deposits which, in most localities, have yielded the greater part of the tin produced. Tantalite, monazite, gadolinite and euxenite are occasionally found with the cassiterite in these deposits.

At the King's Sound Tin Mine, West Kimberley, narrow veins of quartz in a slaty rock contain scorodite (hydrous arsenate of iron), with cassiterite and wolframite in varying but usually small amounts.

NEW ZEALAND. There is no production of tin ore in New Zealand. Table 45 shows the imports of tin, which is mainly of Australian origin. The importation of tinned plate has practically doubled between 1910 and 1916, reaching 6,584 tons in the latter year, the plate is mainly English, though increasing quantities have come from the United States in recent years.

Table 45
Imports of Tin into New Zealand
In cwt. (112 lb.)

Countries whence Imported *	1910	1911	1912	1913	1914	1915	1916	1917.
United Kingdom .	1,011	1,119	953	1,256	2,745	981	594	250
Australia .	2,030	2,770	3,214	2,520	2,075	2,267	2,512	2,702
Other countries .			5	2	5	5	-	-
Total . cwt.	3,041	3,910	4,172	3,787	5,025	3,253	3,016	2,952
Value .	2,288,760	3,040,000	4,150,000	4,150,000	4,450,000	2,630,000	2,922,000	3,090,000

* Countries whence imported in 1910-13, countries of origin in 1914-17.

Stream tin has been reported from various localities near the west coast of the South Island, as at the foot of Mount William Range, at Karama, Mokihimu, Canoe Creek and Clarke River. It has been found in the sluice-box concentrates from auriferous gravels at Wamangaroa and the Blackball district. One sample from the latter locality was found to contain 33.3 per cent. of metallic tin. "Tin crystals" (probably cassiterite) are recorded at Slaty Creek and in the vicinity of Lake Brunner, and "tin" is said to occur in the Thames subdivision, Hauraki, Auckland. Stream tin and lodes also occur near Port Pegasus in Stewart Island. No deposits of economic value appear to be known.

CHAPTER III

SOURCES OF SUPPLY OF TIN ORES *(continued)*

(b) FOREIGN COUNTRIES

EUROPE

AUSTRIA-HUNGARY—The tin-bearing lodes of Bohemia will be dealt with under Germany (p. 78), as they are closely connected with those on the Saxon side of the Erzgebirge. Though once important, their output in recent years has been insignificant, as Table 46 shows.

Table 46

Output of Tin Ore and Tin in Austria-Hungary

In metric tons (2,204 lb.)

	1910	1911	1912	1913
Output of tin ore . . .	37	913	605	939
" tin . . .	49	15	13	11
Value of the ore . . .	96	3,289	4,592	—

The above figures represent low-grade ore, not concentrates, the value being under £8 per ton.

Tables 47 and 48 give the imports and exports of tin for Austria-Hungary. The trade was chiefly with Germany, but the imports from the Straits were nearly as large as the German imports in 1913.

Table 47
Imports of Tin into Austria-Hungary
In metric tons (2,204 lb)

Countries whence Imported	1910	1911	1912	1913.
United Kingdom	288	227	178	116
British Indies	1,706	1,750	1,831	1,908
Germany	2,321	2,401	2,553	2,000
Holland	103	180	110	77
Dutch East Indies	70	100	60	60
Other countries	126	17	74	44
Total, metric tons	4,674	4,795	4,806	4,214
Value	£ 31,100	93,071	1,001,250	842,820

Table 48
Exports of Tin from Austria-Hungary
In metric tons (2,204 lb)

Countries to which Exported	1910	1911	1912	1913.
Germany	400	553	608	827
Other countries	109	206	130	234
Total, metric tons	509	759	1,038	1,061
Value	£ 73,065	131,770	199,007	191,590

FRANCE.—The production of tin ore in France has been small and erratic, the last output, apparently, being 22 tons from Montebrias in 1909. There is, however, a small tin-smelting industry. The imports and exports of ore and metal are shown in the following tables.

Table 49
Imports of Tin Ore into France
In metric tons (2,204 lb)

Countries whence Imported	1910	1911	1912	1913	1914	1915.	1916.
United Kingdom	*	74	540	374	103		
Chile	1,280	1,814	1,136	1,932	1,983		
Peru	274	771	82	32	125		
Indo-China	372	211	171	128	123		
Other countries	78	113	128	338	211		
Total, metric tons	2,004	2,083	2,057	2,804	2,545	205	445
Value	£ 72,144	110,420	89,694	121,128	86,537		

* Not stated.

FRANCE

77

Table 50
Imports of Tin into France

In metric tons (2,204 lb.)

Countries whence Imported	1910	1911	1912	1913	1914	1915	1916
United Kingdom	2,333	1,852	1,527	1,590	11,962 [†]		
British Indies	5,053	4,991	5,029	5,014	(2,065)		
Germany	1,082	1,231	760	838	(895)		
Holland	425	366	419	419	(685)		
Dutch Indies	1,236	1,731	1,811	1,190	(702)		
China			811	611	(1,145)		
Other countries	670	5,010	1,008	233	(205)		
Total, metric tons	10,803	13,266	13,114	13,485	19,692	10,200	12,068
Value	£ 1,655,298	2,100,490	2,141,811	2,230,143	1,431,041		

* Not stated.

† The figures in brackets represent tin in metric tons for consumption.

Table 51
Exports of Tin Ore from France

In metric tons (2,204 lb.)

Countries to which Exported	1910	1911	1912	1913	1914
United Kingdom	590	547	911	1,147	393
Belgium	167	241	170	104	193
Germany	408	455	222	151	309
Other countries	20	111	68	35	
Total, metric tons	1,185	1,355	1,371	1,437	895
Value	£ 11,554	95,200	96,220	61,940	39,427

Table 52
Exports of Tin from France

In metric tons (2,204 lb.)

Countries to which Exported	1910	1911	1912	1913	1914
United Kingdom	1,815	1,765	822	924	819
Belgium	35	65	52	31	53
Germany	63	172	65	*	42
Holland	226	96	46	151	46
Italy	347	172	511	382	413
Russia	327	419	132	506	486
Spain	147	190	265	224	221
Switzerland	338	151	131	203	212
United States	*	467	851	570	77
French Colonies	57	131	143	169	121
Other countries	91	190	92	131	69
Total, metric tons	3,649	3,778	3,429	3,495	2,559
Value	£ 1,569,182	710,245	699,496	663,469	409,594

* Not stated.

In Brittany lodes occur in granite and slate, as in Cornwall. The chief minerals present are quartz, cassiterite, apatite, fluorite, molybdenite, arsenopyrite, pyrite, zinc-blende, chalcopyrite, and galena. Topaz and tourmaline are of rare occurrence, and wolframite is absent. At La Villeder, south-west of Ploermel, in Morbihan, mining was carried on from 1856 to 1863 and again from 1880 to 1886. Lodes also occur at Piriac, in Loire-Inférieure, and at Montebbras, Vaulry, Cieux and other localities on the Central Plateau. At Montebbras the lodes have been worked at various times; they occur in a fine-grained granite, and many of them are rich in phosphates such as apatite, wavellite, and amblygonite.

GERMANY — Tin-mining in the Erzgebirge was an important industry in medieval times. Now, however, the lodes on both the Saxon and Bohemian sides of the range are practically exhausted. Table 46 (p. 75) shows the Austrian output in 1910-1913, and for Germany the output was 125 metric tons of ore in 1910 and 116 in 1911, valued at £2,800 and £5,850 respectively. In 1912 the output of tin ore was included with that of cobalt, nickel and bismuth ores.

Before the war Germany had a considerable tin-smelting industry based chiefly on Bolivian ore. Tin was imported from the Dutch Indies, the Straits Settlements, Australia, the United Kingdom, and elsewhere, and the imports of tin-plate from the United Kingdom amounted to 48,061 metric tons in 1912.

The exports of tin, as shown in Table 55, were mainly to the United States and the countries bordering on Germany.

Table 53
Imports of Tin Ore into Germany

In metric tons (2,204 lb.)

Countries whence imported	1910	1911	1912.	1913.
United Kingdom	34	320	102	82
Australia	7	4	480	1,015
Bolivia	15,025	15,227	13,296	15,831
Chile	914	1,874	914	868
Other countries	403	536	1,765	940
Total, metric tons	17,343	17,961	16,557	18,736
Value	£ 1,335,450	1,796,050	2,069,650	2,342,090

Table 54
Imports of Tin into Germany
In metric tons (2,204 lb.)

Countries whence Imported	1910	1911	1912	1913
United Kingdom	1,393	1,524	1,614	1,697
British Indies, etc.	1,195	1,266	1,387	942
British Malaya, etc.	471	549	494	941
Hong Kong	10	5	21	*
Australia	1,129	1,114	1,519	1,661
Austria-Hungary	943	482	845	393
Belgium	529	517	517	297
France	86	21	104	74
Holland	67	7	33	509
Switzerland	59	133	180	91
China	394	117	53	142
Dutch East Indies	8,135	50	754	6,364
United States	82	115	674	929
Other countries	82	18	55	143
Total, metric tons	11,297	11,727	18,556	14,264
Value	£ 1,288,985	1,460,000	1,425,000	1,913,350

* Not stated

Table 55
Exports of Tin from Germany
In metric tons (2,204 lb.)

Countries to which Exported	1910	1911	1912	1913
United Kingdom	189	56	519	521
Belgium	957	712	345	595
France	1,174	1,277	711	929
Italy	522	616	334	338
Holland	366	119	387	227
Austria-Hungary	945	494	137	947
Russia	347	47	991	771
Switzerland	311	198	554	479
Spain	94	155	195	129
Turkey	84	213	207	198
Argentina	106	179	73	59
United States	2,159	1,777	1,394	1,041
Other countries	417	646	643	542
Total, metric tons	7,521	7,606	6,368	6,437
Value	£ 1,169,550	1,239,350	1,054,100	1,166,800

The principal tin deposits of Germany and Austria are those on both sides of the Erzgebirge, where tin-mining commenced

in the twelfth century. The lodes are connected with two granite intrusions which cross the range from Saxony into Bohemia, and they occur chiefly in the upper part of the granite and in the overlying phyllite, gneiss and porphyry, the deeper and more central portions of the granite being barren. Thus at Altenberg the ore was followed to a depth of 760 feet, below which it was no longer worth working. The ore here is in the form of a stockwork, with innumerable small veins or *Zwitter* bands. Farther south, at Zinnwald, flat lodes (*Flöze*) and gneiss yield tin, wolframite and lepidolite, the last named having been worked as a source of lithia. At Graupen, on the Bohemian side of the range, orthoclase and fluorspar are abundant in the vein material, with topaz in the adjacent rock. Farther west are the lodes of Geyer and Ehrenfriedersdorf.

At Berggesslhubel, near the eastern end of the Erzgebirge, thin veins of orthoclase, quartz, fluorspar and cassiterite occur in altered limestone bands near a granite intrusion.

Tin lodes were formerly worked in the granite of the Fichtelgebirge, at Weissenstadt and elsewhere.

HOLLAND. — Holland is important, not as a producer or large smelter of tin ore, but as the distributing centre of the greater part of the tin produced in the Dutch East Indies. Tables 56 to 59 show the imports and exports of tin and ore. Small amounts of ore, mostly Bolivian, were imported in the years preceding the war, but this is insignificant in comparison with the metallic tin. Practically the whole output of tin in Banka was sold in Holland, and there were also imports from the

Table 56
Imports of Tin Ore into Holland

In metric tons (2,204 lb)

Countries whence Imported	1910	1911	1912	1913	1914
United Kingdom	62	—	4	2	—
Australia	—	21	—	—	—
France	29	110	7	21	—
Germany	—	3	1	603	1
Chile	244	45	300	60	389
Dutch East Indies	—	—	20	5	20
Other countries	—	—	—	5	—
Total, metric tons	335	179	332	696	410
Value	£ 4,468	2,368	4,439	9,279	5,467

Table 57
Imports of Tin into Holland

In metric tons (2,204 lbs.)

Countries whence Imported.	1910	1911	1912	1913	1914
United Kingdom	2,718	1,924	1,319	3,926	2,969
Straits Settlements	707	771	1,557	505	511
Germany	2,600	3,010	1,122	1,309	867
Dutch East Indies	14,743	15,974	15,788	15,641	12,242
China	148	180	308	61	220
Other countries	791	513	1,491	682	110
Total, metric tons	21,676	24,155	23,613	27,124	16,909
Value	£ 1,806,357	2,030,011	2,013,611	1,816,650	1,490,360

Table 58
Exports of Tin Ore from Holland

In metric tons (2,204 lbs.)

Countries to which Exported	1910	1911	1912	1913	1914
United Kingdom	85		14		5
Germany	250	112	19	21	
Other countries					
Total, metric tons	283	112	189	21	5
Value	£ 1,767	1,887	2,570	231	72

Table 59
Exports of Tin from Holland

In metric tons (2,204 lbs.)

Countries to which Exported.	1910	1911	1912	1913	1914
United Kingdom	160	509	1,697	1,373	478
Belgium	1,389	1,270	1,639	1,369	762
France	329	305	270	249	255
Germany	13,463	13,680	13,751	12,945	10,128
Russia	1,875	2,225	2,319	2,665	1,614
United States	2,973	3,032	3,649	479	409
Other countries	599	779	780	697	869
Total, metric tons	19,885	21,066	24,099	18,787	14,455
Value	£ 1,657,992	1,451,731	2,068,230	1,565,626	1,204,667

United Kingdom and other countries. The greater part of the tin was re-exported, two-thirds going into Germany, and it was therefore necessary at an early stage in the war to limit the imports of tin into Holland to an amount sufficient for domestic consumption. According to the monthly statistics of the New York Metal Exchange, the tin deliveries in Holland in the years 1913-17 were 15,522, 12,025, 4,734, 943, and 962 tons respectively.

ITALY.—The production of tin ore in Italy is small, and was estimated at 20 tons in 1911 and 350 tons in 1912, all from one mine. The imports of tin are normally between 2,500 and 3,000 tons; in 1915 they rose to 4,245 metric tons, but became normal again in 1916. Some 30,000 tons of tin-plate is produced yearly.

At Campiglia Marittima, in Tuscany, iron and tin were mined in early times, and the deposits were re-discovered in 1871. Masses of cassiterite occur in veins of limonite, probably derived from pyrite, which traverse limestones and shales of the Lower Liass. The occurrence is of interest as forming almost the only example in Europe of tin deposits of Tertiary age, to which the great Bolivian deposits belong. In the neighbouring island of Elba specimens of cassiterite have been found in granites of Tertiary age.

PORTUGAL.—The Portuguese tin deposits will be described with those of Spain (p. 84), with which they are closely connected. The output in recent years is given below.

Table 60

Output of Tin Ore in Portugal

In metric tons (2,204 lb)

1910.	1911	1912	1913	1914.
9	85	196	254	370

RUSSIA.—Russia produces little tin, and her imports in normal years are between 5,000 and 6,000 tons. Table 61 shows the effect of the war on the imports. In 1915 the total was 42 per cent. greater than in the previous year, and nearly nine-tenths came from the United Kingdom; imports from Continental Europe practically ceased, and the only other imports of any significance were from Japan and the United States.

RUSSIA

Table 61
Imports of Tin into Russia

In pounds (30 lb)

Countries whence Imported	1912	1913	1914	1915
United Kingdom	97,272	106,818	141,775	151,239
Austria-Hungary	9,159	8,566	8,147	-
Belgium	1,806	5,921	2,828	-
France	10,789	11,278	10,467	-
Germany	12,337	112,271	70,870	1,380
Holland	84,892	83,724	81,331	3,017
Spain	4,100	19,773	7,599	-
East Indies	8,100	10,469	10,733	-
Japan	-	-	1,100	31,686
United States	2,514	-	490	11,078
Other countries	3,821	9,999	7,157	6,613
Total	pounds 345,341	368,148	348,899	191,613
	tons 10,550.1	11,044.6	10,666.0	5,799.9
Value	£ 6,291,904	£ 12,764,611	8,991,147	10,690,990

An extensive tin-plate industry formerly existed at Odessa, using black plate imported from Wales. Since 1903, however, this trade has decreased, owing to the discovery of suitable iron ore for black plate in the Urals near Perm. Modern works, copying those in Wales, were erected, and these Ural works now command the Russian market. There is still, however, a small tin-plate industry at Odessa. The tin-plate imported before the war was mainly from Germany.

In the Russian Empire tin deposits are known in the Trans-Baikal province, in the Urals, and in Finland. The Trans-Baikal deposits consist of lodes and placers near the villages Olovianoy Roudnik and Nizhni-Sharanai on the Onon River, and in the valleys of the Malaya Kouhinda and Ingoda, tributaries of the Onon. At Olovianoy, about 150 miles south-west of Nerchinsk, the lodes contain quartz and cassiterite, together with beryl, fluorite and lepidolite. They have been known since 1811, and were worked on a small scale between 1812 and 1835. In more recent years a German company was formed to exploit them.

The occurrence at Pitkaranta, north of Lake Ladoga in Finland, was worked from 1814 to 1904, during which period it is said to have yielded some 250,000 tons of iron ore, 6,617 tons of copper, 489 tons of tin, and 11.2 tons of silver. The ores consist of magnetite with some cassiterite and chalcopyrite.

and a little scheelite; they occur in altered limestones and schists, and particularly in a rock known as "skarn," which is made up of salite and garnet.

Tin deposits have also been reported in the Sosnowics and Dombroff basins in Poland.

SPAIN.—The tin-bearing gravels of the Iberian peninsula were worked by the Phoenicians and Romans, but at the present time neither the gravels nor the veins yield any large amount. The output given in Table 62 represents very low-grade material, the total value in 1912 being only £3,506, which is equivalent to about 1.4s. per ton. In normal years Spain imports about 1,400 tons of tin, chiefly from the United Kingdom and Germany.

Table 62
Output of Tin Ore in Spain

In metric tons (2,204 lb)

1910	1911	1912	1913	1914	1915	1916
35	34	5,079	6,626		102	86

The most extensive series of occurrences in the Peninsula are the lodes in a belt stretching north-westward from Zamora, across the north-eastern part of Portugal, into the province of Orense in Galicia. In this belt are the lodes of Penuta, Romilo, Verin, Monterey, Almaraz, Lumbriles, Viana del Bollo and Pontevedra in Spain, and those of Mirandella, Montesinhos, Parada, Coelho, Marao Angueta and Valle Seixo in the Province of Trás os Montes in Portugal. Other occurrences are those of Terrubias and Santo Tomé de Rozadas near Salamanca, San Isodoro and Marinera near Cartagena, near Almería on the south coast of Spain, and near Ramalhoso, Vizeu, and Belmonte in Portugal. In 1914 a bucket dredge was erected in the Gata valley near Belmonte (Beira Alta). The lodes occur in granite and schist. Wolframite is often abundant, either in association with cassiterite or in separate lodes.

ASIA

CHINA.—China exports some 8,000 tons of crude tin yearly, nearly all of which is sent to Hong Kong (Table 63). The industry is entirely in the hands of the Chinese, who smelt the

Table 63
Exports of Tin from China

In piculs (133½ lb.)

Countries to which Exported	1910.	1911.	1912.	1913.	Total.	1915.	1916.	1917.
Hong Kong	167,613	99,798	111,994	137,195	117,787	131,997	125,237	195,035
French Indo-China	17	331	293	72	162	18	98	515
Japan	—	—	186	1	187	73	—	288
France	—	2	—	2,191	1,199	—	—	—
United States	—	—	116	81	34	168	394	411
Other countries	—	—	—	185	—	19	157	88
Total	167,630	100,129	112,229	137,553	119,255	132,879	125,444	196,327
Value	84,902	50,175	57,211	69,855	72,907	78,017	75,311	116,856
				1,018,918	1,088,741	1,199,190	1,131,618	2,634,855

1914

Imports of Tin into China

In piculs (133½ lb.)

Countries whence Imported	1910.	1911.	1912.	1913.	Total.	1915.	1916.	1917.
United Kingdom	48	—	2	132	95	23	174	14
Hong Kong	9,378	11,112	8,199	49,814	96,602	31	47,388	41,421
Straits Settlements, etc.	3,956	3,112	1,897	2,117	2,085	1,307	2,051	991
Japan	—	222	—	235	177	126	441	571
Other countries	21	153	99	189	85	314	299	542
Total	14,422	33,257	10,197	53,127	95,517	41,73	51,313	43,469
Value	27,114	1,694	2,507	3,142	3,385	2,424	3,654	2,587
	228,123	105,425	239,638	351,023	396,113	266,599	434,575	561,478

ore in small furnaces and obtain a product containing about 90 or 92 per cent. of tin, part of which is sent to Hong Kong to be refined. In 1913 refining works of German design were completed near the Kochiu mines, but have not proved very successful.

The exports to Hong Kong do not represent the total output of tin in China, nor yet the quantity of Chinese tin which reaches the European and American markets. About one-third is returned to China in a refined state, as shown in Table 64. The imports of tin-plate into China are from 20,000 to 25,000 tons in normal years. Most of this was of British origin until recently, but in 1917 the United States supplied 68 per cent. of the total.

Some 90 per cent. of the tin exported is produced in the Mengtze district of Yunnan. Here are situated the Kochiu mines, 20 miles from Mengtze, which are worked by native methods and employ 30,000 men. The production of tin at these mines in the years 1912 to 1916 is said to have been 8,234, 7,636, 6,681, 7,495, and 6,862 tons respectively. In eastern Kwangsi are the Ho Yuan mines at Holsien and the Fuchuan mines; in Huai the mines of An Yuan, Lenshee and Shanwhaling; and in Hainan the Nuitsongling mines near Nodoo. The Kowloon extension, Hong Kong, also contains tin ore.

The tin lodes of Kochiu are said to be connected with pegmatite of post-Triassic age, and traverse limestones. Copper and iron sulphides, sometimes arsenical, occur at depth, but near the surface the limestone weathers to a red clay containing tinstone free from sulphides. At Fuchuan and Lenshee the ore is found in a sandy soil overlying granite near its junction with limestone. Pipes and caves in the limestone are also worked. The yearly output of the Fuchuan district is said to be about 150 tons of metal; it generally assays over 98 per cent. tin, and is used by the refiners in Hong Kong to improve the grade of the Yunnan tin. The workings at Shanwhaling follow pipes in limestone close to a granite intrusion; pyrrhotite and pyrite are abundant, and tourmaline, fluorite, zinc-blende and galena also occur.

In the Tungchwan district, Yunnan, a lode of stannite is worked. The metal obtained on smelting is known as perhtung or white copper, and contains 42.57 per cent. of tin, 49.7 of copper, 1.3 of sulphur, and 1.8 of lead.

DUTCH EAST INDIES.—The tin-producing islands of the Dutch East Indies are Banka, close to the east coast of Sumatra, Billiton, south-east of Banka, and Singkep, a small island

north-west of Banka. Sumatra also possesses tin deposits, especially in Siak. The output of the three islands is given in the following table:—

Table 65
Output of Tin in the Dutch East Indies
In tons (2,240 lbs.)

	1915	1916	1917	1918	1919
Banka	19,374	18,489	14,853	14,437	14,229
Billiton	4,490	4,981	4,282	4,049	5,111
Singkep	399	853	673	601	821
Total	24,263	24,323	19,808	19,087	20,161

According to *The Ironmaster Metal Market Year Book* the production in Banka was 13,229 tons in 1915-16 and 14,522 tons in 1916-17, while that of Billiton was 5,691 tons in the former year.

In Banka tin mining is carried on by the Government. The ore deposits are almost exclusively alluvial and are worked in open pits by Chinese coolies, either under contract or under direct Government supervision. The ore is smelted locally in blast furnaces, or sent to central smelters which exist in some districts. Before the war Banka tin was all sold by auction in Holland, with the exception of small amounts sold in Batavia or used for Government services. To prevent the tin reaching Germany during the war, the supplies to Holland were limited by the Allies, and much of the Banka tin came direct to England and the United States. In Billiton and Singkep private companies work the tin deposits, and a large part of the ore obtained is smelted at Singapore.

The three islands lie on the south-easterly extension of the axis of the Malay Peninsula. The primary tin deposits are in granites and ancient sediments, and consist more of impregnations than true veins. The granite enclosing them is altered to greisen containing cassiterite and topaz, while the veins contain cassiterite, pyrite, wolframite, tourmaline, magnetite and sometimes siderite.

There is some lode mining, but most of the tin ore is obtained from detrital deposits. These are of two kinds: *kulit*, or eluvial deposits on the hillsides, and *kollong*, or alluvial deposits in the valleys. The former result from the weathering of the

rocks almost *in situ*, and sometimes contain great masses of cassiterite weighing nearly a ton. In the valley deposits the tin is practically confined to a rich zone known as *kaksa*, which rests immediately on the bed-rock (*kong*) and is covered by barren sand and clay to a depth of 12 to 50 feet. The *kaksa* is commonly from 4 to 10 inches thick, though it may be as much as 3 feet. It consists chiefly of grains and blocks of quartz with some clay, and contains tourmaline, muscovite, hornblende, topaz and corundum, as well as cassiterite, wolframite, scheelite, magnetite, monazite and sometimes gold. This material, which often contains 2 to 4 per cent. of cassiterite, is washed and concentrated to a 68-73 per cent. metallic tin content, and the concentrate is often smelted on the spot. Some lode-mining is carried on in Billiton, and off the coast of Singkep stanniferous deposits are worked by dredges. In addition to tin, Billiton yields some wolfram ore and Singkep a little gold.

Tin mining in Banka began in 1718, and the island is said to have yielded some 500,000 tons of tin up to the present. The Billiton deposits were not exploited on a large scale till the middle of last century, and those of Singkep about thirty years later.

INDO-CHINA.—This French colony produces small amounts of tin ore, part of which is smelted locally and part exported to France and elsewhere. A large amount of crude tin from Yunnan also passes through the country on its way to the refineries at Hong Kong. No production figures are available, but the exports are given below.

Most of the tin ore comes from the neighbourhood of Kao-Bang, in the north of Tonkin, where it occurs with wolfram ores in cluvial and alluvial deposits. These are derived from veins of quartz with cassiterite and wolframite in granite.

Table 66

Exports of Tin Ore (of Domestic Origin) from Indo-China

In metric tons (2,204 lb.)

Countries to which Exported	1910	1911	1912	1913.	1914.
Hong Kong	--	6	50	33	11
France	153	236	84	94	61
Belgium	7	--	8	50	10
Total	160	242	142	177	82
Value	6,423	9,700	5,687	7,076	3,293

Table 67

Exports of Tin (of Domestic Origin) from Indo-China

In metric tons (2,204 lb.)

Countries to which Reported	1910	1911	1912	1913	1914
Hong Kong	17	1	—	287	—
France	98	1	2	58	10
Other countries	—	—	3	—	—
Total	115	2	5	345	10
Value	£ 17,702	302	720	53,120	1,591

Table 68

Exports of Yunnan Tin in Transit to Hong Kong, etc.

In metric tons (2,204 lb.)

	1910	1911	1912	1913	1914
Quantity	5,600	6,352	8,010	6,610	4,645
Value	£ 78,004	97,932	108,184	1018,003	715,352

Tin ore occurs also at Ban-ta-coua in Laos, in what appears to be an ancient alluvial deposit. Although water-worn, it is very impure; it is intimately mixed with limonite, and contains also arsenic, bismuth, molybdenum, lead and copper. The natives sink small shafts 30 feet deep or less, crush and pan the ore, and smelt it to a tin with 10 or 20 per cent of impurities, or even to a tin-iron alloy which they use for weighting nets, etc.

JAPAN.—Japan has a small output of tin ore, but this meets only a fraction of her requirements, and about 1,200 tons of tin and 25,000 tons of tin-plate are imported in normal years. The following tables give the statistics so far as they are available:—

Table 69

Output of Tin Ore in Japan

	1910	1911	1912
Quantity, metric tons (2,204 lb.)	23	352	410
Value	£ 3,579	24,222	37,476

Table 70
Imports of Tin into Japan

In km (1,3228 lb.)

Countries whence Imported	1911	1912	1913	1914 *	1915 *	1916 *	1917 *
Hong Kong	99,932	124,753	142,740	—	—	—	—
Straits Settlements	1,570,418	1,615,813	1,384,091	—	—	—	—
China	141,187	135,760	346,680	—	—	—	—
Other countries	53,821	129,126	82,350	—	—	—	—
Total km	1,851,801	2,005,452	1,955,779	2,183,703	1,959,540	1,839,109	3,377,701
Value tons	1,091	1,185	1,150	1,290	1,175	1,086	1,995
Value £	196,595	211,516	210,865	210,609	186,697	183,397	385,954

* Detail not available

The chief mine is that of Taniyama in the province of Satsuma. Other mines in the extreme south (Kyushu) are those of Nagao in the province of Osumi, Iwato and Mitate in Hyuga, and Kiura in Bungo, while there are productive placer deposits at Taniyama and, nearer to the centre, at Nayegi in Mino and at Sudzukoya in Hitachi.

At Taniyama the veins traverse a Tertiary tuff; they average about a yard in width, and some reach a length of one mile. They consist of quartz with cassiterite and varying amounts of galena and pyrite. These veins have been worked almost continuously since 1955.

The veins near the border of Hyuga and Bungo appear to be connected with a quartz-porphry which cuts Palaeozoic limestones and quartzites. They are composed chiefly of pyrrhotite, sometimes with arsenopyrite, chalcopyrite or zincblende, while cassiterite occurs in quartz veinlets.

In the alluvial deposits of Nayegi in Mino the cassiterite is found close to the granite bed-rock, and is associated with quartz, topaz, corundum, wolframite, fergusonite, etc.

SIAM.—The tin deposits of Siam form part of the great tin-bearing belt which stretches from Banka through the Malay Peninsula into Burma, and are connected with the granite of the Main Range which forms the watershed of the peninsula.

As in the Malay States, the chief production is from detrital deposits on the west side of the Main Range, in Monthon Puket, while the east-coast Monthons of Chumporn, Nakorn Sitamarat and Patani produce far smaller amounts. Tin ore also occurs in small amount in the valley of the Nam Sak river and other places in the north of Siam.

In the year 1916-17 the output of dredging operations

amounted to 32 per cent. of the total production. The following table shows the output of tin by provinces.—

Table 71

Output of Tin in Siam in the years ending March 31, 1911-1917

In piculs (133 lb.)

Months	1910-11	1911-12	1912-13	1913-14	1914-15	1915-16	1916-17
Chumporn	2,782	2,911	3,007	2,858	3,427	2,259	2,278
Nakorn Sitamarat	2,517	1,479	1,594	2,150	2,025	2,402	3,053
Patani	6,297	8,983	6,067	8,351	7,980	15,199	10,689
Puket	70,719	87,351	90,001	100,297	98,400	99,004	130,739
Total	piculs 82,255	99,622	109,669	113,356	112,731	118,864	147,259
	tons 4,896	5,933	6,358	6,548	6,501	6,900	8,765

Table 72 shows the amounts contributed by the various Muangs in the Monthon of Puket to the total exports, treated as metallic tin.

Table 72

Exports of Tin from the Monthon of Puket in the years ending 31st March, 1911-14

In tons (2,240 lb.)

Muangs	1910-11	1911-12	1912-13	1913-14
Puket	2,483	3,000	3,547	3,793
Pangnga	65	63	27	84
Renong	192	59	297	688
Takuapa	52	53	51	53
Trang	123	178	210	205
Setul				
Total	4,083	5,199	5,951	5,970

AFRICA

BELGIAN CONGO.—To the north of the copper-bearing belt of Katanga a tin-bearing belt extends in a north-east and south-west direction for over 100 miles. Promising deposits are known at Busanga, Muika, Kiambi, Muanga and Mulongo, and development work has been done at some of these localities. The cassiterite occurs, often in large crystals, in veins of quartz

and pegmatite cutting schist and granite. The Muika mine is said to have produced 10 tons of concentrates a month at the beginning of 1914, but operations were suspended on the outbreak of war.

At the Busanga ridge, between the Lualaba and Lufupa rivers, tin-bearing quartz veins occur in schist. Disintegration of the rocks has produced a mass of loose material fairly rich in tin.

PORTUGUESE EAST AFRICA.—Some of the concentrates from stream deposits in the territory of the Companhia de Moçambique, examined at the Imperial Institute, were found to contain small amounts of cassiterite. The streams in question flow over foliated granite. A recent discovery at Chimoio is said to be important.

SOUTH-WEST AFRICA.—This former German colony produced tin ore to the value of £31,568 in 1913. The tin-bearing belt extends from Otjumboyo, on the Khan River north-east of Karabib, through the Erongo Mountains in a north-westerly direction to Uis, which is east of the Brandberg and about fourteen miles south of the Ugab River. Cassiterite was first discovered in 1910 at Ameib, south of the Erongo Range, and further discoveries soon followed at Dawib, Aubinhonis, Tsomtsaub, Neiners, Uis, Kawab, Otjumue and Kohero East. At all these localities the mineral occurs in pegmatite intrusive in the ancient rocks and genetically connected with the older granites of the Erongo area. The pegmatite is usually a coarse-grained rock composed of quartz, feldspars and pale greenish-white muscovite. The accessory minerals include tourmaline, garnet, magnetite and apatite, together with beryl at Ameib, wolframite, monazite, columbite and molybdenite at Dawib, and lepidolite at Kohero East. Tourmaline and cassiterite rarely occur together in the pegmatite. The cassiterite occurs sporadically in large grains and crystalline masses, sometimes of very large size, one mass found at Dawib having weighed 500 lb.

The results obtained from the opening up of the veins have been somewhat disappointing, owing to the patchy distribution of the ore in the pegmatite and the way in which many of the veins die out at comparatively shallow depths. The Kohero East Mine, however, was successful in producing about 120 tons of concentrates, averaging over 70 per cent. of metallic tin, before the outbreak of the war. This mine was only worked to a depth of 92 feet, below which the pegmatite disappeared completely.

Alluvial deposits and "float," formed from the erosion of the stanniferous pegmatites, occur at Chatputz (north-west of Ameib), Otjimboyo, Tsomitsaub, Aubinhonis, Neineis and Kawab. In general they were found to be poor and of slight extent, and most of the good ground appears to have been worked out. Occasional nuggets of gold were obtained at Neineis, Aubinhonis and Chatputz, and at the last-mentioned locality a large storage dam, to supply water for hydraulic working, was erected in 1913, but was destroyed during the recent campaign.

AMERICA

BOLIVIA.—Tin mining in Bolivia only began late in the nineteenth century, but the country now ranks second among producers. The output increased steadily up to 1913, and the export of barilla (tin ore concentrate containing about 60 per cent. metallic tin) in recent years is shown in Table 73:—

Table 73
Exports of Tin Ore (Barilla) from Bolivia
In metric tons (2,204 lb.)

	1910	1911	1912	1913	1914	1915	1916	1917
Barilla	38,518	37,773	35,370	34,594	33,259	30,324	35,097	45,418
Tin contents estimated at 60 per cent.)	23,129	22,241	21,227	20,759	22,155	21,794	21,058	27,251

According to the British Legation at La Paz (*Met. Ind.* 1918, 18, 27) the destination of the tin ore exported is as follows:—

Table 74
Exports of Tin Ore from Bolivia
In metric tons (2,204 lb.)

Country of Destination	1914	1915	1916	1917
United Kingdom	35,957	35,358	32,569	Official figures not available.
Germany	1,111	28	—	
United States	26	1,191	2,884	
Other countries	168	5	1,690	
Total	37,259	36,492	36,543	45,000

Only a small amount of metallic tin was smelted in Bolivia in the years preceding the war, the bulk of the barilla being shipped from Antofagasta, Mollendo and other Pacific ports. Most of it was sent to the United Kingdom, but a considerable amount went to Germany. The exports to Germany, which in 1913 amounted to about 35 per cent. of the total production, ceased on the outbreak of war. A fresh market for this ore was found in the United States, which took increasing amounts of the Bolivian exports in 1915 and 1916, most of the remainder going to the United Kingdom. Smelting works for Bolivian ore were erected at Perth Amboy, New Jersey, and others at Arica in Chile and La Paz in Bolivia.

The Bolivian tin mines are situated on the Eastern Cordillera and the high plateau between the Eastern and Western Cordillera, some of them being over 17,000 feet above sea-level. Three-quarters of the production come from the department of Potosi, and the most important mining centres, from north to south, are Araca, Oruro, Machacamarca, Huanuni, Llallagua, Uncia, Potosi, Sala Sala, Chocaya and Chorolque. The Uncia and Llallagua mines together produce over 40 per cent. of the total. The tin is often associated with silver ores, especially in the southern districts, and is connected with eruptive rocks of Tertiary age. The most important gangue mineral is quartz, which is sometimes accompanied by calcite and barite, but tourmaline, fluorite, topaz, apatite and lithia-mica are either absent or rare.

In addition to cassiterite and the silver minerals tetrahedrite, pyrargyrite, proustite, etc., there occur also pyrite, arsenopyrite, pyrrhotite, chalcopyrite, stibnite, galena, zinc-blende, stannite, bournonite and bismuth minerals, as well as the rare tin-bearing minerals plumbostannite, canfieldite, cylindrite and frauckeite. The element germanium is present in the last three minerals and in argyrodite. The lodes have an oxidised gossan of considerable depth, which is rich in primary cassiterite and wood-tin formed from tin sulphides, and which often contains native silver and cerargyrite together with much iron oxide.

In the time of the Spanish domination, the mines of Bolivia were worked only for gold, silver, and copper. The tin ores were rejected, and accumulated on the dumps and in old stopes, forming valuable deposits. Where the tin and silver ores are in close association, it is usual to roast the ore and leach out the silver before concentrating the cassiterite on jigs and tables. At the present day, however, the bulk of the Bolivian tin ore

comes from simple tin lodes free from silver. The barilla as shipped to England usually contains about 80 per cent. oxide of tin, 16 per cent. oxide of iron, and 4 per cent. silica, sometimes with traces up to 1 per cent. of sulphur and antimony. Some of the mines have installed electro-magnetic separators to improve the grade of the concentrates. Some stream tin is obtained, as at Potosi, Uncia and Hallagua. The gravel at Uncia is up to 90 feet in thickness and is worked by shafts, as the cassiterite is mainly at the bottom.

OTHER SOUTH AMERICAN STATES -- Chile and Peru export large quantities of tin ore mined in Bolivia, but apart from the last-named state there appears to be no appreciable production in South America. Tin deposits, many of them workable, are known to occur in many parts, and transport difficulties are the chief obstacle to the development of some of these deposits. In Argentina cassiterite occurs in granulite in the provinces of Catamarca and La Rioja.

MEXICO -- Cassiterite is widely distributed in Mexico, and has been worked by the natives in Durango, Jalisco, Guanajuato, San Luis Potosi, Aguas Calientes and Coahuila. As in Bolivia, the mineral occurs in volcanic rocks of Tertiary age usually in rhyolites with porphyritic quartz and felspar, in rhyolite-tuffs, or occasionally in trachyte (Durango). It is found in fissures and fault-planes in mineralised belts in these rocks, sometimes limited between well-defined walls, sometimes impregnating the altered country rock for a considerable distance. Chalcedony is the commonest of the associated minerals, and others are quartz, opal, calcite, oxides of iron and manganese, fluorite, topaz, durangite (fluoro-arsenate of sodium, aluminium and iron), wolframite and bismuth ores. Nodules of crystalline cassiterite are found showing a radiating structure and weighing as much as 25 lb. Alluvial deposits also occur, as at Tepezaca in Aguas Calientes.

Tin mining was carried on in the Aztec period and still continues on a small scale, the output of tin being under 50 tons a year. The ore is cobbled by hand to about $\frac{1}{4}$ inch, and washed first in a planilla (a hole in the ground with a sloping surface about 5 feet long draining to a cup-shaped hollow), and finally in a wooden batea. The dried concentrate usually contains 45 to 65 per cent. of tin. The blast furnaces are built of stone and clay, are only 2 feet 6 inches high, and have two bellows of ox-hide. The concentrate is smelted with charcoal and hard-head obtained by crushing and washing the

slag from previous operations. The metal produced contains from 90 to 96 per cent. of tin, and is sold locally.

UNITED STATES.—The United States is the largest consumer of tin in the world, taking about 40 per cent. of the world's output before the war and over 50 per cent. in 1916 and 1917. Nevertheless, its production of tin ore is insignificant, and it had till recently no tin-smelting industry, even the ore raised in the country being sent, for the most part, to the Straits Settlements for smelting. Its large requirements were met by tin imported in the metallic state, mostly from the Straits by way of England, but direct shipments from the Straits Settlements and the Dutch East Indies have increased during the war.

Table 75
Output of Tin Ore in the United States
In short tons (2,000 lb.)

	1910	1911	1912	1913	1914	1915	1916	1917
Quantity, short tons	59	66*	107	84	104*	102*	232	251
Value	\$1,885	\$1,799	\$6,000	\$7,229	\$3,867	\$6,426	\$5,393	---

* Metallic equivalent

Table 76
Imports of Tin Ore into the United States in the years ending
June 30th, 1916 to 1918. Imports for previous years are
not published

In tons (2,240 lb.)

Whence Imported	1915-16	1916-17	1917-18.
South America	5,415	5,110	---
Central America	2	---	---
China	---	10	---
Total	5,417	5,120	14,816
Value	\$71,899	\$84,435	\$2,144,013

The war rendered uncertain the supply of tin from British sources, and at the same time stopped the export of Bolivian ore to Germany. These circumstances have resulted in the

establishment of a considerable tin-smelting industry in the United States, treating Bolivian ore, the purer ores from British sources not being available for smelting outside the British Empire. Electrolytic refining of the tin is being tried. The first tin-smelting works, excluding an unfortunate attempt in the past, began operations at Perth Amboy, New Jersey, early in 1916, and is reported to have produced 3,800 tons of metal from Bolivian concentrates during that year. Other plants constructed or planned by American companies, both in the United States and in Bolivia or Peru, have an estimated capacity of some 35,000 tons of metal annually, which exceeds the present ore-output of Bolivia and also the smelting capacity of Great Britain. So great an expansion of the world's smelter capacity, accompanied as it is by diminishing ore production, must lead to keen competition for ore in the immediate future. The output of tin ore in the United States is given in Table 75, and Table 76 shows the imports of ore.

Table 77 shows the imports of tin. The figures for 1912-13 were the largest on record, but those for 1915-16 are 25 per cent. higher than these. Including tin in ore the total imports for 1917-18 are estimated at 78,100 short tons. In 1916 the production of tin-plate amounted to 1,383,200 short tons, or double the production in 1909, and 260,930 short tons of plate were exported in the fiscal year 1916-17.

Alaska is the only commercial producer of tin ore, about two-thirds of the output in 1916 coming from dredges in the York district, and the remainder from gold-tin placers in the Hot Springs district on the Lower Tanana. There is also some lode mining on the Lost River. Stream tin was first discovered in 1900 on Buhna Creek, near York, some twelve miles south-east of Cape Prince of Wales in the western part of the Seward Peninsula.

In this district the placer deposits of Buck Creek and Lost and Anikovik Rivers have been the chief producers, the last named yielding gold as well as tin ore. Lode mining has been carried on, to a small extent, at Cape Mountain and on the Lost River, and lodes are also known to exist at Ear Mountain, Buck Creek, Brooks Mountain and other localities. In the Lost River region, dykes of quartz-porphyry in limestone contain irregular seams and stringers of quartz and lithia-mica, with which are associated cassiterite and wolframite. Pyrite, arsenopyrite, galena, zinc-blende and molybdenite are sometimes present, and the chief gangue minerals are fluorite, zinnwaldite and topaz. On Brooks Mountain, at the head of

Table 77
Imports of Tin into the United States in the years ending June 30th, 1910-1917

Countries where Imported	1909-10	1910-11	1911-12	1912-13	1913-14	1914-15	1915-16	1916-17
United Kingdom	8,885	79,224	37,255	26,117	26,315	22,954	20,865	29,973
Strait Settlements	18,837	15,880	16,358	5,142	19,279	21,577	19,804	28,116
Hong Kong	512	918	954	1,563	369	369	2,536	2,536
Canada	12	80	94	57	86	101	117	117
Australia	19	508	235	21	146	149	198	1,493
Total from British Possessions	47,876	108,068	59,979	53,443	97,111	45,101	63,931	53,229
Austria-Hungary	—	24	59	28	—	—	—	—
Belgium	—	4	11	302	—	—	—	—
France	43	60	511	155	127	—	80	—
Germany	2,222	2,622	1,983	1,543	2,654	251	—	—
Netherlands	417	2,676	2,225	1,791	413	146	—	—
China	—	—	—	15	—	11	979	2,168
Dutch East Indies	—	—	—	—	28	1,815	7,112	12,944
Other Foreign Countries	—	5	4	20	28	15	189	447
Total from Foreign Countries	2,691	4,852	1,026	3,915	2,078	2,241	8,061	15,559
Total	5,567	51,720	55,002	57,358	59,089	47,432	71,992	68,788
Value	6,431,152	7,023,320	6,027,958	11,065,124	9,213,016	6,412,004	10,599,351	11,457,520

* Including 118 tons from Japan and 68 tons from South America.

the Lost River, the tin-iron borates hulsite and paigeite occur in limestone metamorphosed by a granite intrusion.

In the Yukon basin the placer deposits of Sullivan Creek, Tanana River, in the Hot Springs district, yield cassiterite and gold, and stream tin also occurs in the Circle and Ruby districts. A small amount of the Alaskan tin concentrates has been smelted at Seattle; some has been sent to Swansea; but the greater part has been shipped to Singapore for treatment.

On the borders of North and South Carolina, at Gaffney, King's Mountain and Lincolnton, small amounts of tinstone have been obtained from alluvial deposits and from pegmatite dykes which traverse decomposed gneiss. The Black Hills of South Dakota and Wyoming include two tin-bearing regions, Spearfish and Tinton in the north and Harney Peak in the south, in both of which mining operations have had disappointing results. In Texas veins and impregnations in granite have been mined on the east slope of Mount Franklin, ten miles north of El Paso. The concentrate was smelted on the spot in a small oil-fired reverberatory furnace, and the output was 3 tons of block tin in 1910 and 4 tons in 1911.

In Lander County, Nevada, mammillary cassiterite occurs with hematite, chaledony, opal, tridymite and quartz in Tertiary rhyolite. Tinstone also occurs in veins in the Shenandoah valley, Virginia, in San Diego County, and at Lomescal, California, and at a number of other localities.

The recovery of "secondary tin," mainly from clean tin scrap, and to a less extent from old tin cans, etc., is an important industry in the United States. In 1916 the amount thus recovered was about 24 per cent of the tin imported into the country, the amount being 17,400 tons valued at £3,152,300. The quantity recovered as tin was 7,600 tons, and that in alloys and chemical compounds 9,800 tons. The latter consisted mainly of tin chloride, with some tin oxide, putty powder, etc., and alloys such as babbitt metal, bronze, solder, pewter and electrotype metal.

REFERENCES TO LITERATURE ON TIN

GENERAL

- Beck, R.—The Nature of Ore Deposits, translated by W. H. Weed. *The Engineering and Mining Journal*, New York and London, 1905.
- Beyschlag, F., J. H. L. Vogt and P. Krusch.—The Deposits of the Useful Minerals and Rocks, translated by S. J. Truscott. Macmillan & Co., London, 1914-16.
- Colonial Reports. H.M. Stationery Office, London.
- Davies, D. C.—A Treatise on Metalliferous Minerals and Mining. Crosby Lockwood, London, Sixth Edition, 1901.
- De Launay, L.—Gîtes Minéraux et Métallifères. Ch. Béranger, Paris et Liège, 1913.
- Diplomatic and Consular Reports. H.M. Stationery Office, London.
- Fawns, S.—Tin Deposits of the World. *Mining Journal*, 1905.
- Ferguson, H. G., and A. M. Bateman.—Geologic Features of Tin Deposits, *Econ. Geol.*, 1912, 7, 209.
- Goßland, W.—The Metallurgy of the Non-ferrous Metals. Griffin, London, Second Edition, 1918.
- Grünwald, J. (translated by H. H. Hodgson).—The Raw Materials for the Enamel Industry. Griffin, London, 1914.
- Home Office.—Mines and Quarries. Part IV. Colonial and Foreign Statistics. H.M. Stationery Office. Annual.
- Jones, W. R.—Tin and Wolfram Ores, *Mining Magazine*, 1917, 17, 230.
- Lacroix, A.—Minéralogie de la France et de ses Colonies. Baudry et Cie., Paris, 1893-1913.
- Lindgren, W.—Mineral Deposits. McGraw Hill Book Co., New York and London, 1913.
- Metal Statistics. American Metal Market Co., New York. Annual.
- Mineral Industry. McGraw Hill Book Co., New York and London. Annual.
- Phillips, J. A., and H. Louis.—A Treatise on Ore Deposits. Macmillan & Co., Second Edition, 1896.
- Ries, H.—Economic Geology. John Wiley, Fourth Edition, 1916.
- Singewald, J. T., Jr.—Some Genetic Relations of Tin Deposits, *Econ. Geol.*, 1912, 7, 263.

REFERENCES TO LITERATURE ON TIN 101

- Steinhart, O. J.—The Sale of Tin Ores, *Min. Mag.*, 1912, 6, 202.
 Thibault, P. J.—Metallurgy of Tin. Pitman, London, 1908.
 Thomas, H. H., and D. A. MacAlister.—The Geology of Ore Deposits. Arnold, London, 1909.
 Turner, T.—Tin: Thorpe's Dictionary of Applied Chemistry. Longmans, London, 1913.
 Symposium on the Conservation of Tin. *Chem. and Met. Eng.*, 1918, 19, 656.

UNITED KINGDOM

- Statement of the Trade of the United Kingdom with Foreign Countries and British Possessions. H.M. Stationery Office. Annual.
 Home Office.—Mines and Quarries. Part III, Output. H.M. Stationery Office. Annual.
 Flett, J. S., and C. T. Clough.—Magnetite with Tinstone from Ross-shire, *Summ. Prog. Geol. Survey for 1903, 1904*, p. 58.
 Hill, J. B., and D. A. MacAlister.—The Geology of Palmouth and Truro and of the Mining District of Camborne and Redruth. *Mem. Geol. Survey*, 1906.
 MacAlister, D. A.—Geological Aspects of the Lodes of Cornwall, *Econ. Geol.*, 1908, 3, 361.
 Maclaren, M.—The Geology of the East Pool Mine, *Min. Mag.*, 1917, 18, 245.
 Reid, C., and others.—The Geology of the Lund's End District. *Mem. Geol. Survey*, 1907.
 ————The Geology of the Country around Tavistock and Launceston. *Mem. Geol. Survey*, 1911.
 ————The Geology of Dartmoor. *Mem. Geol. Survey*, 1912.
 Ussher, W. A. E., and others.—The Geology of the Country around Bodmin and St. Austell. *Mem. Geol. Survey*, 1909.

CEYLON

- Imperial Institute Report on the Results of the Mineral Survey of Ceylon, 1904-5. Colonial Reports—Miscellaneous No. 37 [Cd 3190], 1906, 36, 40.
 ————1905-6. Col. Rept. Misc. No. 42 [Cd 3762], 1907, 11, 13, 14, 16, 19, 29, 30.
 ————1906-7 and 1907-8. Col. Rept. Misc. No. 74 [Cd 5390], 1910, 10.
 ————Col. Rept. Misc. No. 87 [Cd 7175], 1914, 4.
 Coomaraswamy, A. K.—Mineralogical Survey Report. Ceylon Administrative Report for 1904, E. 10.
 ————for 1905, E. 9.

HONG KONG

- Administrative Reports. Hong Kong. Annual.
 Colonial Reports. Annual. H.M. Stationery Office, London.

INDIA

- Mineral Production of India. *Rec. Geol. Surv. India*. Annual. Quinquennial Review of Mineral Production for the years 1909 to 1913. *Rec. Geol. Surv. India*, 1915, **46**.
- Ball, V.—Geology of India. Part III. Economic Geology. *Geol. Surv. India*, 1881.
- Bleeck, A. W. G.—Wolframite in Tavoy. *Rec. Geol. Surv. India*, 1913, **43**, 48.
- Brown, J. C.—The Cassiterite Deposits of Tavoy. *Rec. Geol. Surv. India*, 1918, **49**, 23.
- Hayden, H. H. (Fin at Nuringa, Hazaribagh district).—General Report for 1911. *Rec. Geol. Surv. India*, 1912, **42**, 79.
- Holland, Sir F. H. (Meigui District). General Report for 1907, 1908. *Rec. Geol. Surv. India*, 1908, **37**, 38, and 1909, **38**, 53.
- Hughes, T. W. H. Tin mining in Meigui District. *Rec. Geol. Surv. India*, 1889, **22**, 188.

MALAYA

- Federated Malay States. Report on the Administration of the Mines Dept., etc. F.M.S. *Government Gazette*. Annual.
- Malay States. Report on the Federated Malay States. F.M.S. *Government Gazette*; also H.M. Stationery Office. Annual.
- Reports on the Unfederated Malay States under British Protection. H.M. Stationery Office. Annual.
- Negri Sembilan Administration Report. F.M.S. Government Printing Office, Kuala Lumpur. Annual.
- Pahang Administration Report. F.M.S. Government Printing Office, Kuala Lumpur. Annual.
- Perak Administration Report. F.M.S. Government Printing Office, Kuala Lumpur. Annual.
- Selangor Administration Report. F.M.S. Government Printing Office, Kuala Lumpur. Annual.
- Straits Settlements. Return of Imports and Exports. Singapore. Annual.
- Belfield, H. C.—Handbook of the Federated Malay States. Stanford, London, Third Edition, N.D.
- Brelich, H.—Mining in Trengganu. *Min. Mag.* 1915, **13**, 263.
- Collet, O. J. A.—L'Étain. Étude Minière et Politique sur les États Fédérés Malais. Falk, Brussels, N.D.
- Graham, W. A.—Kelantan a State of the Malay Peninsula. MacLehose, Glasgow, 1908.
- Jones, W. R.—The Origin of the Secondary Stanniferous Deposits of the Kinta District, Perak. *Quart. Journ. Geol. Soc.*, 1917, **72**, 165.
- Mineralisation in Malaya. *Min. Mag.*, 1915, **13**, 195 and 322.

- Scrivenor, J. B.—Geologist's Report of Progress, Sept. 1903—Jan. 1907. F.M.S. Government Press, Kuala Lumpur, 1907.
- Geologist's Annual Report. F.M.S. Government Press, Kuala Lumpur.
- The Geology and Mining Industries of Ulu Pahang. F.M.S. Government Printing Office, Kuala Lumpur, 1911.
- The Geology and Mining Industry of the Kinta District, Perak. F.M.S. Government Printing Office, Kuala Lumpur, 1913.
- Notes on Prospecting for Tin Ore in the Federated Malay States. F.M.S. Government Press, Kuala Lumpur, 1911.
- The Origin of Tin Deposits. F.M.S. Government Printing Office, Kuala Lumpur, 1909.
- The Deposits of Tin Ore in the Foothills of the Kinta Valley, Perak. Times of Malaya Press, Ipoh, 1914.
- On an Occurrence of Native Copper with Tin Ore in the Federated Malay States. *Malayan and Malacca*, 1908, 10, **15**, 299.
- The Lahat "Pipe." *Quart. Journ. Geol. Soc.*, 1900, **65**, 382.
- The Limestone Concretion Rock of Kinta. *Quart. Journ. Geol. Soc.*, 1910, **66**, 33.
- The Gopeng Beds of Kinta. *Quart. Journ. Geol. Soc.*, 1912, **68**, 140.
- The Geological History of the Malay Peninsula. *Quart. Journ. Geol. Soc.*, 1913, **69**, 33.
- Notes on Geomorphology of the Malay Peninsula. *Mineralogical Magazine*, 1913, **16**, 11.
- Malayan Geology. *Mineralogical Magazine*, 1918, **19**, 33.
- Warford Lock—Mining in Malaya for Gold and Tin. Crowther & Goodman, London, 1907.
- Wright, A., and F. H. Reid. The Malay Peninsula. Fisher Unwin, 1912.

GOLD COAST

- Kitson, A. E. *Rep. Geol. Surv.*, 1913, p. 7.
- Rep. Geol. Surv.*, 1915, p. 7.

NIGERIA

- Blue Book: Colony and Protectorate of Nigeria. Govt. Printer, Lagos. Annual.
- Colonial Reports—Nigeria. H.M. Stationery Office, London. Annual.
- Miscellaneous. Imperial Institute Reports on the Mineral Survey of Northern Nigeria, [Cd. 875], 1906, [Cd. 3914], 1908, [Cd. 3915], 1908, [Cd. 4716], 1909, and [Cd. 5899], 1911.
- Imperial Institute Report on the Mineral Survey of Southern Nigeria [Cd. 2876], 1906.

104 REFERENCES TO LITERATURE ON TIN

- Calvert, A. F.—Nigeria and its Tin Fields. Stanford, London, 1912.
 Canning, A. R.—The Alluvial Tin Properties belonging to the Northern Nigeria (Bauchi) Tin Mines, Ltd., *Min. Mag.*, 1918, **18**, 176.
 Falconer, J. D.—The Geology and Geography of Northern Nigeria. Macmillan, London, 1911.
 ———Nigerian Tin, its Occurrence and Origin, *Econ. Geol.*, 1912, **7**, 542.
 Nicholls, H. E.—The Nature of Nigerian Tin Deposits, *Min. Mag.*, 1916, **14**, 371.
 Thomas, W. F.—Tin Deposits in Nassarawa, Nigeria, *Min. Mag.*, 1918, **19**, 240.

NYASALAND

- Colonial Reports—Miscellaneous—Imperial Institute Reports on the Results of the Mineral Survey, [Ed. 3916] 1908, [Ed. 4908], 1909.

RHODESIA

- Rhodesia Chamber of Mines, Bulawayo.—Annual Report.
 Southern Rhodesia.—Report of the Secretary for Mines. Govt. Printer, Salisbury, Rhodesia.—Annual.
 Rhodesia Munitions and Resources Committee.—Interim Report for the Period ended June 30th, 1916.—Bulawayo, 1916.
 Maufe, H. B.—The Geology of the Victoria Tin Field. Rep. Dir. Geol. Surv. S. Rhodesia for 1911.—Argus Publishing Co., Salisbury and Bulawayo, 1912.
 ———Geological Notes on the Lateopristine Limestone, *Rhodesian Mining Review*, 1911, **7**, 530.
 Zealley, A. E. V.—The Mineral Resources of Rhodesia. Appendix to Ninth Ann. Rep. of the Rhodesia Museum, Bulawayo, 1910.

UNION OF SOUTH AFRICA

- Report of the Government Mining Engineer.—Government Printing Office, Pretoria.—Annual.
 Trade and Shipping of the Union of South Africa and of Southern and Northern Rhodesia.—Government Printing Department, Cape Town.—Annual.
 Hatch, F. H.—Report on the Mines and Mineral Resources of Natal. Clay, London, 1910.
 Humphrey, W. A.—On a Portion of the Bushveld bordering the Crocodile River and including the Rooiberg Tinfield. *Rep. Geol. Surv. for 1908*. Govt. Printing Office, Pretoria, 1909.
 Johnson, J. P.—The Ore Deposits of South Africa. Part I. Crosby Lockwood, London, 1908.

REFERENCES TO LITERATURE ON TIN 105

- Kynaston, H.—Geological Survey Report for 1911. Govt. Printing Office, Pretoria, 1912.
- On a Portion of the Waterberg District West and North-west of Warmbaths. *Rep. Geol. Surv. for 1909*, Pretoria, 1910.
- and E. T. Mellor. — The Geology of the Waterberg Linfields. Geol. Surv. Transvaal, Mem. No. 4. Govt. Printing Office, Pretoria, 1909.
- The Geology of the Country round Warmbaths and Nylostroom, including the Roodberg Linfields. Geol. Surv. Pretoria, 1912.
- and A. L. Hall. — The Geology of the Country round Potgietersrust. Geol. Surv. S. Africa, Explanation of Sheet 7. Govt. Printing Office, Pretoria, 1911.
- Mellor, E. T. — On a Portion of the Waterberg District West of Potgietersrust. *Rep. Geol. Surv. for 1908*. Govt. Printing Office, Pretoria, 1909.
- The Geology of a Portion of the Waterberg District North of Nylostroom. *Rep. Geol. Surv. for 1909*. Pretoria, 1910.
- Rogers, A. W., and A. E. Du Toit. — The Geology of Cape Colony. Longmans, London. Second Edition, 1909.
- Frevor, T. G. — Article on "Tin" in the Official Year Book of the Union of South Africa. Pretoria, 1918.
- Wagner, P. A. — Notes on the Tin Deposits in the Vicinity of Cape Town. *Trans. Geol. Soc. S. Africa*, 1909, **12**, 102.

SWAZILAND

- Colonial Office Report. Swaziland. H.M. Stationery Office, Annual.
- Gairard, J. J. — Hydraulic Tin Mining in Swaziland. *Bull. Inst. Min. and Metall.*, No. 139, 1917.
- Hall, A. L. — Notes on the Tin Deposits of Embabalan and Forbes Reef in Swaziland. *Trans. Geol. Soc. S. Africa*, 1913, **16**, 142.

CANADA

- Report on the Mineral Production of Canada. Canada Dept. of Mines, Mines Branch. Annual.
- Summary Report of the Geological Survey, Department of Mines, for 1907, 1908, 1910, 1911, and 1912.
- Johnston, R. A. A. — A List of Canadian Mineral Occurrences. Canada Geol. Surv., Memoir 74. No. 61, Geological Series, 1915.

AUSTRALIA

- Record of Mining in the Northern Territory of South Australia. Adelaide, 1900.
- Report of the Department of Mines, New South Wales. Annual.
- Western Australia. Annual.

- Report of the Secretary for Mines, Tasmania. Annual.
 ----- Victoria. Annual.
 Report of the Under Secretary for Mines, Queensland. Annual.
 Report of the Administrator, Northern Territory. Annual.
 Ball, L. C.—Tin, Copper, and Silver Mining in the Stanthorpe District. Geol. Surv. Queensland, Pub. 191, 1904.
 --- Gold, Platinum, Tinstone and Monazite in the Beach Sands of the South Coast. Geol. Surv. Queensland, Pub. 198, 1905.
 --- The King of the Ranges Tin Mine, Watsonville. Geol. Surv. Queensland, Pub. 222, 1910.
 --- The Etheridge Mineral Field (the Potentialities of the Southern Portion). Geol. Surv. Queensland, Pub. 245, 1915.
 Bathurst, F. H. Mount Bischoff. *Min. Mag.*, 1910, **3**, 105.
 Blatchford, F. Mineral Resources of the North West Division. Investigations in 1912. Geol. Surv. W. Australia, Bull. No. 52, 1913.
 --- The King's Sound Tin Mine, West Kimberley. Geol. Surv. W. Australia, Bull. No. 59, 1914, p. 242.
 Brown, H. Y. L. Record of the Mines of South Australia. Govt. Printer, Adelaide, Fourth Edition, 1908, p. 310.
 Cameron, W. E. The Kangeroo Hills Mineral Field. Geol. Surv. Queensland, Pub. 167, 1901.
 --- The Hetherington Tin Field. Geol. Surv. Queensland, Pub. 192, 1904.
 --- The Annan River Tinfield. Geol. Surv. Queensland, Pub. 210, 1907.
 --- The Tin Lodes of Sandy Creek, Charters Towers District. Geol. Surv. Queensland, Pub. 235, 1911.
 Carne, J. E. The Tin-Mining Industry and the Distribution of Tin Ores in New South Wales. N.S.W. Dept. of Mines, 1911.
 Conder, H. The Tinfields of North Dundas. Dept. of Mines, Tasmania. Geol. Surv., Bull. No. 76, 1918.
 Dunn, F. J. Tin Ore on Wilson's Promontory. Rec. Geol. Surv. Victoria, Vol. II, Part 2, 1907, p. 193.
 --- Tin Ore at Glen Wills. *Ibid.* p. 194.
 --- Gold and Tin Workings at Tin Creek, near Buxton. *Ibid.* p. 105.
 --- Tin Ore at Koetong and Cudgewa. *Ibid.* Vol. III, Part I, 1909, p. 90.
 Dunstan, B. The Stanhills Tinfields (near Croydon). Geol. Surv. Queensland, Pub. 211, 1907.
 Feldtman, F. R. The Ore Occurrences of the Kapanga Mine, Greenbushes Tinfield. Geol. Surv. W. Australia, Bull. No. 59, 1914, p. 156.
 Godfrey, J. R. The Ardlethan Tinfield. N.S. Wales Dept. of Mines, 1915.
 Gregory, J. W. The Mount Cudgewa Tinfield. Bull. Geol. Surv. Victoria, No. 22, 1907.

- Herman, H.—Economic Geology and Mineral Resources of Victoria.
Bull. Geol. Surv. Victoria, No. 34, 1914. (Reprinted from
Handbook to Victoria, Brit. Assoc. for the Advancement of Science,
Australian Meeting, 1914.)
- Howitt, A. M.—The Tertiary Tin Deposits. Geol. Surv. Victoria,
Vol. III, Part I, 1909, p. 51.
- Kitson, A. E.—The Economic Minerals and Rocks of Victoria.
Dept. of Mines, Victoria, 1906. Reprinted from the *Victorian*
Year-book for 1905.
- Liversidge, A.—Minerals of New South Wales. Triebner, London,
1888.
- Maclaren, J. M.—On the Stannary Hill—Tin Mines, Fureka Creek,
Watsonville District. Geol. Surv. Queensland, Pub. 146, 1900.
- Maitland, A. G.—The Geological Features and Mineral Resources
of the Pilbara Goldfield. Geol. Surv. Western Australia.
Reprint of Bulls. No. 15, 20, and 21, 1908.
- Geological Investigation of part of the Carey Cove, Ashburton,
and West Pilbara Goldfields. Geol. Surv. Western Australia,
Bull. No. 33, 1909.
- and A. Montgomerie.—The Geology and Mineral Industry of
Western Australia. Geol. Surv. W. Australia, Bull. No. 50,
1911.
- Pittman, E. F.—The Mineral Resources of New South Wales.
Geol. Surv. N. S. Wales, 1901.
- and A. G. Maitland.—Mining Field of Australia. Brit. Assoc.
Handbook for Australia, Melbourne, 1914.
- Saint Smith, F. C.—Geology and Mineral Resources of the Stan-
thorpe, Ballandean and Wallangarra Districts. Geol. Surv.
Queensland, Pub. 141, 1914.
- Geology and Mineral Resources of the Cocktown District Tin-
fields. Geol. Surv. Queensland, Pub. 150, 1916.
- Simpson, E. S., and C. G. Gibson.—The Distribution and Occurrence
of the Base Metals in Western Australia. Geol. Surv. W.
Australia, Bull. 39, 1907.
- Skertchlev, S. B.—On the Deep Tin Field, Herberton. Geol.
Surv. Queensland, Pub. 115, 1896.
- On the Tin Mines of Watsonville, etc. Geol. Surv. Queens-
land, Pub. 119, 1897.
- On the Geology of the Country round Stentle 190 and Warwick.
Geol. Surv. Queensland, Pub. 120, 1898.
- Twelvetreves, W. H.—Report on Cox's Bight Tinfield, Tasmania.
Geol. Surv. 1906.
- Report on the Renison Bell Tinfield, Tasmania. Geol. Surv.,
1906.
- The Scamander Mineral District, Tasmania. Geol. Surv., Bull.
No. 9, 1911.
- The Middlesex and Mount Claude Mining Field, Tasmania.
Geol. Surv., Bull. No. 14, 1913.

- Twelvetrees, W. H.—The Gladstone Mineral District, Tasmania. Geol. Surv., Bull. No. 25, 1916.
- and L. K. Ward.—Geological Examination of the Zeehan Field, Tasmania. Geol. Surv., Bull. No. 7, 1909.
- — — — — The Ore-bodies of the Zeehan Field, Tasmania. Geol. Surv., Bull. No. 8, 1910.
- Ward, L. K.—The Tinfield of North Dundas, Tasmania. Geol. Surv., Bull. No. 6, 1909.
- — — — — The Mount Balfour Mining Field, Tasmania. Geol. Surv., Bull. No. 10, 1911.
- — — — — The Cross River Tinfield, Tasmania. Geol. Surv., Bull. No. 12, 1911.
- Waterhouse, L. L.—The Stanley River Tinfield, Tasmania. Geol. Surv., Bull. No. 15, 1914.
- — — — — The South Heemskirk Tinfield, Tasmania. Geol. Surv., Bull. No. 21, 1916.
- Whitelaw, O. A. L., J. P. L. Kenny, and J. G. Easton.—The Mitta Mitta Tin and Gold Field. Bull. Geol. Surv. Victoria, No. 37, 1915.
- — — — — Notes on the Geology of the Greenbushes Tinfield (with special reference to the Deep Leads). Geol. Surv. W. Australia, Bull. No. 32, 1908.
- Woodward, H. P.—The Geology and Ore Deposits of the West Pilbara Goldfield. Geol. Surv. W. Australia, Bull. No. 41, 1911.

NEW ZEALAND

- Mines Statement. Govt. Printer, Wellington. Annual.
- New Zealand Geological Survey, various Bulletins.
- Handbook of New Zealand Mines. Govt. Printer, Wellington, 1887.
- Binns, G. J.—Mining in New Zealand, *Trans. Fed. Inst. Min. Eng.*, 1892.

AUSTRIA HUNGARY

- Statistik des Auswärtigen Handels der Österr.-Ungar. Monarchie. Vienna. Annual.

FRANCE

- Le Commerce de la France. Paris, Imprimerie Nationale. Annual.

GERMANY

- Statistik des Deutschen Reichs. Berlin. Annual.
- Singewald, J. T., Jr.—The Erzgebirge Tin Deposits, *Econ Geol.*, 1910, 5, 166 and 265.

PORTUGAL

- Down, T. A.—Tin and Tungsten in Portugal, *Min. Mag.*, 1916, 14, 19.

REFERENCES TO LITERATURE ON TIN 109

RUSSIA

The Russian Year-Book. Eyre & Spottiswoode. Annual.

SPAIN

Preiswerk, H. — Über einige Zinnvorkommen in Spanien und Portugal, *Zeit. f. prakt. Geol.*, 1913, **21**, 74.

CHINA

The China Year-book. Routledge. Annual.

The Maritime Customs. Statistical Series. Shanghai. Annual.

Brown, G. E. — Visiting the Hunan Fields. *Min. Mag.*, 1915, **13**, 141.

Collins, W. F. — Tin Production in the Province of Yunnan, China, *Trans. Inst. Min. and Met.*, 1909, **19**, 187.

Wheler, A. S. — Metalliferous Mines of Hunan. *Min. and Sci. Press*, 1916, **112**, 137.

Yung, M. B. — Tin and Coal Deposits of the Tu Chuan District, China, *Bull. Amer. Inst. Min. Eng.*, 1914, **93**, 2451.

DUTCH EAST INDIES

Year-book of the Netherlands East India. Sub-dept. of Industry and Commerce, Batavia, Java.

INDO-CHINA

Statistiques de l'Industrie Minière dans les Colonies Françaises. Paris. Bureau de Vente des Publications Coloniales Officielles.

JAPAN

Mining in Japan. Bureau of Mines, Japan, 1909.

SIAM

Statistical Year Book. Dept. of Commerce and Statistics. Annual.

BELENGO, CONGO

Ball, S. H., and M. K. Shaler. — Economic Geology of the Belgian Congo, *Econ. Geol.*, 1914, **9**, 640.

Farrell, J. R. — The Copper and Tin Deposits of Katanga, *Eng. and Min. Journ.*, 1908, **85**, 747.

Guillemin, C. — Zur Kenntnis der Lagerstätten in der Provinz Katanga, *Zeit. f. prakt. Geol.*, 1913, **21**, 335.

PORTUGUESE EAST AFRICA

Companhia de Moçambique. Mineral Survey Map, Explanatory Notes and Photographs.

SOUTH-WEST AFRICA

- Calvert, A. F. - The German African Empire. Werner Laurie, 1916.
 Dahms, A. - Über Erzlagerstätten in sauren Eruptivgesteinen Deutsch-Südwestafrikas. *Zeit. f. Prakt. Geol.*, 1912, **20**, 240.
 Wagner, P. A. - The Geology and Mineral Industry of South-West Africa. Union of South Africa Mines Dept., Geol. Surv. Mem. No. 7. Govt. Printing Office, Pretoria, 1916.

BOLIVIA

- Bancroft, H. - The Tin Situation in Bolivia. *Bull. Amer. Inst. Min. Eng.*, 1913, **81**, 2311.
 Lewis, H. A. - The Berenguela Tin District. *Min. Mag.*, 1914, **11**, 309.
 Lincoln, F. C. - Milluni Tin Mining District, Bolivia. *Min. and Sci. Press*, 1915, **110**, 470.
 --- Qumisa Cruz Tin District, Bolivia. *Ibid.*, 721.
 --- Potosi Tin Mining District, Bolivia. *Ibid.* 1915, **111**, 127.
 --- Oruro Tin-Silver District, Bolivia. *Ibid.* 1917, **115**, 57.
 Rumbold, W. R. - The Origin of the Bolivian Tin Deposits. *Econ. Geol.*, 1909, **4**, 321.
 Singewald, J. L., and B. L. Miller. - The Mining Industry of Bolivia. *Eng. and Min. Journ.*, 1916, **102**, 1005.
 Wallé, P. - Bolivia. Town, London, 1914.
 Wepler, G. W. - Tin Mining in Bolivia. *Min. and Sci. Press*, 1914, **108**, 251.

MEXICO

- Master, G. C. - Tin Mining in Mexico. *Min. Mag.*, 1913, **9**, 199.
 Wittich, E. - Zinnerze in der Sierra von Guanajuato (Mexiko). *Zeit. f. Prakt. Geol.*, 1910, **18**, 121.

UNITED STATES

- Mineral Resources of the United States. Part I. U.S. Geol. Surv. Annual.
 Statistical Abstract of the United States. U.S. Dept. of Commerce. Annual.
 Collier, A. J. - The Tin Deposits of the York Region, Alaska. U.S. Geol. Surv., Bull. No. 229, 1904.
 Eakin, H. M. - Tin Mining in Alaska. Mineral Resources of Alaska: Report on Progress of Investigations in 1914. U.S. Geol. Surv., Bull. No. 622, 1915, p. 81.
 Hess, F. L. - The York Tin Region. Mineral Resources of Alaska: Report on Progress of Investigations in 1905. U.S. Geol. Surv., Bull. No. 284, 1906, p. 145.
 --- Tin Resources of Alaska. Mineral Resources of Alaska: Report on Progress of Investigations in 1911. U.S. Geol. Surv., Bull. No. 520, 1912, p. 89.

REFERENCES TO LITERATURE ON TIN III

- Knopf, A.—Geology of the Seward Peninsula Tin Deposits, Alaska.
U.S. Geol. Surv., Bull. No. 358, 1908.
- Some Features of the Alaskan Tin Deposits, *Econ. Geol.* 1909,
4, 214.
- Wood Tin in the Tertiary Rhyolites of Northern Nevada,
Econ. Geol. 1916, 11, 652.
- Weed, W. H.—The El Paso Tin Deposits. U.S. Geol. Surv., Bull.
No. 178, 1901.

